



## Bio-prototyping and thermoluminescence response of cellular rare earth ceramics



S.C. Santos\*, C. Yamagata, L.L. Campos, S.R.H. Mello-Castanho

Instituto de Pesquisas Energeticas e Nucleares—IPEN, Av. Prof. Lineu Prestes 2242, Cidade Universitaria, Sao Paulo, Brazil

### ARTICLE INFO

#### Article history:

Received 11 September 2015

Received in revised form 15 October 2015

Accepted 18 October 2015

#### Keywords:

Rare earths  
Lanthanides  
Bio-prototyping  
Thermoluminescence  
Ceramic processing

### ABSTRACT

The use of renewable materials is essential toward green economy. Vegetable structures are abundant, exhibit complex hierarchically built shape and an architecture that is promising to form functional materials. In this work using a mixture of rare earth oxides, which contain around 57 wt% yttrium oxide, cellular ceramics by bio-prototyping from the vegetable sponge *Luffa cylindrica* were produced and the thermoluminescence response was evaluated. By colloidal processing aqueous suspensions with 25 vol% solids content, pH 10, 1 wt% deflocculant and 0.2 wt% binder exhibited shear thinning behavior and apparent viscosity suitable for replica method. By thermal treatment at 1600 °C for 2 h in air biomorphic rare earth ceramics with dense microstructure and reticulated architecture were produced.

© 2015 Elsevier Ltd. All rights reserved.

### 1. Introduction

Rare earth elements (RE) have unique chemical and physical properties and therefore are very useful for high technological applications such as permanent magnets [1], batteries [2], thin films semiconductors [3], phosphors [4], petroleum catalysis [5], gas burners [6], radiation dosimeters [7], biological tracers [8] and diagnostic contrast [9]. Since no alternative materials that exhibit similar performance of RE have been found yet, UNEP (Global Environmental Alert Service) have done many alerts about the green economy vulnerability to rare earth minerals shortages [10]. In addition, any restriction in the production and supply of RE may have serious consequences for the world's transition to green energy supply, as well as may affect the global economy since the technologies are important in creating jobs, promoting economic growth, and fighting climate change.

From RE, yttrium oxide ( $Y_2O_3$ ) also known as yttria has intrinsic chemical and physical properties as melting point around of 2400 °C, refractive index of 1.9, thermal and chemical stability [11,12].  $Y_2O_3$  is used for processing of advanced materials as sintering additive [13], catalysis [14], phosphors [15], ionic conductors [16], thin films [17], special alloys [18] and lasers [19]. Abe et al. [20] prepared yttrium doped europium ( $Y_2O_3:Eu^{3+}$ ) nanoparticles by homogenous precipitation. The obtained nanoparticles exhibited strong and narrow red photo luminescent spectra, as well

as promising biocompatibility. Li et al. [21] produced yttrium doped zinc oxide nanofibers ( $ZnO:Y_2O_3$ ) by electrospinning method. The produced nanofibers exhibited uniform morphology, high specific surface area ( $40.2\text{ m}^2\text{ g}^{-1}$ ) and gas sensing. Santos et al. [22] developed  $Y_2O_3$  nettings with dense microstructure, reticulated structure and thermoluminescent response ( $\lambda = 550\text{ nm}$  and  $T = 150\text{ °C}$ ) by colloidal processing and followed by replica from a nylon–cotton template.

Innovative actions toward green economy involves the controlled use of RE and smart process. In this context, colloidal processing leads the formation of reliable ceramic components whereby the ceramic suspension structure is controlled for a desired shape forming. This method is followed by thermal treatment for consolidation of the particles and formation of the final microstructure [23–25]. Moreover, the use of renewable materials such as wood [26], coral [27], cotton [28], and vegetable sponge [29] as templates to produce biomorphic functional ceramics leads also to green economy consolidation. Santos et al. [30], developed  $\beta\text{-}Y_2Si_2O_7$  reticulated ceramics from biotemplating of the vegetable sponge gourd of *Luffa cylindrica*. The sponge architecture is promising for gas burner design because its reticulated structure can improve gas burning and light emission.

In this work a process to form cellular rare earth ceramics by bio-prototyping from *L. cylindrica* is presented. Apart from colloidal processing of rare earth oxides followed by replica method, cellular ceramics with reticulated structure and dense microstructure were produced.

\* Corresponding author.

E-mail addresses: [silas.cardoso@usp.br](mailto:silas.cardoso@usp.br), [silasc@ipen.br](mailto:silasc@ipen.br) (S.C. Santos).

## 2. Experimental

RE<sub>2</sub>O<sub>3</sub> powders (RE/wt%=Y/56.6; Dy/19.4; Er/6.5; Lu/4.1; Ho/3.1; Yb/2.0) with pycnometric density ( $\rho$ ) of 6.03 g cm<sup>-3</sup> and specific surface area (SSA) of 20.5.9 m<sup>2</sup> g<sup>-1</sup> were produced through calcination of rare earth carbonate as reported in our previous work [6].

The thermoluminescence characterization of RE<sub>2</sub>O<sub>3</sub> powders was performed with a TL reader (Risø TL/OSL-DA-20). The samples were evaluated at a heating rate of 10 °C s<sup>-1</sup> up to 400 °C in nitrogen atmosphere.

The mean particle size ( $d_{50}$ ) of RE<sub>2</sub>O<sub>3</sub> was measured by means of Photon Correlation Spectroscopy (PCS, ZetaPALS Analyzer, Brookhaven Instruments). For PCS measurements an aqueous suspension with 0.01 vol% solids at pH 10, which is a good condition to disperse particles [30], was prepared. For dispersion of particles tetraethylammonium hydroxide (TEAH, Sigma–Aldrich) was used as deflocculant. The homogenization of ceramic suspensions was performed on a ball mill for 24 h.

RE<sub>2</sub>O<sub>3</sub> aqueous suspensions with 25 vol% solids content were prepared at pH 10 from tetramethylammonium hydroxide (TEAH, Sigma–Aldrich), 1 wt% PAA (poly-acrylic ammonium acid, Sigma–Aldrich), 0.2 wt% CMC (carboxymethyl-cellulose, Sigma–Aldrich) based on the suspension weight. All suspensions were homogenized in a ball mill for 24 h, using alumina spheres ( $\phi_{\text{spheres}} = 10$  mm).

The flow behavior of RE<sub>2</sub>O<sub>3</sub> suspensions was evaluated with a rheometer (Haake RS600, Thermo Scientific). The sensor system consisted of a double-cone rotor and a stationary plate (DC60/1°). The flow behavior of the suspensions was characterized in the control rate mode (CR) and compared with rheological models available in rheometer database (Haake Rheowin Data Manager v. 3.61.0.1). All measurements were evaluated at 25° by increasing the shear rate ( $\dot{\gamma}$ ) from 0 to 1000 s<sup>-1</sup> in 5 min, holding for 2 min at 1000 s<sup>-1</sup> and returning to 0 s<sup>-1</sup> in 5 min. For each CR step 200 points were measured.

The vegetable sponge gourd (*L. cylindrica*, LCy) was used as a template once it exhibits a reticulated structure promising for gas burner technology. LCy samples were immersed in RE<sub>2</sub>O<sub>3</sub> aqueous suspension for 30 min (optimized time) [31]. The impregnated samples were sintered in a vertical furnace (Lindberg/Blue M), where the thermal treatment conditions were based on thermal and gravimetric analysis results of LCy fibers (TGA/TDA, S60/38336 Setaram). The microstructure of the LCy fibers, impregnated samples and biomorphic replicas were evaluated with scanning electron microscopy (SEM, TM3000Hitachi and SEM, INCAx-act Oxford Instruments). The crystalline structure of the biomorphic RE<sub>2</sub>O<sub>3</sub> replicas was evaluated by X-ray diffraction (XRD, Rigaku Multiflex), with scanning at 0.5° min<sup>-1</sup>, from 10–80° (2 $\theta$ ), Cu-K $\alpha$  radiation.

## 3. Results and discussion

The mean particle size distribution of RE<sub>2</sub>O<sub>3</sub> particles performed with PCS is shown in Fig. 1. As a result, RE<sub>2</sub>O<sub>3</sub> particles exhibited a nanosized particle distribution with a mean diameter ( $d_{50}$ ) of 722.6 nm, which is almost fifteen times higher than the theoretical diameter ( $d_{\text{BET}}$ ) calculated from specific surface area (SSA)  $d_{\text{BET}} = 48.7$  nm. This significant size difference was due to the shape factor (elongated particles, Fig. 1b) and the agglomerated state of particles, in which the agglomeration factor was very high around of 14.85. In addition, the difference between minor ( $d_{10}$ ) and major ( $d_{90}$ ) size distributions (Span) and the relative span were 294.1 nm and 0.41 respectively.

Particle characteristics have a significant effect on ceramic processing from suspensions such as, packing density, size and shape of pore interstices, rheological behavior and drying, as well as microstructure formation [32]. Besides, particles which are in colloidal scale are ruled by surface forces being able to agglomerate easily [33]. As RE<sub>2</sub>O<sub>3</sub> particles exhibit a shape factor far from spherical, nanosized particle distribution, high pycnometric density and agglomerated state the processing of ceramic suspensions have to be very effective in order to lead stable suspensions with suitable viscosity for replica method.

Fig. 2 shows the TL response of RE<sub>2</sub>O<sub>3</sub> powders. From the result is observed that there was no formation of TL peaks from  $\lambda = 350$  up to 750 nm. All emission of light took place on infrared range ( $\lambda = 750$ –4300 nm), where an intense peak was recorded at  $\lambda = 1000$  nm and  $T = 400$  °C. Considering that RE<sub>2</sub>O<sub>3</sub> is constituted of a mixture of rare earth oxides (RE/wt%=Y/56.6; Dy/19.4; Er/6.5; Lu/4.1; Ho/3.1; Yb/2.0), the RE activator ions can interfere in luminescence behavior of each other and consequently in the TL response. In addition, particle characteristics have influence on luminescence performance, e.g. particle size, particle shape and surface roughness. Feofilov [34] reported that the time life of RE<sup>3+</sup> ions tend to increase as a function of decreasing particle size. Bolshukhin [35] et al. showed that nanoparticles of Sr<sub>4</sub>Al<sub>2</sub>O<sub>3</sub>:Eu<sup>3+</sup> exhibits higher luminescence and luminous persistent.

The image by SEM of the LCy vegetable sponge used for formation of biomorphic ceramic components by replica method is shown in Fig. 3. The LCy template of pycnometric density  $\rho = 1.55$  g cm<sup>-3</sup> exhibits a reticulated structure (Fig. 3a), and fibers in random disposition like a web (Fig. 3b). The vegetable fibers presented a mean diameter of = 60  $\mu$ m and a specific surface area SSA = 22.5 m<sup>2</sup> g<sup>-1</sup>. In addition, vegetable fibers are composed of fibrils, which are joined together by a vegetal resin tissue (Fig. 3c).

The use of renewable materials is an important contribution for sustainable development. Nevertheless, it is usually necessary to do a previous treatment of the material before using [36–39]. The conditioning treatment depends on the type of vegetable sponge, type of soil, climate conditions and age of plant. For LCy template (Fig. 2d), the alkaline treatment with 2 wt% NaOH at 60 °C for 2 h was successful to remove surface substances such as cellulose and lignin. Besides, microchannels and scratches are visible on fibers surface (Fig. 2d—white arrows). In conclusion, the chemical treatment used in this work was suitable to clean fibers surface and to adequate the LCy template for impregnation method.

In Fig. 4 is shown the plot of flow curves of RE<sub>2</sub>O<sub>3</sub> suspensions in CR mode up to 1000 s<sup>-1</sup>. As described in our previous work [6], the stability conditions for RE<sub>2</sub>O<sub>3</sub> suspensions are pH 10, 1 wt% PAA and 0.2 wt% CMC. Ceramic suspensions based on 25 vol% RE<sub>2</sub>O<sub>3</sub> and prepared at these conditions exhibited shear thinning behavior, in which the apparent viscosity ( $\eta$ ) decreases as the shear rate ( $\dot{\gamma}$ ) increases. Extreme values of  $\eta$  are observed at  $\dot{\gamma} < 50$  s<sup>-1</sup> as a consequence of the ceramic suspension changed from static to flowing state. In addition, RE<sub>2</sub>O<sub>3</sub> suspension exhibited  $\eta < 100$  mPa s from  $\dot{\gamma} > 200$  mPa s, which indicates that ceramic particles were well dispersed. The rheological behavior of RE<sub>2</sub>O<sub>3</sub> suspension in CR mode fitted to Cross model ( $\eta_0 = 14.27$  mPa s;  $\eta_\infty = 23.11$ ;  $\dot{\gamma} = 2.397$  s<sup>-1</sup>;  $n = 0.2347$ ). Besides, the ceramic suspension exhibited a thixotropy around of 4.394.10<sup>6</sup> Pa.s<sup>-1</sup> due to particle characteristics (size and shape), which lead to formation of agglomerates. Furthermore, the thixotropic behavior can be associated with extension of polymers chains, particles deformation, and break down of particle agglomerates formed by CMC binder.

Shear thinning suspensions are suitable for replica method. In this context, the suspension exhibits low viscosity as undergo a shearing and shows high viscosity in static condition. Hence, the ceramic suspension remains on the template surface during impregnation method. In Fig. 5 are shown images by SEM of LCy

Download English Version:

<https://daneshyari.com/en/article/10629436>

Download Persian Version:

<https://daneshyari.com/article/10629436>

[Daneshyari.com](https://daneshyari.com)