Contents lists available at ScienceDirect

Applied Catalysis A: General

journal homepage: www.elsevier.com/locate/apcata

Silica material variation for the Mn_xO_y-Na₂WO₄/SiO₂

M. Yildiz^{a,**}, Y. Aksu^{b,1}, U. Simon^c, T. Otremba^{a,2}, K. Kailasam^{d,3}, C. Göbel^d, F. Girgsdies^e, O. Görke^c, F. Rosowski^f, A. Thomas^d, R. Schomäcker^a, S. Arndt^{a,*}

^a Technische Universität Berlin, Institut für Chemie, Technische Chemie, Sekr. TC8, Straße des 17. Juni 124, 10623 Berlin, Germany

^b Technische Universität Berlin, Institut für Chemie, Metallorganische Chemie & Anorganische Materialien, Straße des 17. Juni 115, 10623 Berlin, Germany

^c Technische Universität Berlin, Institut für Werkstoffwissenschaften und -technologien, Fachgebiet Keramische Werkstoffe, Sekr. BA3, Hardenbergstraße

40, 10623 Berlin, Germany

^d Technische Universität Berlin, Institut für Chemie, Funktionsmaterialen, Sekr. BA2, Hardenbergstraße 40, 10623 Berlin, Germany

^e Fritz-Haber-Institut der Max-Planck-Gesellschaft, Abteilung Anorganische Chemie, Faradayweg 4-6, 14195 Berlin, Germany

^f BasCat UniCat BASF JointLab, Technische Universität Berlin, Sekretariat EW K 01, Hardenbergstraße 36, 10623 Berlin, Germany

ARTICLE INFO

Article history: Received 11 January 2016 Received in revised form 30 May 2016 Accepted 30 June 2016 Available online 1 July 2016

Keywords: Oxidative methane coupling OCM Mn_xO_y-Na₂WO₄/SiO₂ Silica support material variation Mesoporous silica SBA-15

ABSTRACT

The oxidative coupling of methane (OCM) is one of the best methods for the direct conversion of methane. Among the known OCM catalysts, $Mn_xO_y-Na_2WO_4/SiO_2$ is a promising candidate for an industrial application, showing a high methane conversion and C_2 selectivity, with a good stability during long-term catalytic activity tests. In the present study, some results have been already published and discussed briefly in our previous short communication. However, we herein investigated comprehensively the influence of various silica support materials on the performance of the $Mn_xO_y-Na_2WO_4/SiO_2$ system in the OCM by means of *ex situ* and *in situ* XRD, BET, SEM and TEM characterization methods and showed new results to reveal possible support effects on the catalyst. The catalytic performance of most $Mn_xO_y-Na_2WO_4/SiO_2$ catalysts supported by different silica support materials did not differ substantially. However, the performance of the SBA-15 supported catalyst was outstanding and the methane conversion was nearly twofold higher in comparison to the other silica supported catalysts at similar C_2 selectivity as shown before in the communication. The reason of this substantial increase in performance could be the ordered mesoporous structure of the SBA-15 support material, homogeneous dispersion of active components and high number of active sites responsible for the OCM.

© 2016 Elsevier B.V. All rights reserved.

1. Introduction

According to the statistical review on the worldwide energy resources, the proven reserves contain 187.1 trillion cubic meters natural gas by the end of 2014 [1]. Natural gas is used for home and industrial heating and the generation of electrical power, but it is still an underutilized resource for chemicals and liquid fuels. Since the reserves are far away from industrial areas and the high costs of building pipelines for transportation, on-site conversion of methane, the main constituent, to more useful chemicals (e.g. ethylene, methanol) could be of great importance for using it more effectively in industry [2–8].

Generally, there are two different ways for CH_4 utilization: the indirect and the direct way. All indirect methods for CH_4 conversion require a highly endothermic and expensive synthesis gas step. The disadvantages of indirect methods could be avoided by direct conversion of CH_4 into value added compounds. One of the most important direct reactions is the oxidative coupling of







Abbreviations: BET, Brunauer Emmett Teller; C₂, ethane + ethylene; EDX, energydispersive X-ray spectroscopy; OCM, oxidative coupling of methane; S, selectivity; SEM, scanning electron microscopy; TEM, transmission electron microscopy; X, conversion; XRD, X-ray diffraction; XRF, X-ray fluorescence.

^{*} Corresponding author. Present address: PCK Raffinerie GmbH, Passower Chaussee 111, 16303 Schwedt/Oder, Germany.

^{**} Corresponding author. Present address: ABC Consultancy, Am Markt 2, 17291 Gramzow.

E-mail addresses: yildizm@gtu.edu.tr

⁽M. Yildiz), yilmazaksu@akdeniz.edu.tr (Y. Aksu), ulla.simon@ceramics.tu-berlin.de (U. Simon), torsten.otremba@integratedlabsolutions.com

⁽T. Otremba), kamal@inst.ac.in (K. Kailasam), caren.goebel@tu-berlin.de (C. Göbel), girgsdie@fhi-berlin.mpg.de (F. Girgsdies), oliver.goerke@ceramics.tu-berlin.de (O. Görke), frank.rosowski@basf.com (F. Rosowski), arne.thomas@tu-berlin.de

⁽A. Thomas), schomaecker@tu-berlin.de (R. Schomäcker), arndt@electric-mail.org (S. Arndt).

¹ Present address: Akdeniz University, Faculty of Engineering, Department of Material Science and Engineering, Dumlupinar Bulvari, 07058 Antalya, Turkey.

 $^{^{2}}$ Present address: ILS Integrated Lab Solutions GmbH, Max-Planck-Strasse 3, 12489 Berlin, Germany.

³ Present address: Institute of Nano Science and Technology, Habitat Centre, Phase-10, Sector-64, 160062 Mohali, Punjab, India.



Fig. 1. A general comparison of some OCM catalysts published in literature (approximately 100 results were selected randomly from [10]).

methane (OCM) to ethane and ethylene. The targeted reaction and the desired product are shown in Eq. (1):

$$aCH_4 + bO_2 \rightarrow cC_2H_6 + dC_2H_4 + eH_2O \tag{1}$$

However, up to date, this reaction has not reached the stage of commercial application, even though a large number of catalysts [9-11] have been tested since the first attempts by Keller et al. and Hinsen et al. [12,13]. Methane is the most stable hydrocarbon, having the strongest C–H bond; therefore, the activation of this bond is most difficult [14]. Thus, the oxidative coupling of methane occurs at high temperatures, usually above 700 °C. At these high temperatures, many catalysts suffer from severe stability and selectivity problems, e.g. Li/MgO as shown by Arndt et al. [15,16].

The most vital challenge for the OCM is the stability of the catalyst. Among the known OCM catalysts, $Mn_xO_y-Na_2WO_4/SiO_2$ is a promising one [17,18] in the literature for the commercialization of an industrial process [19–28]. Moreover, its catalytic performance (CH₄ conversions of 20–30% at C₂ selectivities of approximately 70–80%) is superior to the most OCM catalysts.

Besides that it is a very difficult issue to compare own results with reported results in literature due to the very different conditions and the very temperature-sensitive features of the OCM reaction. Therefore, as seen in Fig. 1 some selected results from literature are broadly scattered, prohibiting any conclusion.

Although the incipient wetness impregnation has been the most applied method for the catalyst preparation, different preparation procedures for the Mn_xO_y - Na_2WO_4/SiO_2 like solution combustion, flame spray pyrolysis and sol-gel routes have been used in recent years [29–32]. Besides that, Hiyoshi and Ikeda showed an improving effect of alkali chloride addition into Mn_xO_y - Na_2WO_4/SiO_2 . However, the most important challenge was the deactivation due to the evaporation of alkali metal chlorides from the catalyst [33].

Liu et al. carried out experiments with SiC as a support material for this trimetallic system and the $Mn_xO_y-Na_2WO_4/SiC$ showed similar performance compared to the silica supported catalyst [34]. Yu et al. applied La₂O₃, CeO₂, Pr₆O₁₁, Nd₂O₃, Sm₂O₃, Dy₂O₃, Yb₂O₃ and SiO₂ compounds as support material for only Na₂WO₄ as active component. However, some of the used support materials like Sm₂O₃ and Nb₂O₃ are known as active catalysts themselves for the OCM [35]. Wang et al. and Pak et al. investigated Mn_xO_y-Na₂WO₄/SiO₂ and Mn-Na₂WO₄/MgO systems to figure out the active sites and the elementary reactions. Na-O-Mn species as active site, sodium as suppressing component for the CH₄ total oxidation, tungstate ions as stability providing component and surface oxygens as hydrogen abstracting species from CH₄ were concluded [36,37]. Recently, Elkins and Hagelin-Weaver have compared Mn_xO_y-Na₂WO₄/SiO₂, Mn-Na₂WO₄/MgO, Mn_xO_y/SiO_2 and Na_2WO_4/SiO_2 and indicated that except $Mn_xO_v\text{--}$ Na₂WO₄/SiO₂, other compared catalyst showed lower methane conversion in the OCM. Furthermore, Na₂WO₄ and Mn₂O₃ phases were more stable in the Mn_xO_y-Na₂WO₄/SiO₂ in comparison to that of $Mn-Na_2WO_4/MgO$ and the reason of that was suggested the α -cristobalite phase of the SiO₂ support material [38]. Serres et al. increased the loading amount of active compounds with respect to the support material to improve the performance of the catalyst sustaining its high C₂ selectivity. After they had concluded to hinder a substantial decreasing of the surface area of the catalyst at high loadings, the SiO₂ support material of the Mn_xO_v-Na₂WO₄/SiO₂ catalyst was replaced with porous SiC and α -Al₂O₃ expecting a catalyst with high surface area at high loading of the active components. Increasing the amount of the active compounds improved evidently the performance of the catalyst but it is limited to a proper loading level. While a replacement of the SiO₂ support with porous SiC providing a high surface area upgraded the activity, an application of α -Al₂O₃ instead of SiO₂ resulted in poor performance due to a differently composed surface in the absence of silica. In spite of the improvements of catalyst activity in that study, even the performance of the optimized Mn-Na-W-/SiC do not reach to a La based catalyst, La/Sr/CaO [39].

In a previous study [40], we investigated a wide-range variety of support materials for the Mn_xO_y-Na₂WO₄/SiO₂ catalyst, in order to test alternative support materials to SiO2, which could suppress the pathway of the total oxidation of methane and found that SiO₂, TiO₂-rutile and SiC were the most suitable support materials. Furthermore, a Mn_xO_y-Na₂WO₄ catalyst without support material showed remarkable activity, raising questions on the role of the support material. Recently, we showed the catalytic activity results of the differently performing Mn_xO_y-Na₂WO₄/SiO₂ catalysts (Cat-H, Cat-M and Cat-L) prepared from three various silica materials, superiority of the SBA-15 supported Mn_xO_v-Na₂WO₄ and discussed concisely some results on BET surface area, XRD phase analysis and SEM-EDX images [41]. Herein, we studied more intensively the effect of different SiO₂ materials as support for the Mn_xO_y-Na₂WO₄/SiO₂ catalyst and the structural impact on the catalytic performance. Hence, we included also the previously published results of our short communication in this paper for the sake of completeness of the scientific discussion.

2. Experimental part

2.1. Support material preparation

Each silica type material has been given a code, since there were many different types of silica support materials. All of the used silica support materials, their origins, specific surface areas and the codes are shown in Table 1. The preparation method of ordered mesoporous silica material produced in the laboratory of the Functional Materials Department of the Technische Universität Berlin is explained in the supporting information.

2.2. Catalyst preparation

Eleven different silica supported $Mn_xO_y-Na_2WO_4$ catalysts were prepared by a standard two-step wet impregnation procedure and a mixed milling method as explained in the supporting information. The amounts of the active components were 5 wt% Na_2WO_4 and 2 wt% Mn_xO_y . Manganese was present in the form of manganese oxides or Mn-containing mixed oxides, however, the loading was calculated for pure Mn. For a structural analysis after the reaction, it is necessary to retrieve the catalysts. With the applied quartz sand this is not possible, because its particle size distribution is too large and overlaps with the particle size of Download English Version:

https://daneshyari.com/en/article/38687

Download Persian Version:

https://daneshyari.com/article/38687

Daneshyari.com