

The Tenth International Conference on Waste Management and Technology (ICWMT)

Preparation of carboxymethyl cellulose from corncob

Fang Jia^{1,2, *}, Hong-jie Liu^{1,2}, Guo-gang Zhang^{1,2}

¹ Hebei University of Science & Technology, Shijiazhuang 050018, PR China

² Hebei Engineering Research Center of Pharmaceutical and Chemical Engineering, Shijiazhuang 050018, PR China

Abstract

In this paper, to find out the best technological conditions of extracting microcrystalline cellulose from corncob by using high pressure cooking method. The optimum concentration of NaOH of the extraction of microcrystalline cellulose is 50% with the method of high pressure cooking. Preparation of carboxymethyl cellulose (CMC) from microcrystalline cellulose was carried out by an etherification process, using NaOH and monochloroacetic acid (MCA), with ethanol and water as the supporting medium. The results indicated that the best reaction condition was that the microcrystalline cellulose were alkalized at 30 °C for 50 min and etherificated at 65 °C for 3 h, 85% ethanol as solvent with the molar ratio of cellulose/NaOH/MCA was 1:1:1. NaOH is added in three batches with total amount the ratio is 6:2.5:1.5. Under the optimized reaction conditions, the substitution degree (DS) of CMC is 1.02 and the viscosity is 6 mPa·s, which possessed special characteristics of low viscosity.

© 2016 The Authors. Published by Elsevier B.V This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>).

Peer-review under responsibility of Tsinghua University/ Basel Convention Regional Centre for Asia and the Pacific

Keywords: Corn cop; Microcrystalline cellulose; Carboxymethyl cellulose; High pressure cooking

1. Introduction

CMC is manmade modified cellulose, a linear, long-chain, water-soluble, anionic polysaccharide which is prepared by the reaction of MCA with alkali cellulose¹. CMC has got ample scientific attention, especially due to its polyelectrolyte character and it is the most widely used cellulose ether today with applications in the detergent, food exploration, paper, textile, pharmaceutical and paint industries². The increasing environmental concerns have forced the researchers to obtain useful industrial materials from plant biomass. Recently the synthesis of CMC from different cellulosic sources have reported such as raw cellulose³, paper sludge⁴, wood residue⁵, cotton linters^{6,7}, fibers⁸ etc.

* Corresponding author. Tel.: +86-311-81668382.

E-mail address: 1174714552@qq.com

China has a rich crop straw resources, (annual output is as high as 700 million tons⁹) which account for a considerable part of maize corncob that contains a large number of natural polymer materials such as cellulose, lignin and hemicellulose. Recently cultivation of corncob has tremendously increased in China and huge amounts of corncob are either thrown away as waste or burnt. However, these are applications with low added value, causing disposal as well as environment pollution problems¹⁰. If corncob can translate to low viscosity carboxymethyl cellulose¹¹ it could be effective use of biological resources, reduce environmental pollution and produce a great economic benefits and ecological benefits.

In this paper, microcrystalline cellulose was extracted with the method of high pressure cooking. CMC was prepared from microcrystalline cellulose carried out by an etherification process, using NaOH and MCA, with ethanol and water as the supporting medium.

2. 2. Materials and methods

2.1. Materials

Corn cop was collected from Hebei Yingtian Biology Science & Technology co; Ltd. Chemicals used during the study were NaOH (Yongda, Tianjin), MCA (Bodi, Tianjin), ethyl alcohol (Yongda, Tianjin), potassium dichromate (Bodi, Tianjin), ferrous ammonium sulfate (Damao, Tianjin), 1,10-Phenanthroline monohydrate (Yongda, Tianjin),ect.

2.2. Methods

- Extraction of cellulose

The corn cob samples were washed, dried and cut manually into small pieces about 1cm, then put it in the steam pressure pot with NaOH solution at 170 °C and 0.7 MP for 90 min. The cellulose residue was separated by filtration, washed thoroughly with water to neutral, dried and tested the cellulose content. H₂O₂ was added to bleach the crude cellulose, and then treated with HCl was to get microcrystalline cellulose.

- Synthesis of carboxymethyl cellulose

Microcrystalline cellulose was added to ethanol aqueous solution with magnetic stirring, 50 min later then, NaOH was added. The alkalization reaction was conducted at 30 °C. After the alkalization reaction, MCA was added dropwise at 65 °C and stirred for 3 h. The solutions was then neutralized by HCl and filtered. The residue dried until reaching a constant weight.

- Determination of carboxymethyl cellulose

The substitution degree of CMC was determined by the method of complexometric titration¹² and the viscosity of the mass fraction of 1% CMC was measured by using the NDJ-5S type rotary viscosity meter.

3. Results and discussion

3.1. Effect of NaOH dosage on the extraction of cellulose

As is shown in Fig. 1, the effect of NaOH concentration was tested in different concentration of the NaOH solution. It was observed that the cellulose content of solid increased with NaOH concentration and attained a maximum content of 79.08% at an alkali dosage of 50% (by dry corncob meter). At particular alkali strength, the cellulose content reached maximum after which it started declining. This observation can be explained that cellulose molecules were hydrolyzed with the increase of dosage of alkali.

Download English Version:

<https://daneshyari.com/en/article/4401525>

Download Persian Version:

<https://daneshyari.com/article/4401525>

[Daneshyari.com](https://daneshyari.com)