



Effects of hydrogen and propylene presence on decomposition of hydrogen peroxide over palladium catalysts



Tao Chen^a, Emila Kertalli^b, T. Alexander Nijhuis^{b,c,*}, Simon G. Podkolzin^{a,*}

^aDepartment of Chemical Engineering and Materials Science, Stevens Institute of Technology, Castle Point on Hudson, Hoboken, NJ 07030, United States

^bLaboratory of Chemical Reactor Engineering, Department of Chemical Engineering and Chemistry, Eindhoven University of Technology, PO Box 513, 5600 MB Eindhoven, The Netherlands

^cSABIC, STC Geleen, PO Box 5151, 6130 PD Sittard, The Netherlands

ARTICLE INFO

Article history:

Received 10 April 2016

Revised 10 June 2016

Accepted 19 June 2016

Keywords:

H₂O₂
Reaction mechanism
Adsorption
DFT
Oxidized Pd
C₃H₆
Propylidyne

ABSTRACT

Reaction rates for H₂O₂ decomposition in a methanol solution were measured over Pd/SiO₂ catalysts in the presence of gas-phase N₂, H₂ and propylene. The H₂O₂ decomposition rates were higher in the presence of H₂ and lower in the presence of propylene compared to those under N₂, which acted as an inert gas. For interpretation of the experimental results, H₂O₂ decomposition reactions were evaluated with density functional theory calculations on four Pd(111) surfaces: (1) clean, (2) with pre-adsorbed hydrogen, (3) with molecularly pre-adsorbed propylene, and (4) with dissociatively pre-adsorbed propylene. The computational results show that the mechanism of H₂O₂ decomposition can proceed through O–O and O–H bond splitting reactions. The O–O bond splitting reactions are energetically preferable because they are exothermic and have lower activation energies. However, in the absence of H₂, the endothermic O–H bond splitting reactions with higher activation energies are required for the formation of molecular decomposition products: O₂ and H₂O. In contrast, in the presence of H₂, the O–H bond splitting reactions are no longer required, and the H₂O₂ decomposition can proceed only through the facile O–O bond splitting reaction in H₂O₂. The formed surface OH species can readily react with H species from dissociative H₂ adsorption, forming H₂O as the only product. This change in the reaction mechanism from the O–H bond splitting to the O–O bond splitting explains the experimentally observed higher H₂O₂ decomposition rates in the presence of H₂. The lower H₂O₂ decomposition rates in the presence of propylene are due to blocking of Pd surface sites by hydrocarbon species formed on propylene adsorption. Although propylene does not directly participate in H₂O₂ decomposition, it adsorbs on Pd more strongly than H₂O₂ and, therefore, forms surface spectator species that reduce the number of Pd active sites.

© 2016 Elsevier Inc. All rights reserved.

1. Introduction

Hydrogen peroxide, H₂O₂, is an important chemical that is widely used as an environmentally-friendly oxidizing agent in numerous household and industrial applications. For example, it is used in the production of disinfectants and laundry detergents as well as for wastewater treatment and for bleaching in the production of paper and textiles. Although the use of H₂O₂ is environmentally-friendly, its current production is based on a multistep anthraquinone process with consecutive hydrogenation and

oxidation steps. Since this process requires at least two reactors, large recycle streams and multiple separation units, it is usually economical to operate only large-scale centralized plants. In addition, the concentration of H₂O₂ needs to be increased by distillation prior to its transportation from a production plant in order to reduce the transported volume and then diluted back to smaller concentrations prior to its local use. It is, therefore, desirable to develop an efficient simplified process for small-scale (less than 50,000 tons/year) local on-demand production of H₂O₂ directly from H₂ and O₂ [1–3].

One of the main challenges in the development of an economical process for the direct H₂O₂ synthesis is minimizing the side reactions that lead to wasteful water formation. The challenge is that Pd-based catalysts that are efficient in the direct H₂O₂ synthesis are also effective in catalyzing water formation from two side reactions: (1) directly from H₂ and O₂ and (2) from H₂O₂ decomposition

* Corresponding authors at: SABIC, STC Geleen, PO Box 5151, 6130 PD Sittard, The Netherlands (T.A. Nijhuis). Department of Chemical Engineering and Materials Science, Stevens Institute of Technology, Castle Point on Hudson, Hoboken, New Jersey 07030, United States (S.G. Podkolzin).

E-mail addresses: Alexander.Nijhuis@SABIC.com (T.A. Nijhuis), Simon.Podkolzin@Stevens.edu (S.G. Podkolzin).

in the presence of H₂ [1,4]. The overall result from both reactions is wasteful H₂ burning to water. In order to deconvolute the reaction mechanism of water formation over Pd catalysts, it is useful to analyze separately the H₂O₂ decomposition in the presence of H₂. This reaction is sometimes referred to as H₂O₂ reduction.

Previous studies of H₂O₂ decomposition compared reaction rates in the presence and absence of H₂ over 2 wt.% Pd/SiO₂ in a flow microreactor [5,6], 5 wt.% Pd/Al₂O₃ in a batch reactor [7,8] and 3 wt.% Pd supported on an activated carbon cloth in a batch reactor [9]. These studies showed that the presence of H₂ significantly increased the decomposition rates. This effect was observed with different solvents and stabilizing agents under various experimental conditions. The higher rates in the presence of H₂ were tentatively assigned to an increase in the fraction of metallic Pd atoms. This explanation was proposed based on the observed slow deactivation of a 5 wt.% Pd/C catalyst in consecutive H₂O₂ decomposition reaction runs in a batch reactor at 298 K [10]. The deactivation was attributed to gradual oxidation of the Pd surface by O₂ produced in H₂O₂ decomposition. The argument was that the presence of H₂ makes the Pd surface more metallic and, therefore, makes the catalyst more active. This explanation, however, is inconsistent with the results of H₂O₂ decomposition in the presence of flowing O₂ reported by the same group [7]. The H₂O₂ decomposition rates practically did not change over a 5 wt.% Pd/Al₂O₃ catalyst in a batch reactor at 300 K when the reaction was first conducted under flowing N₂ and then repeated under flowing O₂ [7]. Therefore, the presence of O₂ at the typical reaction conditions was not significant.

Furthermore, the reaction kinetics of H₂O₂ decomposition were reported to change over 2 wt.% Pd/SiO₂ at 303–323 K in the presence of H₂ [5,6]. The apparent reaction orders in H₂O₂ at different temperatures were only positive in the absence of H₂ [5]. In contrast, the apparent reaction orders in H₂O₂ changed from being positive, to zero and then to negative with increasing H₂O₂ concentrations in the presence of H₂ under the same reaction conditions [6]. These kinetic differences indicate that the reaction mechanism changes in the presence of H₂.

In this work, reaction rates of H₂O₂ decomposition were systematically compared over oxidized and reduced Pd/SiO₂ catalysts in the absence and presence of H₂. Effects of H₂ presence on elementary reaction steps in H₂O₂ decomposition on Pd were analyzed at the molecular level with density functional theory (DFT) calculations. Our results identify how the reaction mechanism changes in the presence of H₂, explaining the experimental observations.

Due to its environmental friendliness, H₂O₂ is a desirable oxidizing agent for selective oxidation of hydrocarbons in the chemical industry. For example, it is advantageous to use H₂O₂ for selective oxidation of propylene to propylene oxide. Propylene oxide is used in the production of polyurethane plastics and multiple other large-volume commodity chemicals. The current production of propylene oxide is mostly based on either the multistep chlorohydrin process with salty waste streams and chlorinated by-products or another multistep process with an aromatic hydrocarbon by-product [11]. In order to improve the efficiency of propylene oxide production, The Dow Chemical Company and BASF have recently commercialized a new Hydrogen Peroxide – Propylene Oxide (HPPO) process, in which propylene oxide is produced by reacting H₂O₂ with propylene over a TS-1 catalyst in liquid phase [11–13]. In this process, unreacted H₂O₂ in the product stream needs to be decomposed in the presence of hydrocarbons. It is, therefore, useful to determine how the presence of propylene affects H₂O₂ decomposition over metals, such as Pd, that are active in catalyzing H₂O₂ decomposition. For example, effects of the reaction temperature and the solution pH on H₂O₂ decomposition in an HPPO product stream were experimentally evaluated over

supported Pt and Pd catalysts with an objective of complete H₂O₂ decomposition [12].

A reverse objective, preventing wasteful H₂O₂ decomposition, is critically important in the development of a single-step process where in situ formation of H₂O₂ or surface OOH species can be combined with their immediate use for selective propylene oxidation in the same reaction mixture. Such a process with H₂, O₂ and propylene as the feed and propylene oxide and H₂O as products is extensively studied as a gas-phase reaction over Au/TiO₂ and Au/TS-1 catalysts [11,14]. For example, our recent study showed that an Au/Ti-SiO₂ catalyst can be used with a membrane, with propylene and O₂ being forced through the catalytic membrane and H₂ reaching the catalyst by counter-diffusion [15]. Alternatively, a membrane reactor can produce H₂O₂ from H₂ and O₂ over Pd/SiO₂ in the first catalytic layer and then immediately utilize the produced H₂O₂ for selective hydrocarbon oxidation over TS-1 in the second catalytic layer [16]. Since such single-step processes in effect combine the direct H₂O₂ synthesis with propylene epoxidation, here it is also useful to determine effects of propylene presence on H₂O₂ decomposition over catalytic metals, including Pd, that are active in catalyzing H₂O₂ formation.

In this work, in addition to the evaluation of H₂ presence effects, reaction rates of H₂O₂ decomposition were systematically compared over oxidized and reduced Pd/SiO₂ catalysts in the absence and presence of propylene. The experimental results were analyzed with DFT calculations by comparing elementary reaction steps in H₂O₂ decomposition on a clean Pd surface and on Pd surfaces with pre-adsorbed hydrogen and propylene.

2. Experimental and computational methods

2.1. Catalyst preparation

2 wt.% Pd/SiO₂ catalysts were prepared using incipient wetness impregnation with palladium acetate (99.9%, Sigma-Aldrich) and Davisil 643 silica (pore size 15 nm, 200–425 mesh, Sigma-Aldrich). Prior to the Pd deposition, the SiO₂ support was dried at 373 K overnight. After the Pd deposition, the samples were first dried in vacuum at 393 K for 12 h and then calcined in air at 573 K for 4 h. After the calcination, the samples were split into two sets. The first set was tested without any additional pretreatment (oxidized Pd/SiO₂). The second set was tested after a reduction pretreatment in 10 mol% H₂/He (99.999%, Linde grade 5.0) at a flow rate of ~20 sccm at 473 K for 2 h (reduced Pd/SiO₂).

The sizes of Pd nanoparticles in the oxidized and reduced samples were analyzed using multiple images obtained with a FEI Tecnai G2 Sphera transmission electron microscope (TEM) at an acceleration voltage of 200 kV. Representative TEM images are shown in Fig. 1. The histograms of particle size distributions for the oxidized and reduced Pd nanoparticles, which are also shown in Fig. 1, demonstrate that, as expected for the conversion of an oxide to the metal, the size of nanoparticles decreased from 2.8 ± 0.6 nm for the oxidized Pd (Fig. 1b) to 2.2 ± 0.6 nm for the reduced Pd (Fig. 1a). Importantly, the particle size distributions indicate that the H₂ treatment did not cause any significant size changes for the Pd nanoparticles, only their reduction.

2.2. Catalyst testing

Rates of H₂O₂ decomposition in a methanol solution were measured using a 100 ml glass autoclave batch reactor immersed in a cooling bath for temperature control. The autoclave had an internal thermocouple, pressure sensor and gas dispersion impeller. The temperature was kept constant at 313 K. The initial total pressure in the reactor was 6 bar. The reactor pressure varied slightly during

دانلود مقاله



<http://daneshyari.com/article/60488>



- ✓ امکان دانلود نسخه تمام متن مقالات انگلیسی
- ✓ امکان دانلود نسخه ترجمه شده مقالات
- ✓ پذیرش سفارش ترجمه تخصصی
- ✓ امکان جستجو در آرشیو جامعی از صدها موضوع و هزاران مقاله
- ✓ امکان پرداخت اینترنتی با کلیه کارت های عضو شتاب
- ✓ دانلود فوری مقاله پس از پرداخت آنلاین
- ✓ پشتیبانی کامل خرید با بهره مندی از سیستم هوشمند رهگیری سفارشات