



## Fabrication and characterization of a composite dosimeter based on natural alexandrite

Neilo Marcos Trindade<sup>a,b,\*</sup>, Anna Luiza Metidieri Cruz Maltez<sup>c</sup>, Augusto de Castro Nascimento<sup>a</sup>, Ronaldo Santos da Silva<sup>d</sup>, Luiz Gustavo Jacobsohn<sup>b</sup>, Elisabeth Mateus Yoshimura<sup>e</sup>

<sup>a</sup> Federal Institute of Education, Science and Technology of São Paulo, Department of Physics, São Paulo, SP, Brazil

<sup>b</sup> Clemson University, Department of Materials Science and Engineering, Clemson, SC, USA

<sup>c</sup> Federal University of Technology – Parana, Curitiba, PR, Brazil

<sup>d</sup> Federal University of Sergipe, São Cristóvão, SE, Brazil

<sup>e</sup> University of São Paulo, Institute of Physics, São Paulo, SP, Brazil

### ARTICLE INFO

#### Keywords:

Alexandrite  
OSL  
Natural dosimeter  
Mechanical properties

### ABSTRACT

This work aims at demonstrating the fabrication of a new composite material based on the micron-sized powder of the alexandrite mineral ( $\text{BeAl}_2\text{O}_4:\text{Cr}^{3+}$ ) dispersed in a fluorinated polymer for OSL dosimetric applications. Composites with 50 wt% alexandrite powders were obtained and characterized in their chemical composition, mechanical, and luminescent properties. Energy dispersive X-ray spectroscopy mapping measurements of the pellets revealed a homogeneous distribution of alexandrite particles throughout the organic matrix. PL measurements showed the signal related to  $\text{Cr}^{3+}$  ions in alexandrite remained active besides all fabrication steps, and tensile tests showed the pellets to have good ductility and tensile strength. The OSL results showed the integrated intensity signal varied linearly with the beta irradiation dose and that the pellets were stable at room temperature over time of 28 days. Nevertheless, improvements in the fabrication process are necessary toward obtaining the same OSL intensity from different pellets.

### 1. Introduction

Natural and synthetic dosimetric materials are used for the determination of the irradiation dose received in the environment as well as in medical and technological activities. Synthetic dosimeters have the advantage of controlled synthesis and precise chemical composition thus presenting high levels of reproducibility. On the other hand, natural dosimeters find application, e.g., in retrospective dosimetry and may be a lower-cost alternative to synthetic ones. Further, they may be more readily available in large quantities [1].

Optically stimulated luminescence (OSL) has long established itself as a reliable technique in dosimetry. The OSL signal arises from the recombination of charges optically released from specific traps inside the material that was previously irradiated with ionizing radiation. The charge carrier population in the traps is the result of the irradiation, and thus the OSL intensity is related to the absorbed radiation dose [2–4]. The OSL signal obtained under stimulation with constant light power is observed to progressively decrease as the charges are released from the traps (decay curve) [3]. Due to the optical nature of the process, the OSL technique presents several advantages such as simplicity of

measurement, possibility of reevaluation of irradiation doses, and flexibility for obtaining cumulated and individual dose measurements with the same detector [4,5]. Since the OSL signal can be monitored at room temperature without heating the material, the readout process is less destructive and usually does not affect the defects involved in the luminescence mechanism. On the other hand, the main disadvantage of this technique lies in the low number of materials that present intrinsic characteristics suitable for application in radiation dosimetry [4,6]. Therefore, due to the advantages of the OSL technique and the low number of commercially available OSL detectors, there is need to discover and develop new OSL dosimetric materials [7–10]. In terms of natural dosimetric materials, this effort has been mostly directed to accident dosimetry and luminescence dating [3] using quartz and feldspar.

The material under consideration in this work is the mineral alexandrite ( $\text{BeAl}_2\text{O}_4:\text{Cr}^{3+}$ ), with the largest deposits in the world found in the Brazilian States of Bahia, Espírito Santo, and Minas Gerais [11]. Alexandrite, a variety of the mineral Chrysoberyl, has a fraction of its Al ions substituted by Cr ions and thus its unique optical properties. Chrysoberyl has a closed hexagonal (hcp) structure and the unit cell

\* Corresponding author. Federal Institute of Education, Science and Technology of São Paulo, Department of Physics, São Paulo, SP, Brazil.  
E-mail address: [ntrindade@ifsp.edu.br](mailto:ntrindade@ifsp.edu.br) (N.M. Trindade).

contains four formula units ( $Z = 4$ ). Eight  $\text{Al}^{3+}$  ions occupy distorted octahedral sites and four  $\text{Be}^{2+}$  ions occupy distorted tetrahedral sites. The distortion in the hcp structure gives rise to the appearance of two distinct crystallographic sites:  $\text{Al}_1$ , located at inversion sites, and  $\text{Al}_2$  located at a reflection plane [12,13]. The larger  $\text{Cr}^{3+}$  ions are preferably incorporated into the larger  $\text{Al}_2$  site that has an average Al–O bond length of 1.938 Å, instead of the  $\text{Al}_1$  site with an average Al–O bond length of 1.890 Å [14,15]. According to the literature,  $\text{Cr}^{3+}$  ions located in the  $\text{Al}_2$  sites are responsible for the optical properties of alexandrite, including laser emission [14,16–18].

The motivation for this work lies on the fact that chrysoberyls contain 19.8 wt% BeO and 80.2 wt%  $\text{Al}_2\text{O}_3$  [19] with both of these simple oxides being commercially used as OSL dosimeters.  $\text{Al}_2\text{O}_3\text{:Cr}$ , first developed as a highly sensitive TL material [20], became widely used as an OSL sensor because of its thermal stability close to room temperature, reproducibility, sensitivity to low gamma-ray irradiation doses down to 1  $\mu\text{Gy}$ , low fading rate (< 5% per year), and the capability for imaging radiation fields [21]. BeO was suggested as an OSL dosimeter in the 1970s [22], but its properties were only investigated in detail in the late 1990s [23]. This dosimeter has been used in photon and beta dosimetry [24] combined with being a low-cost material [25]. BeO presents high sensitivity to ionization radiation, linear dose response in a broad range from 1  $\mu\text{Gy}$  to 5 Gy [21], and negligible fading within long storage times (< 1% in 6 months) [25]. The low effective atomic number ( $Z_{\text{eff}} = 7.14$  [26]; 7.21 [21]) of BeO is near tissue-equivalent and allows for medical applications [26].

The investigation of the potential of alexandrite as a dosimetric material was executed by means of thermoluminescence measurements and first reported in Ref. [27]. This paper focuses on the development and the characterization of a dosimetric composite based on the powdered mineral dispersed in a binder, a fluorinated polymer, toward achieving higher control and reproducibility of the dosimetric response. The dosimetric properties of this new dosimetric composite are reported here for the first time.

## 2. Materials and methods

### 2.1. Preparation of powdered alexandrite

The natural sample used in this work was originated from the State of Bahia, Brazil. The procedure for obtaining alexandrite powder was as follows:

1. Crystals of green alexandrite were visually separated from the natural piece of rock.
2. These fragments were manually crushed and powdered using a Chiarotti porcelain mortar and pestle.
3. The powder was sieved with a pair of Granutest sieves, selecting grain sizes smaller than 75  $\mu\text{m}$ .
4. The sieved alexandrite powder was thermally treated at 400 °C for 1 h to clean any signal previously accumulated in the material due to natural irradiation.

### 2.2. Preparation of alexandrite composite pellets

The composite pellets were obtained using a proprietary technique for OSL sheet production developed at the Federal University of Technology in Curitiba, Paraná, Brazil. The fabrication process consisted in mixing the alexandrite powder with an organic matrix based on a fluorinated polymer on a 1:1 mass ratio. This matrix was chosen to embed the alexandrite powder because it does not emit any OSL signal, and because it gives rise to a good sheet homogeneity. Finally, 1.4 mm thick, 5.5 mm diameter, and 1.87 g/cm<sup>3</sup> average density pellets were obtained from the original sheet using a handheld slot punch.

### 2.3. Characterization of alexandrite pellets

The surface morphology and microstructure of the samples were imaged by means of scanning electron microscopy (SEM) measurements in backscattered electron (BSE) mode, while the local chemical composition was determined by energy dispersive X-ray spectroscopy (EDS) measurements using a Hitachi S–3400 N scanning electron microscope.

Tensile strength test of the composite was executed using Instron 5500R1125 and 4582 tensile analyzers. The analysis was carried out at room temperature at a speed of 10 mm/min using a sample with a rectangular shape (6 mm length, 6.76 mm width, 1.45 mm thickness). From these measurements, the Young's modulus, maximum load, and elongation were determined using the Bluehill 2 Software.

Steady-state photoluminescence emission (PL) spectra were collected with a Horiba Jobin-Yvon Spex FluoroLog 2 spectrofluorometer equipped with a Hamamatsu R928 photomultiplier detector. The equipment has double monochromators for both excitation and detection, and a 450 W xenon lamp as the excitation source. The measurements were carried out at room temperature with a 2 nm excitation slit, 1 nm emission slit, 0.5 nm wavelength increment step, and 0.5 s integration time.

OSL measurements were carried out using a commercial automated TL/OSL reader produced by Risø National Laboratory (model DA-20). OSL luminescence was stimulated using blue light emitting diodes (470 nm, FWHM = 20 nm) delivering 80 mW/cm<sup>2</sup> at the sample position in CW mode. Each OSL measurement was carried out with 90% of the maximum LED power density. The OSL signal was detected with a bialkali photomultiplier tube (PMT) behind an UV transmitting broad-band glass filter (Hoya U-340, 7.5 mm thick) to block the stimulation light while transmitting part of the OSL signal from the samples. Irradiation was performed at room temperature using the built-in <sup>90</sup>Sr/<sup>90</sup>Y beta source of the TL/OSL reader (dose rate of 10 mGy/s) within a dose range from 100 to 500 mGy.

## 3. Results and discussion

Fig. 1 shows the as-received alexandrite mineral before any processing (a), the powder before sieving (b), the alexandrite: fluorinated polymer composite sheet (c), and the 5.5 mm diameter pellet (d). Fig. 2 shows a SEM image of the pellet surface (central image, top layer) while composition mapping of selected chemical elements (C, Mg, Al, Ca, Fe) are shown in the surrounding images. Visual analysis showed that each element presented a uniquely different distribution in the sample. Since Be cannot be detected by EDS, the distribution of alexandrite particles within the polymeric matrix was determined through the mapping of Al. These results indicated the alexandrite particles were reasonably well homogeneously distributed in the matrix. Fe is a common impurity of alexandrite and its distribution to regions rich in Al (*i.e.*, the alexandrite phase). Because of the low concentration, Cr was not detected in this experiment. In a previous work, we have shown that the natural mineral alexandrite contained other phases, including mica, allanite, and apatite [27]. These secondary phases were revealed through the presence and distribution of elements like Mg and Ca. Mg is commonly present in mica, and Ca is commonly found in apatite. As expected, the distribution of these elements did not match that of alexandrite (Al). C was originated from the polymeric matrix. Similar results were obtained from other pellets analyzed the same way. According to previous work on the same group of alexandrite samples, the Cr and Fe average concentration values are 0.7 wt% and 1.9 wt%, respectively [27]. As discussed before in the literature, Cr and Fe are responsible for the optical and luminescent properties [14,16,18, 27,28].

In order to evaluate some of the effects of handling of the composite, the mechanical response under tensile stress was investigated. A typical load/deformation curve is presented in Fig. 3. The results showed a significant plastic deformation and energy absorption (toughness) before the fracture, demonstrating the ductile nature of the composite

Download English Version:

<https://daneshyari.com/en/article/10128416>

Download Persian Version:

<https://daneshyari.com/article/10128416>

[Daneshyari.com](https://daneshyari.com)