



Production of pullulan by *Aureobasidium pullulans* from Asian palm kernel: A novel substrate

K.R. Sugumaran, E. Gowthami, B. Swathi, S. Elakkiya, S.N. Srivastava, R. Ravikumar, D. Gowdhaman, V. Ponnusami*

School of Chemical and Biotechnology, SASTRA University, Thanjavur – 613401, Tamilnadu, India

ARTICLE INFO

Article history:

Received 6 August 2012
Received in revised form
14 September 2012
Accepted 24 September 2012
Available online 2 October 2012

Keywords:

Pullulan
Aureobasidium pullulans
Asian palm kernel
Solid state fermentation

ABSTRACT

Production of a commercially important biodegradable polymer, pullulan, by *Aureobasidium pullulans* from four agricultural wastes namely wheat bran, rice bran, coconut kernel and palm kernel was evaluated in solid state fermentation. Under the experimental conditions, palm kernel resulted in highest concentration of pullulan (16 g/L) among the four solid substrates. Optimum initial pH and moisture content for pullulan production were found out to be 6.5 and 50% respectively. 18.43 g/L of pullulan was produced from Asian palm kernel with initial pH 6.5 after 7 days of fermentation and yeast like morphology was predominant under this condition. Among different nitrogen sources tried in this study, yeast extract was found to be the best. The pullulan produced from palm kernel was characterized by FTIR and ^1H NMR. The results were matching with that of commercial pullulan. Thus, Asian palm kernel appears to be an attractive low cost carbon source for the production of pullulan.

© 2012 Elsevier Ltd. All rights reserved.

1. Introduction

Pullulan is a linear, un-branched exo-polysaccharide (Carolan, Catley, & McDougal, 1983; Taguchi, Kikuchi, Sakano, & Kobayashi, 1973) which consists of uniform linkage pattern of maltotriose units which are attached by an α (1 $\rightarrow$ 4) glycosidic linkages and repeated maltotriose units which are attached to each other by an α (1 $\rightarrow$ 6) glycosidic linkages (Catley, Ramsay, & Servis, 1986; Sutherland, 1998). It is a water soluble biopolymer but it is insoluble in organic solvents, excluding dimethylformamide and dimethylsulfoxide (Leathers, 2002; Sugimoto, 1978). It is nontoxic, tasteless, odourless, white, and non-hygroscopic (Leathers, 2002; Sugimoto, 1978).

Aureobasidium pullulans called as black yeast have five different cell morphologies like swollen blastospores, yeast-like cells, mycelia, chlamydospores and young blastospores (Ronen, Guterman, & Shabtai, 2002). From an ecological point of view, *A. pullulans* is mainly found on leaves and various surfaces such as concrete, lime stone, wood, soil and forest barks (Bhadra, Rao, Singh, Sarkar, & Shivaji, 2008). *A. pullulans* is a polymorphic fungus, ranging from blastic conidia and swollen cells to pseudohyphae, hyphae, and chlamydospores, depending upon age of inoculum,

culture conditions and medium composition (Leathers, 2003) that produces pullulan (Gibbs & Seviour, 1992).

Recently pullulan has been widely used in pharmaceutical industry as a biomaterial (Alban, Schauerte, & Franz, 2002; Masci, Bontempo, & Crescenzi, 2002; Sivakumar & Rao, 2003). Pullulan can be also used as a non-caloric food ingredient, dietary food as a starch. It forms transparent film, impervious to oxygen transfer and used as a packing and coating materials in food and pharmaceutical industries (Deshpande, Rale, & Lynch, 1992). Pullulan is widely used in high performance liquid chromatography (HPLC) columns and in size exclusion chromatography as a molecular mass standard (Buliga & Brant, 1987).

In spite of its commercial importance and wide spread applications in the fields of food, pharmaceutical, lithography and other fields, its use in large scale is limited by the economic constraints. In the recent review on the pullulan, it is reported that the cost of pullulan is about three times higher than that of other polysaccharides (Ram, Gaganpreet, & Kennedy, 2008). Various approaches had been adopted to bring the cost pullulan production. This includes, engineering innovations, improved strains (Ram et al., 2008) and identification of cheaper and effective carbon and nitrogen sources (Wu, Jin, Tong, & Chen, 2009; Göksungur, Uzunoğlu, & Dağbaşı, 2011). It had been reported that cost of the media components accounts for 30% of total production cost (Miller & Churchill, 1986; Nishat Sharma, Prasad, & Choudhury, in press). Agro-industrial wastes (Israilides, Bocking, Smith, & Scanlon, 1994; Israilides et al., 1998),

* Corresponding author. Tel.: +91 4362 264101; fax: +91 4362 264120.

E-mail addresses: vponnu@chem.sastra.edu, ponnusamiv@yahoo.com (V. Ponnusami).

potato starch waste (Barnett, Smith, Scanlon, & Israilides, 1999), deproteinized whey (Roukas, 1999a), brewery wastes (Roukas, 1999b), jaggery (Vijayendra, Bansal, Prasad, & Nand, 2001), beet molasses (Lazaridou, Roukas, Biliaderis, & Vaikousi, 2002), sweet potato (Wu et al., 2009), coconut by-products (Thirumavalavan, Manikkandan, & Dhanasekar, 2009), hydrolyzed potato starch waste (Göksungur et al., 2011), and corn steep liquor (Nishat Sharma et al., in press) were the alternate carbon sources reported in pullulan literature.

In this study, four different agricultural wastes namely wheat bran, rice bran, coconut kernel and palm kernel were evaluated as possible low cost carbon sources for the production of microbial pullulan. Asian palm kernel emerged to be the best carbon source among the four. The effects of moisture content, nitrogen source, initial pH and fermentation time on pullulan production from Asian palm kernel were investigated in solid state fermentation. To the best of our knowledge, this is the first report on production of pullulan by *A. pullulans* in solid state fermentation using palm kernel as a sole carbon source.

2. Materials and methods

2.1. Microorganisms and culture conditions

A. pullulans MTCC 2670 was purchased from MTCC, Chandigarh, India. Stock cultures of the fungi were maintained on potato dextrose agar at 4 °C and sub cultured every 3 weeks. Potato dextrose agar composition was: potato (scrubbed and diced) – 200 g/L; dextrose – 20 g/L; agar – 15 g/L.

2.2. Inoculum preparation in culture medium

Basal medium contains the following: sucrose – 30 g/L; $(\text{NH}_4)_2\text{SO}_4$ – 2 g/L; yeast extract – 0.4 g/L; K_2HPO_4 – 5.0 g/L; $\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$ – 0.2 g/L and NaCl – 1.0 g/L and pH was adjusted to 7 before sterilization. The medium was sterilized for 15 min at 121 °C and cooled. Two loops of *A. pullulans* cells were transferred to 250 mL Erlenmeyer flasks containing 50 ml of sterilized culture medium which was incubated at 30 °C for 48 h in an orbital shaker at 200 rpm. These cultures were used as inoculum for pullulan production.

2.3. Solid state fermentation

Palm kernel was used as solid substrate and carbon source in solid state fermentation. Palm kernel was obtained from matured palmyra fruit (*Borassus flabellifer*). The outer most layers of the palmyra fruits were removed and the matured inner part (palm kernel) of the palmyra fruits had been cut into pieces. These pieces were sun-dried for 6–8 days to prevent microbial deterioration. Solid substrate was prepared by taking 20 g of palm kernel pieces in 250 mL Erlenmeyer flask and the volume of basal medium was varied according to the moisture content. The basal medium was added with solid substrate and initial pH was adjusted to 7.5 (before sterilization). Then mixture was sterilized for 15 min at 121 °C and sterilized medium was inoculated with 2% v/v of 48 h old culture (0.8 O.D at 650 nm) of *A. pullulans* grown on culture medium.

2.4. Determination of the effect of different factors on pullulan production

As mentioned earlier in the introduction section, four different agro-wastes namely wheat bran, rice bran, coconut kernel and palm kernel were examined for the production of microbial pullulan. After screening solid substrate, effects of these variables such as initial pH (3–11), fermentation time (1–8 days), initial moisture

content (10–90%) and screening of nitrogen sources such as ammonium sulfate, ammonium chloride, peptone, yeast extract and malt extract on pullulan production were studied.

2.5. Estimation of pullulan concentration

Samples were taken from fermentation medium and centrifuged at $10,000 \times g$ for 20 min for estimating pullulan concentration. The supernatant obtained from centrifugation was precipitated by adding two volumes of ethanol at 4 °C for 1 h. Then precipitate was treated with acetone and filtered by pre-weighed Whatman No.1 filter paper and dried at 90 °C for constant weight and dry weight of pullulan was expressed as g/L (Vijayendra et al., 2001).

2.6. Morphological observation and yeast biomass estimation

Cell morphology was observed using light microscopy (Carl Zeiss inc. Germany). Estimation of yeast biomass in dry weight was carried out according to the method described by Reeslev, Nielsen, Olsen, Jensen, and Jacobsen (1991). Sample was taken from solid state fermentation under aseptic condition and centrifuged at 12,000 rpm for 10 min centrifugation was carried out three times for efficient separation of cells and substrate from supernatant. It was ensured that cells were not present in the supernatant using light microscope (Carl Zeiss inc., Germany). The pellet so collected was added with 5 mL of 1% NaCl solution. Then sample was filtered through a nylon mesh of 41 μm square porosity for the separation of yeast cells from mycelium and solid substrate (Reeslev et al., 1991). Using light microscope, it was conformed that only yeast like cells were appeared in the filtrate and yeast like cells were dried at 90 °C to constant weight. Mycelia mat on the mesh and solid substrate were washed with water and dried at 90 °C to constant weight. Yeast biomass was expressed by percentage of total dry weight of solid substrate and cells (Mitchell, Krieger, & Berovi, 2006).

2.7. Characterization of pullulan

The purified sample was characterized using IR spectroscopy (Perkin-Elmer 1600 spectrophotometer) and ^1H NMR (Bruker 300 MHz Instrument, Germany) and results were compared with that of commercial pullulan (TCI chemicals, Tokyo). FTIR sampling was done with KBr pellet method (Hui-zhu et al., 2009; Thirumavalavan et al., 2009) and ^1H NMR sample was prepared by dissolving 10 mg of pullulan in 0.5 mL DMSO-d_6 solvent and TMS was used as an internal standard (Hui-zhu et al., 2009).

3. Result and discussion

3.1. Screening of solid substrate

Fig. 1 shows the screening of solid substrate on pullulan production with 50% moisture content. Maximum pullulan concentration obtained with these carbon sources were 5.5, 7.5, 9.5 and 16.0 g/L for rice bran, wheat bran, coconut kernel and palm kernel respectively. Therefore, palm kernel was selected as a solid substrate for pullulan production and used for further studies. Thirumavalavan et al. (2009) obtained pullulan concentration of 38.3 g/L and 58 g/L from coconut water and coconut milk respectively in submerged fermentation. Vijayendra et al. (2001) had reported 51 g/L pullulan yield from jaggery and derivative of sucrose. Ray and Moorthy (2007) produced pullulan from wheat bran, rice bran and cassava starch with and without basal medium and maximum production of pullulan 27.5 g/kg of substrate, was achieved using cassava starch residue as a solid substrate (Ray & Moorthy, 2007).

Download English Version:

<https://daneshyari.com/en/article/10601793>

Download Persian Version:

<https://daneshyari.com/article/10601793>

[Daneshyari.com](https://daneshyari.com)