

## A contribution to the explanation of the action principles of organic plasticizers

T. Sebök, J. Krejčí\*, A. Musil, J. Šimoník

*Faculty of Technology, Tomas Bata University, Nám.TGM 275, 72 03 Zlín, Czech Republic*

Received 24 June 2003; accepted 12 July 2004

### Abstract

Suspensions of laboratory cement modified with 0.25% to 1.5% of MSFC-type dispersant were prepared. The sorption of organic molecules, viscosity and integral value of heat liberation after 5, 10 and 20 min were determined. Regression analysis showed that the viscosity changes of suspension are influenced by about 86% by the changes of sorption and heat liberation.  
© 2004 Elsevier Ltd. All rights reserved.

**Keywords:** Calorimetry; Rheology; Adsorption; Admixture

### 1. Introduction

The effectiveness of plasticizers on the rheological parameters of concrete mixes is tested according to the standard specifications of industrial countries, up to 30 min. This time seems to be sufficient for the filling of moulds and compaction of mixes in practice. Therefore, our experiments were focused to this time period.

The rheological properties of cement suspensions and the influence of dispersants on them have been studied by a number of authors (for instance, [1–13]) for a long time. Therefore, many questions remain without explanation. The substantial results can be shortly assumed as follows.

The water/cement ratio, derived parameter-hydraulic radius, dose of dispersants in a mix and parameters of cement and additives influence the viscosity of suspensions predominantly. Changes of the potential  $\zeta$  of cement particles are influenced by the concentration and parameters of additives. But a commonly accepted relationship between the potential  $\zeta$  of cement particles and rheological parameters of modified suspensions has not been found.

The intensity of steric repulsive forces between the charged particles depends on the structure and other parameters of sorbed organic molecules and on their concentration on the surface of cement particles. But relationships between the potential  $\zeta$ , magnitude of those forces and viscosity of modified suspensions have not been published.

### 2. Experimental part

#### 2.1. Cement

The mineralogical composition of the clinker, determined by optical microscopy [14], was the following (%):  $C_3S=65.3$ ,  $C_2S=8.7$ ,  $C_3A=9.1$ ,  $C_4AF=16.8$  and porosity 3.71%.

Clinker +5% gypsum was ground in a laboratory ball mill. The specific surface of the cement was  $BET=1.8 \text{ m}^2/\text{g}$  and Blaine= $0.536 \text{ m}^2/\text{g}$ . Density was  $3.104 \text{ g/cm}^3$ .

#### 2.2. Additive

The results published [15] indicated that the molar weight of MSFC-type dispersants changes with the time

\* Corresponding author. Tel.: +42 57603 1524; fax: +42 57603 1563.  
E-mail address: [krejci@ft.utb.cz](mailto:krejci@ft.utb.cz) (J. Krejčí).

of storing. Therefore, the powder form of additive Melment F10X was used for the tests. Fresh solutions of additive were prepared 24 h before the preparation of suspensions. The dose of additive is expressed in percent of dry content from the mass of cement.

### 2.3. Determination of viscosity

A number of preliminary tests were carried out for the determination of optimal conditions for the tests. The following parameters seemed to be optimal for the best reproducibility of results: water+additive, cement ratio was 0.5. The cement and the solution of additive were homogenized by hand 10 s. Then, the suspension was homogenized using a propeller agitator (400 rotation/min) during 15 s. The suspension was homogenized by hand again before the determination of viscosity after 5 min. Rotary viscometer Rheotest RV (Prüfgerete Werk, Medingen), cone-plate system was used for the tests. The vertex angle of the cone was  $150^\circ$ ,  $D=48.3 \text{ s}^{-1}$ . The temperature of the compounds and environment during measurements was constant at  $20 \pm 0.5^\circ \text{C}$  (Table 1).

### 2.4. Calorimetry

The integral value of heat liberation was determined by a calorimeter in isothermal conditions  $t=+20^\circ \text{C}$ . The composition of suspensions was the same as for the determination of viscosity.

### 2.5. Sorption

It was found that the peak of 217 nm from the total UV spectra of additive (apparatus Cecil CE 3041) was optimal for sorption studies. It is distinctive and does not coincide with that of filtrate of cement. Solutions having different concentrations of MSFC additive (concentrates) were analyzed by the method of UV spectra analysis. A linear relationship between the concentration of solutions and the absorbencies was found.

Afterwards, 100 g of cement was mixed with 100 g of a solution additive. The suspension was filtered (glass porous filter pores 0.7–1.3  $\mu\text{m}$ , vacuum filtration) after a chosen

time, and the filtrate was subsequently analyzed. The sorbed amount of organic molecules  $S_r$  (mg/g) was calculated from formula:

$$S_r = \frac{(C_{rc} - C_{rf})V}{m} \quad (1)$$

where  $C_{rc}$  and  $C_{rf}$ —the concentration of the additive before (concentrate) and after sorption, respectively (mg/l);  $V$ —the volume of the MSFC solution used for sorption (l); and  $m$ —the mass of cement (g).

### 2.6. Regression analysis

The computer program Statgraphics 7 (Statistical Graphics, USA) was used. For the significance of  $R^2$  (coefficient of multiple determination), the following limits were used [16]:  $R^2 \leq 30\%$ —bad or any correlation;  $30\text{--}60\%$ —medium correlation; and  $>60\%$ —very good correlation between tested variables exists.

## 3. Evaluation of results

Results in Fig. 1 and Table 2 indicate that the sorption-active fractions of organic molecules are sorbed out up to 5 min. Changes of sorption between 5 and 20 min are minimal. It seems that differences are in the limits of the method's reproducibility. The course of relationship in Fig. 1 is linear up to about 0.75%. Further changes of sorption are lower.

Our conception presented is based on the presupposition that changes of the rheological parameters of modified cement suspension depends mainly on the proportional influence of additive on the repulsive forces between the charged particles and on the increase of cohesive forces (hydrates and bonds) between them. The final influence of an additive on the rheological characteristics of suspension depends on the proportional action of those forces. Therefore, the sorption and the integral value of heat liberation were chosen as certain comprehensive parameters (or representatives) of those opposite effects.

We presuppose that the magnitude of all defined, and also of undefined, repulsive forces acting due to the presence of sorbed organic molecules on the surface of solid particles changes proportionally with the sorption characteristic  $S_r$  in Fig. 1.

The integral value of heat liberation represents a number of simultaneous partial processes, which are influenced by the organic additives. The changes of proportions between the bound and free water in the hydrating suspension due to the wetting of surfaces, hydration and the creation of new formations are decisive, according our presuppositions.

It is known that the heat liberation of certain cement is a function of time of hydration and can be influenced by additives. Therefore, a regression analysis between the integral value of heat liberation (dependent variable  $Y$ ) after 5, 10 and 20 min (independent variable  $X_1$ ) of the control

Table 1  
Variations of determinations of the cone-plate system used

Number	After 5 min (mPa s)	After 10 min (mPa s)	After 20 min (mPa s)
1	364	408	504
2	330	432	520
3	336	480	510
4	320	412	507
5	305	440	525
6	318	430	512
Average	329	433	513

Additive=0%.

Download English Version:

<https://daneshyari.com/en/article/10622486>

Download Persian Version:

<https://daneshyari.com/article/10622486>

[Daneshyari.com](https://daneshyari.com)