Contents lists available at SciVerse ScienceDirect



Analytica Chimica Acta



journal homepage: www.elsevier.com/locate/aca

A superoxide anion biosensor based on direct electron transfer of superoxide dismutase on sodium alginate sol-gel film and its application to monitoring of living cells

Xiuhua Wang, Min Han, Jianchun Bao, Wenwen Tu, Zhihui Dai*

Jiangsu Key Laboratory of Biofunctional Materials, College of Chemistry and Materials Science, Nanjing Normal University, Nanjing 210097, PR China

ARTICLE INFO

Article history: Received 27 October 2011 Received in revised form 19 December 2011 Accepted 21 December 2011 Available online 10 January 2012

Keywords: Superoxide dismutase Sodium alginate sol-gel film Living cells Superoxide sensor Direct electron transfer

1. Introduction

Superoxide anion $(O_2^{\bullet-})$, one of the most abundant reactive oxygen species (ROS), is involved in a lot of physiological and pathological processes [1–4]. The normal amount of ROS is benefit for immune response, but the existence of excessive ROS is related to the occurrence of aging, heart disease, cancer and progressive neurodegenerative diseases such as Parkinson's disease [5–10]. Therefore, a selective and sensitive method for reliable and durable determination of $O_2^{\bullet-}$ with a low detection limit and wide linear range is essential. It is useful to gain a full understanding of the role which $O_2^{\bullet-}$ plays in pathology and physiology.

The methods commonly used to determine $O_2^{\bullet-}$ are electron spin resonance [11–13], conductometric analysis [14], mass spectrometry [15], spectrophotometry [16] and so on. Recently, considerable efforts have been paid on the development of electrochemical method for determination of $O_2^{\bullet-}$ because the electrochemical method is simple, selective, cost-effective, and can

ABSTRACT

The direct electron transfer of superoxide dismutase (SOD) was greatly facilitated by sodium alginate (SA) sol-gel film with the formal potential of 0.14 V, which was just located between $O_2^{\bullet-}/O_2$ and $O_2^{\bullet-}/H_2O_2$. The preparation of the SOD/SA modified electrode was simple without any mediators or promoters. Based on bimolecular recognition for specific reactivity of SOD/SA toward $O_2^{\bullet-}$, the SOD modified electrode was utilized to measure $O_2^{\bullet-}$ with good analytical performance, such as low applied potential (0 V), high selectivity (no obvious interference), wide linear range (0.44–229.88 μ M) and low detection limit (0.23 μ M) in pH 7.0 phosphate buffer solution. Furthermore, it could be successfully exploited for the determination of $O_2^{\bullet-}$ biosensor, combining with the properties of SA sol-gel film, provided a novel approach for protein immobilization, direct electron transfer study of the immobilized protein and real-time determination of $O_2^{\bullet-}$ released from living cells.

© 2012 Elsevier B.V. All rights reserved.

offer a direct, real time measurement in biological systems. The electrochemical measurements of $O_2^{\bullet-}$ based on the direct oxidation of $O_2^{\bullet-}$ mediated by biomimetic enzymes such as Mn^{2+} [17], and by enzymes such as cytochrome *c* [18–20] and superoxide dismutase (SOD) [21–23] have been reported. The third generation of $O_2^{\bullet-}$ biosensors based on the direct electron transfer of SOD has been well addressed due to the excellent selectivity and high sensitivity.

SOD is an important anti-oxidant enzyme in living organism [2,4]. It can catalyze the dismutation of the $O_2^{\bullet-}$ to O_2 and H_2O_2 efficiently and specifically, which was first reported by McCord and Fridovich [24]. Recently, great efforts have been made to enhance the direct electrochemistry of SOD and constructed selective and sensitive $O_2^{\bullet-}$ biosensors, because it is very useful to determine $O_2^{\bullet-}$ in vitro and in vivo models. However, the direct electron transfer of SOD is very difficult due to its deeply buried redox centers and the unfavorable orientations of SOD. To solve this problem, many immobilized methods and materials were used, such as dispersing gold nanoparticles onto poly(methyl methacrylate) (PMMA)-polyaniline (PANI) core-shell electrospun nanofibers [25], immobilizing SOD on silicon carbon (SiC) nanoparticles [26], silica sol-gel matrix [27,28], high conductive TiO₂ nanoneedles [29], ZnO nanodisks [30,31], gold nanostructures [32], carbon fiber [33], and self-assembled monolayer on gold electrodes [22,34].

Most biological macromolecules are highly efficient in recognizing specific molecules or catalyzing reactions in aqueous biological

Abbreviations: SOD, superoxide dismutase; SA, sodium alginate; ROS, reactive oxygen species; O₂⁻⁻, superoxide anion; RNS, reactive nitrogen species; H₂O₂, hydrogen peroxide; NO, nitric oxide; DA, dopamine; AA, ascorbic acid; ONOO⁻, peroxynitrite; PBS, phosphate butter solution; SCE, saturated calomel electrode; FESEM, field emission scanning electron microscopy; FTIR, Fourier transform infrared; i_{pa} , anodic peak current; i_{pc} , cathodic peak current; $E^{o'}$, formal potential.

Corresponding author. Tel.: +86 25 85891051; fax: +86 25 85891767. *E-mail address:* daizhihuii@njnu.edu.cn (Z. Dai).

^{0003-2670/\$ -} see front matter © 2012 Elsevier B.V. All rights reserved. doi:10.1016/j.aca.2011.12.045

media. Recently, sol–gel films have been widely used to construct biosensors such as sodium alginate (SA) [35–37]. SA is a natural anionic polysaccharide and consists of unbranched copolymers of 1–4 linked D-mannuronic acid and L-guluronic acid which is from marine brown-algae. It owns many properties such as non-toxicity, biocompatibility, hydrophilic property and low cost. It is an important biopolymer used to make microcapsules for drug delivery and immobilization of biocatalysts, wound dressing, tissue engineering [38]. Also it has high water absorbing ability which keeps a moist environment.

Macrophages (i.e. raw 264.7) are known to play an important role in host protection against a wide range of tumors and microorganisms. They are the first cells to participate in the immunological response, with the production of ROS and reactive nitrogen species (RNS) involved in the destruction of pathogens [39]. The major ROS and RNS produced within the macrophages are $O_2^{\bullet-}$, hydrogen peroxide (H₂O₂) and nitric oxide (NO) [40,41]. However, excess ROS and RNS production have been implicated in many inflammatory diseases [42–44]. In this paper, a novel $O_2^{\bullet-}$ sensor based on the direct electron transfer of SOD on SA sol–gel film was described. The obtained sensor exhibited excellent electrocatalytic response to $O_2^{\bullet-}$ and it had good stability and sensitivity. The monitoring of $O_2^{\bullet-}$ released from raw 264.7 macrophage cells using the proposed sensor was also demonstrated.

2. Experimental

2.1. Reagents and materials

SOD (3000 U, 3730 U mg⁻¹) was purchased from Sigma and used without further purification. SA was purchased from Shanghai Guoyao Chemical Reagent Co., Ltd. Dopamine (DA), ascorbic acid (AA) and peroxynitrite (ONOO⁻) were purchased from Sigma. OH• was generated in 10 μ M H₂O₂ catalyzed by Fe²⁺. Phosphate butter solution (PBS, 0.1 M) was prepared by mixed stock standard K₂HPO₄ and KH₂PO₄ solutions, and pH of PBS was adjusted by pH meter. Other reagents were of analytical grade and used as received. A stock solution of KO₂ was prepared by adding KO₂ to dimethyl sulfoxide (stored together with molecular sieve 4Å (Sinopharm Chemical Reagent Co., Ltd.)), sonicating the solution for 2 min. The stock solutions were stored at 4 °C. All solutions were prepared with doubly distilled water.

2.2. Preparation of the modified electrodes

The bare gold electrodes were polished to a mirror-like finish with 1.0, 0.3, and 0.05 μ m alumina slurry (Beuhler) followed by rinsing thoroughly with doubly distilled water. The electrodes were successively sonicated in 1:1 nitric acid, acetone and doubly distilled water, and then allowed to dry at room temperature. SOD (3000 U mL⁻¹) and SA (2 mg mL⁻¹) were mixed (1:1, v/v). Then 2 μ L of the mixture of SOD and SA was applied to the pretreated gold electrodes surface, stored in refrigerator at 4 °C until it was dry.

For control experiment, 2 μ LSA (2 mg mL⁻¹) sol-gel or 2 μ LSOD (3000 U mL⁻¹) was dripped on the gold electrode and dried at 4 °C. Then the SA modified electrode or SOD modified electrode was formed, respectively.

When the modified electrodes were not in use, they were stored in pH 7.0 PBS at $4 \,^{\circ}$ C.

2.3. Apparatus and measurements

Electrochemical experiments were carried out on CHI 660B electrochemical working station, with the modified gold electrode as a working electrode, platinum wire as a counter electrode and saturated calomel electrode (SCE) as a reference electrode. All measurements were carried out at room temperature (about 25 °C). The experimental solutions were deoxygenated by bubbling highly pure nitrogen for 15 min, and a nitrogen atmosphere was kept over the solutions during measurements. The morphologies of the samples were characterized by LEO1530 VP field emission scanning electron microscopy (FESEM) at an acceleration of 15 kV. Fourier transform infrared (FTIR) spectra were obtained in the range of 2500–1200 cm⁻¹ on a NEXUS 670 (Nicolet) FTIR instrument at room temperature.

The $O_2^{\bullet-}$ solutions were prepared by the addition of aliquots of KO₂ stock solution (N₂ saturated). The concentrations of $O_2^{\bullet-}$ were determined by recording the reduction of ferricytochrome *c* spectrophotometrically and using the extinction coefficient (21.1 mM⁻¹ cm⁻¹) of ferrocytochrome.

2.4. Cell culture

Raw 264.7 macrophage cells grew at 37 °C in Dulbecco's modified Eagle medium (DMEM) supplemented with 10% (v/v) fetal bovine serum (FBS), 100 U mL⁻¹ penicillin, and 100 mg mL⁻¹ streptomycin in a 5% CO₂ environment. After growing to 90% confluence, the cells were then washed with pH 7.4 PBS and the cell number was estimated by a hemocytometer.

2.5. $O_2^{\bullet-}$ released from living cells

Raw 264.7 macrophage cells were incubated with zymosan $(250\,\mu g\,m L^{-1})$ in DMEM complete medium in the presence of nitroblue tetrazolium (NBT). For cell adhesion, 0.5 mL of cells at a concentration of 1×10^5 cells $m L^{-1}$ was directly plated on the modified electrode for the electrochemical experiments. The adhered cells were fixed with 2% glutaraldehyde for 20 min at room temperature.

3. Results and discussion

3.1. Characterization of SOD/SA modified gold electrode

The FESEM images of SOD, SA and SOD/SA film were shown in Fig. 1. Significant differences in the surface morphology of the three samples could be observed. The SEM image of SOD with more uniform surface could be observed in Fig. 1A. The surface of the SA was formed by isolated and irregularly shaped enzyme biomolecular flakes (Fig. 1B). However, the image of the SOD/SA (Fig. 1C) showed the aggregates of the trapped enzyme biomolecular with a relatively uniform film, which indicated the formation of specific interface.

It could be seen from Fig. 2 that the FT-IR spectra of the SA exhibited its asymmetric stretching vibration of carboxylate O–C–O at 1646 cm⁻¹, the C–OH deformation vibration with contribution of O–C–O symmetric stretching vibration of carboxylate group at 1536 cm⁻¹, and the C–O stretching vibration of pyranose rings at 1228 cm⁻¹, respectively [45] (curve a). The IR spectra of SOD also showed the adsorption bands at 1633 and 1542 cm⁻¹ which were attributed to amide I and amide II, respectively [46] (curve b). Upon adsorption of the SOD on SA, the bands at 1633 cm⁻¹ shifted to 1594 cm⁻¹, and the band corresponding to amide II and adsorption bands at 1228 cm⁻¹ disappeared, implying an interaction between SA and SOD (curve c).

3.2. Direct electrochemical behavior of SOD

Fig. 3 shows the cyclic voltammograms (CVs) of different electrodes in 0.1 M pH 7.0 PBS at 500 mV s^{-1} . No peak was observed at both bare gold electrode and SA modified gold electrode, which

Download English Version:

https://daneshyari.com/en/article/1166357

Download Persian Version:

https://daneshyari.com/article/1166357

Daneshyari.com