Contents lists available at ScienceDirect

### **Chinese Chemical Letters**

journal homepage: www.elsevier.com/locate/cclet

Original article

## One-pot, solvent-free and efficient synthesis of 2,4,6-triarylpyridines catalyzed by nano-titania-supported sulfonic acid as a novel heterogeneous nanocatalyst

Elham Tabrizian, Ali Amoozadeh <sup>\*</sup>, Salman Rahmani, Elham Imanifar, Saeede Azhari, Masoumeh Malmir

Department of Organic Chemistry, Faculty of Chemistry, Semnan University, Semnan 35131-19111, Iran

#### ARTICLE INFO

Article history: Received 26 February 2015 Received in revised form 10 April 2015 Accepted 8 June 2015 Available online 17 June 2015

Keywords: Nano-titania-supported sulfonic acid Multicomponent reaction 2,4,6-Triarylpyridines Solvent free Heterogeneous nanocatalyst

#### ABSTRACT

Nano titania-supported sulfonic acid (n-TSA) has found to be a highly efficient, eco-friendly and recyclable heterogeneous nanocatalyst for the solvent-free synthesis of 2,4,6-triarylpyridines through one-pot three-component reaction of acetophenones, aryl aldehydes and ammonium acetate. This reported method illustrates several advantages such as environmental friendliness reaction conditions, simplicity, short reaction time, easy work up, reusability of catalyst and high yields of the products. One new compound is reported too. Furthermore, the catalyst could be recycled after a simple work-up, and reused at least six times without substantial reduction in its catalytic activity.

© 2015 Chinese Chemical Society and Institute of Materia Medica, Chinese Academy of Medical Sciences. Published by Elsevier B.V. All rights reserved.

#### 1. Introduction

In the last two decades, multicomponent reactions (MCRs) have been widely used in organic synthesis due to their efficacy for the generation of heterocyclic compounds in a single synthetic step [1]. These reactions represent very powerful chemical technology procedures from both economical and synthetic points of view and they are one of the most influential techniques in green chemistry, industrial chemistry and the modern drug discovery process [2]. Therefore, the discovery of novel MCRs is an interesting topic for synthetic chemistry researchers.

Recently, solid-supported heterogeneous catalysts have gained considerable interest in organic synthesis because of their unique properties such as high efficiency due to more surface area, more stability, reusability, low toxicity and ease of handling [3–8]. We have recently reported nano titania-supported sulfonic acid (n-TSA) [9], as an effective heterogeneous acidic nanocatalyst for the promotion of a wide range of organic reactions as for its Lewis and Bronsted acidity features. Ease of preparation, simple

\* Corresponding author. E-mail address: aamozadeh@semnan.ac.ir (A. Amoozadeh). work-up procedures and improved product yields, facile purification, shorter reaction times, mild reaction conditions and recyclability of the catalyst are the main superiorities of n-TSA.

Pyridine ring systems, particularly 2,4,6-triarylpyridines represent an important class of heterocyclic compounds because of their unique position in medicinal chemistry [10,11]. Moreover, they are prominent synthons in supramolecular chemistry, with their  $\pi$ stacking ability along with directional H-bonding capacity [12,13]. In addition, the excellent thermal stabilities of these pyridines have instigated a growing interest for their use as monomeric building blocks in thin films and organometallic polymers [14].

Since, Krohnke's original report on the synthesis of 2,4,6-triarylpyridines [15], there has been a plethora of research targeting their syntheses [16,17]. Recently, the synthetic approach to 2,4,6-triarylpyridines involves cyclo-condensation reaction of acetophenones, benzaldehydes and ammonium acetate in the presence of different catalysts under heating condition or sonication and microwave irradiation [18–22].

Wide variety of 2,4,6-triarylpyridine chemical and pharmacological applications, encouraged us to develop and validate an efficient protocol for their synthesis. Herein, we have reported nano titania-supported sulfonic acid catalyzed synthesis of 2,4,6triarylpyridines under solvent-free conditions.

http://dx.doi.org/10.1016/i.cclet.2015.06.013

1001-8417/© 2015 Chinese Chemical Society and Institute of Materia Medica, Chinese Academy of Medical Sciences. Published by Elsevier B.V. All rights reserved.





CrossMark

#### 2. Experimental

Chemicals were purchased from the Merck chemical companies. Thin-layer chromatography (TLC) on commercial plates of silica gel 60 F254 was used to monitor the progress of reactions. The products were characterized by FT-IR spectra, <sup>1</sup>H NMR and <sup>13</sup>C NMR. FT-IR spectra were recorded on Shimadzu FT-IR 8400 instrument. <sup>1</sup>H NMR and <sup>13</sup>C NMR spectra were recorded on Bruker Advance Spectrometer 300 MHz and 75 MHz, respectively, using CDCl<sub>3</sub> as solvent. The chemical shifts are expressed in parts per million (ppm) and tetramethylsilane (TMS) was used as an internal reference. Melting points were recorded on a THERMO SCIENTIFIC 9100 apparatus.

#### 2.1. General procedure for the synthesis of catalyst (n-TSA)

Chlorosulfonic acid (1 mL, 15 mmol) was added dropwise to a suspension of powdered nano  $TiO_2$  (4 g) in dry  $CH_2Cl_2$  (20 mL) over a period of 30 min while the mixture was stirred slowly in an ice bath. The mixture was stirred for 30 min at room temperature until HCl evolution was seized. Then, the  $CH_2Cl_2$  was removed under reduced pressure and the solid powder was washed with ethanol (10 mL) and dried at 70 °C. n-TSA was obtained as a white solid powder [9].

The mmol of H<sup>+</sup> per gram of catalyst was also evaluated. For this purpose, the surface acidic protons of nano-TiO<sub>2</sub>-SO<sub>3</sub>H (100 mg) were ion-exchanged with a saturated solution of NaCl (10 mL) by sonicating. This process was repeated twice more, yielding 30 mL of proton-exchanged brine solution. Therefore, to determine the loading of acid sites on the synthesized catalyst the obtained solution titrated with NaOH (0.1 mol/L) solution in the presence of phenol red indicator solution or pH meter. The amounts of acidic protons found to be 4.5 mmol g<sup>-1</sup> of n-TSA. This finding means the effective density of the acid sites.

The catalyst was characterized in our previously published paper by the X-ray diffraction (XRD), scanning electron microscopy (SEM), FT-IR spectroscopy, thermal gravimetric analysis (TGA) and the acid strength of n-TSA was determined by the Hammett acidic function too [9].

## 2.2. General procedure for the synthesis of 2,4,6-triarylpyridine derivatives

A mixture of acetophenones (2 mmol), aromatic aldehydes (1 mmol), ammonium acetate (1.5 mmol) and 0.009 g of n-TSA was stirred at 110 °C under solvent-free condition for an appropriate time. After completion of the reaction (monitored by TLC), the reaction mixture was cooled, eluted with hot ethanol (2 mL) and was centrifuged to separate the catalyst. The title compounds were obtained in their crystalline forms by recrystallization of ethanol solution.

2,6-Bis(4-bromophenyl)-4-(*p*-tolyl)pyridine (**5c**): Light green crystal; mp: 236–240 °C; IR (KBr, cm<sup>-1</sup>)  $\nu_{max}$ : 3028, 1601, 1577, 1516, 1489; <sup>1</sup>H NMR (300 MHz, CDC1<sub>3</sub>):  $\delta$  2.46 (s, 3H), 7.33 (d, 2H, *J* = 8.12 Hz), 7.60 (m, 6H), 7.80 (m, 2H), 8.05 (dd, 4H, *J* = 7.66, 4.02 Hz); <sup>13</sup>C NMR (75 MHz, CDCl<sub>3</sub>):  $\delta$  21.3, 116.8, 123.6, 126.9, 128.6, 129.9, 131.8, 135.6, 138.2, 139.3, 150.3, 156.3.

#### 3. Results and discussion

Considering our researches toward evaluating the catalytic activity of n-TSA for the synthesis of organic compounds [9,23], we have investigated the synthesis of 2,4,6-triarylpyridines (4-7) *via* one-pot, three-component cyclo-condensation reaction of acet-ophenones (1), aldehydes (2) and ammonium acetate (3) under solvent-free conditions (Scheme 1).



Scheme 1. Synthesis of 2,4,6-triarylpyridine derivatives by n-TSA.

To choose the most appropriate condition in this reaction and to understand the influence of different variables, several experiments were studied. Initially, we optimized the amount of catalyst in order to find the required catalyst load. The obtained results are listed in Table 1.

As indicated in Table 1, the best yield was obtained in the presence of 0.009 g catalyst, which is enough to carry out the reaction efficiently (Table 1, entry 4).

In the next step, the effect of temperature, solvent and ammonia source was examined over the reaction and the obtained results are shown in Table 2.

As can be seen in Table 2, the product yield increased as the reaction temperature was raised at 110 °C and the product was obtained in high yield which was considered as the optimum temperature (Table 2, entry 6), but at higher temperature the yield was decreased (Table 2, entry 7) due to side reactions monitored by TLC. On the other hand, neither polar nor non-polar solvents are suitable for this reaction (Table 2, entries 8–13) and the best yield was obtained under solvent-free condition (Table 2, entry 6), which is due to the appropriate interaction between the catalyst and solvent. Eventually, the effect of various ammonia sources on yield of the product was shown that the maximum yield was obtained for NH<sub>4</sub>OAc (Table 2, entry 6), while other ammonia sources required longer reaction times and produced lower yields (Table 2, entries 14–18).

To develop the scope of the reaction, a wide range of aldehydes and acetophenones was subjected to n-TSA-catalyzed reaction under the optimized conditions (Table 3).

In all cases, aromatic aldehydes with substituents carrying either electron-donating or electron-withdrawing groups reacted successfully and gave the products in good yields (Table 3). It was found that aromatic aldehydes with electron-withdrawing groups

 Table 1

 Optimum amount of catalyst on the synthesis of 2,4,6-triphenylpyridine.<sup>a</sup>

	CH <sub>3</sub> + NE	I <sub>4</sub> OAc <u>n-TSA</u> Solvent free 110 °C		
Entry	Catalyst (g)	Yield (%) <sup>b</sup>	TON <sup>c</sup>	$TOF^{d}(h^{-1})$
1	0	65	_	_
2	0.002	73	58.4	29.2
3	0.004	85	34	17
4	0.009	93	16.53	8.26
5	0.012	92	12.27	6.13
6	0.016	91	9.1	4.55
7	0.020	91	7.28	3.64

 $^a\,$  Reaction conditions: acetophenone (2 mmol), benzaldehyde (1 mmol), NH4OAc (1.5 mmol) at 110 °C under solvent-free conditions, reaction time: 2 h.

<sup>b</sup> Isolated yields.

<sup>c</sup> TON = mmol of product per mmol of catalyst.

<sup>d</sup> TOF=TON/time.

Download English Version:

# https://daneshyari.com/en/article/1257104

Download Persian Version:

https://daneshyari.com/article/1257104

Daneshyari.com