

On the stability of the “wired” bilirubin oxidase oxygen cathode in serum

Chan Kang^a, Hyosul Shin^b, Adam Heller^{b,*}

^aDepartment of Chemistry, Chonbuk National University, Chonju 561-756, South Korea

^bDepartment of Chemical Engineering, University of Texas, Austin, TX 78712, United States

Received 15 November 2004; received in revised form 2 March 2005; accepted 4 March 2005

Available online 31 May 2005

Abstract

Oxygen is electroreduced to water on the “wired” bilirubin oxidase (w-BOD) catalyst at a considerably lesser potential than on pure platinum. The w-BOD catalyst could be of value in an implantable glucose–O₂ biofuel cell, operating living tissue, if it were stable in serum. We found, however, that w-BOD loses its activity in a few hours in the combined presence of the urate and O₂, both of which are normal serum constituents (*Bioelectrochemistry*, 2004, 65, 83–88). Here we report a second major instability: When the disconnected w-BOD cathode is allowed, in the absence of urate, to poise itself at the potential of the O₂/H₂O half cell at pH 7.2, it loses its activity rapidly. Unlike the urate/O₂ caused loss, this loss can be avoided either by applying a potential that is reducing relative to the O₂/H₂O half-cell potential, or by excluding O₂ and adding a mildly reducing reagent, such as urate. The w-BOD cathode can be stored, therefore, in deoxygenated serum, which contains urate.

© 2005 Elsevier B.V. All rights reserved.

Keywords: w-BOD cathode; Serum; Urate

1. Introduction

Glucose–O₂ biofuel cells, consisting of two “wired” bioelectrocatalyst-coated electrodes, have been recently reported [1–6]. Because the two reactants are present in most tissues, and because in the saline physiological pH 7.2 environment the cell does not require a membrane or a case, a cell consisting merely of two bioelectrocatalyst-coated carbon fibers could function in-vivo. The w-BOD electrocatalyst consists of the blue copper oxidase bilirubin oxidase (BOD) and its “wiring” redox polymer [7–11]. When BOD from *Myrothecium verrucaria* (*Mv*) is “wired” to a carbon cloth by the copolymer of polyacrylamide and poly(*N*-vinylimidazole) complexed with [Os(4,4′-dichloro-2,2′-bipyridine)₂Cl]⁺²⁺ [10], O₂ is electroreduced to water, under physiological conditions (pH 7.4, 0.15 M NaCl, 37.5 °C) at a current density as high as 5 mA cm^{−2} at −0.18 V vs. the reversible potential of the O₂/H₂O electrode in the

same buffer. When BOD from *Trachyderma tsunodae* (*Tt*) is “wired,” O₂ is electroreduced at a current density of 3 mA cm^{−2} at −0.14 V vs. the reversible potential of the O₂/H₂O electrode [11]. The overpotentials of smooth carbon fibers or disks coated with these bioelectrocatalysts are much smaller than those of smooth platinum fibers or disks [11,12]. Miniature biofuel cells, formed by combining the w-BOD cathode with a “wired” glucose oxidase anode, operate both in a physiological buffer solution at 37 °C for a week and in a living plant, a grape, for a day [2,3].

In serum the w-BOD electrocatalyst loses, however, its activity in a few hours. Among the serum components [13,14], urate is particularly rapidly electrooxidized and was found to damage glucose anodes when operated at oxidizing potentials, near those at which the w-BOD cathodes operate in biofuel cells [15]. The combination of urate and dissolved O₂ damages also the w-BOD cathode [16]. The oxidation of urate by O₂ is catalyzed both by BOD and by its “wire”, and a urate oxidation product irreversibly deactivates the BOD. When urate is added to a physiological buffer solution it causes, at its typical serum concentration, a loss of 1/3rd of the O₂ electroreduction current in 1 h, and of

* Corresponding author. Tel.: +1 512 471 8874; fax: +1 512 471 8799.
E-mail address: heller@che.utexas.edu (A. Heller).

40% of the current in 3 h in the operating, or connected, cathode. Here we show that when the w-BOD cathode is disconnected and its potential is allowed to “float”, poisoning itself under air near the O_2/H_2O potential, the loss of current is exceptionally rapid, greatly exceeding the urate/ O_2 caused loss. We also show that this loss is avoided by poisoning the w-BOD cathode at its optimal operating potential in biofuel cells, and that the cathode is stable when stored in de-oxygenated serum.

2. Experimental section

2.1. Chemicals and materials

Bilirubin oxidase (BOD) from *Trachyderma tsunodae* (*Tt*) was purchased from Amano, Lombard, IL. Poly (ethylene glycol) (400) diglycidyl ether (PEGDGE) was purchased from Polysciences Inc. (Warrington, PA). Uric acid, and 2,2'-azino-bis(3-ethylbenzothiazoline-6-sulfonic acid) (ABTS) were purchased from Sigma, St. Louis, MO. The frozen calf serum (Sigma cat. # C8056, from formula-fed bovine calves, iron-supplemented, cell culture test) was melted before use. A fresh solution of BOD was prepared for each experiment. The pH 7.4 20 mM phosphate, and the pH 7.4 physiological 20 mM phosphate, 0.15 M NaCl (PBS) buffers were prepared with de-ionized water. The electrochemical measurements were performed in PBS and pH 7.4 20 mM phosphate, without NaCl, was used for dissolving the enzyme and the redox polymer. Uric acid was dissolved in 1 M KOH, then the pH was brought to 7.4 using KH_2PO_4 , to yield a 10 mM urate solution.

The BOD “wiring” copolymer of polyacrylamide and poly(*N*-vinylimidazole) complexed with $[Os(4,4'\text{-dichloro-2,2'\text{-bipyridine})}_2Cl]^{+/2+}$ (PAA-PVI- $[Os(4,4'\text{-dichloro-2,2'\text{-bipyridine})}_2Cl]^{+/2+}$) was synthesized as described [10].

2.2. The BOD cathode

Carbon cloth cathodes (0.107 cm^2) were made by the reported three-step procedure, using Toray TGPH-030 carbon cloth from E-TEK, Somerset, NJ [10,17]. The 3 mm diameter glassy carbon electrodes were initially sanded with 600 and 1200 SiC paper, then polished with a $0.3\text{ }\mu\text{m}$ alumina slurry and sonicated in de-ionized water. The cleaned glassy carbon electrodes showed featureless voltammograms. The catalytic films were formed of a mixture of $17.3\text{ }\mu\text{L}$ of 4.5 mg/mL redox polymer in water, $1.44\text{ }\mu\text{L}$ of buffer, $4.8\text{ }\mu\text{L}$ of 15 mg/mL BOD in buffer, and $3.36\text{ }\mu\text{L}$ of 3.2 mg/mL PEGDGE in de-ionized water. A $9\text{ }\mu\text{L}$ aliquot of the mixed solution was pipetted onto the hydrophilic carbon cloth mounted on the glassy carbon disk, which was promptly wetted and penetrated by the solution. The films were cured for at least 18 h at room temperature before use.

2.3. Instrumentation and cell

The measurements were performed using a Model CHI832 potentiostat (CH-Instruments, Austin, TX) controlled through a personal computer. The rotation of the electrode was controlled using a Pine Instrument rotator (Grove, PA). Spectra were measured using an HP 8452A UV–visible spectrophotometer. The three-electrode cell used had a commercial Ag/AgCl (3 M NaCl) reference electrode and an auxiliary platinum wire electrode. The temperature of the cell was controlled with an isothermal circulator (Fisher Scientific, Pittsburg, PA).

2.4. BOD activity assay

BOD was assayed by measuring the time-dependence of the ABTS absorbance at 405 nm [18,19] after adding the assayed BOD aliquot, using the reported $35\text{ mM}^{-1}\text{ cm}^{-1}$ molar absorption coefficient at $22\text{ }^\circ\text{C}$. A unit of enzyme activity (U) is that generating $1\text{ }\mu\text{mol}$ of oxidized ABTS/min; the specific activity is the number of units per mg (U/mg).

3. Results and discussion

The stabilities of the w-BOD cathodes were determined by comparing their O_2 electroreduction-associated voltammograms, before and after 2 h long immersion and rotation, at 100 rpm, in physiological buffer solutions, with or without 0.5 mM urate, under 1 atm O_2 or under argon, and while disconnected or connected and poised at 0.1 V vs. Ag/AgCl. The voltammograms are shown in Fig. 1A–H and the results are summarized in Table 1. With 0.5 mM urate, under 1 atm O_2 and with the electrode disconnected from the potentiostat, 73% of the O_2 electroreduction current was lost. Poisoning the electrode at 0.1 V vs. Ag/AgCl, at which both the “wiring” polymer’s *N*-vinylimidazole-function bound $[Os(4,4'\text{-dichloro-2,2'\text{-bipyridine})}_2Cl]^{+/2+}$ centers and the Cu atoms of BOD are in the reduced state, reduced the loss to 26%. (Fig. 1A and B). When the 0.1 V vs. Ag/AgCl potential was applied, and oxygen and urate were both present, the loss was 26% (Fig. 1B), but no loss was seen in the absence of either urate or O_2 (Fig. 1D and F), confirming earlier results [16]. In the absence of O_2 , but in the presence of urate, the cathode was stable, regardless of whether or not a potential was applied (Fig. 1E and F).

Without urate (Fig. 1C and D) 78% of the current was lost when the electrode was disconnected, but there was no current loss when a 0.1 V vs. Ag/AgCl potential was applied. In the presence of urate, the disconnected electrode under 1 atm O_2 lost 73% of its current (Fig. 1A and E), but there was no loss in the de-oxygenated solution. The disconnected electrode was unstable under 1 atm O_2 , where the osmium centers of the “wire”, as well as the copper centers of BOD, were in their oxidized states (Os^{3+} and

Download English Version:

<https://daneshyari.com/en/article/1272748>

Download Persian Version:

<https://daneshyari.com/article/1272748>

[Daneshyari.com](https://daneshyari.com)