



Iodine binding property of a ternary complex consisting of starch, protein, and free fatty acids

Jie Liu^a, Lingchun Fei^a, Michelle Maladen^b, Bruce R. Hamaker^b, Genyi Zhang^{a,b,*}

^aSchool of Food Science and Technology, Jiangnan University, Lihu Road, No.1800, Wuxi 214122, Jiangsu Province, People Republic of China

^bWhistler Center for Carbohydrate Research, Department of Food Science, Purdue University, 745 Agriculture Mall Drive, West Lafayette, IN 47907, USA

ARTICLE INFO

Article history:

Received 21 May 2008

Received in revised form 10 August 2008

Accepted 21 August 2008

Available online 31 August 2008

Keywords:

Ternary complex

Iodine binding

Potentiometric titration

In-between spectrophotometric property

Amylose–FFA complex

ABSTRACT

A ternary complex consisting of amylose, whey protein, and free fatty acids (FFA) has been identified in our previous investigations, and its iodine binding properties were investigated. After reaction with iodine solution, an absorption peak ($\lambda_{\max}$) at 620 nm was shown for pure amylose whereas the $\lambda_{\max}$ decreased to 510 nm when amylose was first complexed with FFA. Interestingly, a $\lambda_{\max}$ of 550 nm with an intermediate absorbance was observed for the ternary complex indicating its intermediate spectrophotometric property. Consistently, the amount of iodine bound by the ternary complex was between free amylose and typical amylose–FFA complex from potentiometric titration indicating the amylose–FFA complex within the ternary complex is less compact and more space is left for iodine binding. This in-between property of the ternary complex suggests it can be used as a molecular carrier to accommodate a fourth component in addition to its functional lipids carrying capability in food product development.

© 2008 Elsevier Ltd. All rights reserved.

1. Introduction

A three-component complex formed by starch (amylose), protein and free fatty acids (FFA) after a heating and cooling process was identified previously by our group through rheological property measurement and high performance size exclusion chromatograph (HPSEC) analysis. The rheological property (Zhang & Hamaker, 2003b) using a Rapid Visco-analyzer (RVA) showed an atypical cooling stage viscosity peak in the RVA profile of starch paste in the presence of whey protein and FFA, and the HPSEC chromatogram of a dilute model system (Zhang, Maladen, & Hamaker, 2003a) revealed a distinct ternary complex with a molecular weight of $\sim 6\text{--}7 \times 10^6$ Da and amylose was the major functional starch molecules in the complex. Further experimental results using different cereal flours (Zhang & Hamaker, 2005) showed similar rheological properties indicating the three-component interaction among starch, protein and FFA might be a common phenomenon in multi-component food systems.

Amylose is an essentially linear macromolecule composing of α -1,4-linked glucosyl units, and it readily binds iodine ions to form a blue complex, which is commonly used to measure the content of amylose (Knutson, 1986) spectrophotometrically and/or potentiometrically.

For spectrophotometric method, there are variations in terms of absorptivity and wavelength of the maximum absorbance ($\lambda_{\max}$) depending on the degree of polymerization (DP) (Bailey & Whelan, 1961) and the structural properties of amylose molecules, which determine the composition of the polyiodine chains complexed with amylose helices. Yu, Houtman, and Atalla (1996) demonstrated that the primary polyiodide chains were composed of I_3^- and I_5^- subunits, and they could be combined to form four dominant polyiodide chains (I_9^{3-} , I_{11}^{3-} , I_{13}^{3-} and I_{15}^{3-}) with different absorbance spectra when complexed with amylose. Overlapping of these different polyiodine chains produces the characteristic spectrum of the amylose–iodine complex. Additionally the length of the α -1,4-linked glucosyl units available for amylose–iodine complex formation influences the relative proportions of the individual spectrum. Potentiometric titration of iodine is another method that directly measures the amount of bound iodine independent of the length or properties of the amylose in samples. Thus, a combination of spectrophotometric measurement and potentiometric titration will give a better description of iodine binding properties of the amylose molecule, and help to understand the molecular structure of amylose under different conditions.

The property of amylose–iodine complexation has been used in our previous studies showing amylose is the major starch molecule participated in the ternary complex. Differential Scanning Calorimetry (DSC) analysis of the ternary complex revealed that amylose–FFA complex was the major secondary structural component in the ternary complex, and its decreased melting enthalpy compared to

* Corresponding author. Address: Whistler Center for Carbohydrate Research, Department of Food Science, Purdue University, 745 Agriculture Mall Drive, West Lafayette, IN 47907, USA.

E-mail address: gzhang@purdue.edu (G. Zhang).

typical amylose–FFA complex (Zhang & Hamaker, 2004) indicated that the iodine binding by the ternary complex would be different from typical amylose–iodine complex. Therefore, a detailed characterization of the iodine binding properties of the ternary complex is necessary to further the understanding of the structure of the ternary complex formed during the three-component interactions.

2. Experimental

2.1. Materials

Normal maize starch was defatted with 85% methanol for 16 h at room temperature before experiment. Whey protein isolate (WPIBioPro, 97.5% protein) was from Davisco Foods International, Inc. (Eden Prairie, MN). Lauric (C12:0), myristic (C14:0), palmitic (C16:0), stearic acid (C18:0), and linoleic (*cis*-9,*cis*-12-octadecenoic acid, C18:2) acids were from Sigma Chemical Co. (St. Louis, MO). Double distilled water was used in the experiment.

2.2. Amylose, protein and FFA complexation in a dilute system

A dilute system was used to examine amylose–protein–FFA complexation. The normal maize starch solution (0.5%) was prepared by heating for 20 min in a boiling water bath and then cooled to room temperature. After centrifugation at 30,000g for 20 min, the supernatant was used as the amylose solution for interacting with protein and FFA. Interaction among amylose, FFA, and protein was performed by adding 5, 2.5, 1.25, 0.5 mg of whey protein (dissolved in purified water, 10 mg/mL) and 2.5 mg of FFA (dissolved in petroleum ether, 10 mg/mL) to a capped glass tube containing 10 mL amylose solution and then cooked for another 20 min in a boiling water bath with continuous stirring. When the cooked sample was cooled slowly overnight at room temperature with continuous stirring, the supernatant was filtered through a 0.45 μ m filter and injected into a HPSEC–MALLS system (Zhang, Zihua, & Hamaker 2006) for analysis. For comparison, amylose–FFA complex was also prepared by adding corresponding volume of water (compensating the volume of protein solution), and amylose–protein mixture were also kept the same volume by adding water.

The optimum condition to form the three-component complex was found to be 0.5 mg whey protein and 2.5 mg FFA in 10 mL normal maize starch solution. The differential scanning calorimetry (DSC) analysis of the freeze-dried materials used in the dilute model system was performed according to the procedure of Zhang et al. (2006).

2.3. Reaction between iodine and the ternary complex

Iodine solution (2% KI, 0.2% I₂) stored in a nonactinic bottle was used as the standard iodine solution to react with the prepared ternary complex. For comparison, amylose–FFA complexes were also prepared in the same way without adding protein. Then the solutions (2 mL, with the same amylose concentration) of amylose, amylose + whey protein, amylose–FFA complex, and the ternary complex prepared following the above procedure were reacted with 0.2 mL iodine solution. The UV–Vis spectra of the samples were measured using a UV–Vis spectrophotometer Model TU-1900 (Peaking Puxi Inc. Beijing) from 200 to 800 nm.

2.4. Potentiometric titrations of the bound iodine by the ternary complex

A digital pH/mV meter was used (Corning pH/ion analyzer 350, Corning, NY) to measure the iodine binding ability of the samples.

The electrode was a platinum redox combination electrode, having an epoxy body with replaceable junction and refillable electrode with a BNC connector (Corning, Cat. No 476516, Big Flats, NY). The amylose solution (10 mL + 50 μ L water), amylose–FFA complex (10 mL amylose + 2.5 mg FFA + 50 μ L water), and a dilute system of starch–protein–FFA (10 mL amylose + 50 μ L protein + 2.5 mg FFA), which were prepared following the procedure described before, were used as the samples for iodine titration. After being filtered through a 5 μ m filter, the samples was titrated potentiometrically with iodine as described by Schoch (1964).

Sample solution (5 ml) and 2.5 ml of 0.4 N potassium iodide (KI) solution were stirred in a beaker at a constant rate with a magnetic stirrer. Successive amounts of potassium iodate (KIO₃) were added gradually, and change in millivolts was read at increments between 240 and 290 mV. A blank containing 5 ml distilled water and 2.5 ml 0.4 N KI was used as a control. From the mV readings, the concentration of free iodine (I₃[−]) in the solution was determined using a calibration curve. The bound iodine was estimated from the difference between the total amount of iodine added to the model system and the free iodine at each point of the curve. Bound iodine (Y) was then plotted against free iodine (X).

3. Results and discussion

3.1. HPSEC analysis of the ternary complex

HPSEC is the method used before to detect the formation of the ternary complex consisting of starch, protein and FFA, but the ternary complex peak was not so clear (Zhang et al., 2003a). After optimizing the relative content of whey protein component, a clear and distinct peak was shown in the HPSEC profile after a heating and cooling process (Fig. 1 top, Lin3) when linoleic acid was used as the FFA component. The major component of the initial starch solution after centrifugation was amylose with a broad distribution (Fig. 1, starch-CK) and residual amylopectin represented by a small peak. The disappearance of amylose peak after the formation of the ternary complex demonstrates that amylose is the major component of the ternary complex. Similar HPSEC profiles were also shown when other FFAs including oleic acid and stearic acid were used as the FFA component (Fig. 1 bottom, CK-SPR is the HPSEC profile of starch + whey protein). Therefore, the ternary complex formed among amylose, whey protein and FFA can be easily detected using a technique of HPSEC.

3.2. Iodine binding of the ternary complex measured by potentiometric titration

Potentiometric titration offers the most definitive measure of the iodine binding capacity of amylose independent of the structural changes of the amylose molecules under different conditions. Literature reports (Kim & Robinson, 1979; Yamamoto, Sano, Harada, Yasunaga, & Tatsumoto, 1984) have shown that the presence of FFA or surfactants, which formed amylose–lipid complex (Godet, Bizot, & Buleon, 1995), decreased iodine affinity to amylose as revealed by potentiometric measurement. Our results of amylose–FFA complex with a lower iodine binding compared to free amylose (Fig. 2) is consistent with these observations. Less available space in the helical cavity of amylose complexed with FFA is generally considered as the cause for the lower iodine binding capacity of the amylose–FFA complex.

The amylose–FFA–protein ternary complex showed an intermediate iodine binding property between free amylose and typical amylose–FFA complex as shown in Fig. 2. The relative iodine affinity of 100.0%, 53.0%, and 14.5% for free amylose, ternary complex and amylose–FFA complex, respectively, were calculated based

Download English Version:

<https://daneshyari.com/en/article/1386349>

Download Persian Version:

<https://daneshyari.com/article/1386349>

[Daneshyari.com](https://daneshyari.com)