



A sonochemical-assisted synthesis of spherical silica nanostructures by using a new capping agent

Maryam Masjedi-Arani^a, Masoud Salavati-Niasari^{a,*}, Davood Ghanbari^a, Gholamreza Nabiyouni^b

^a*Institute of Nano Science and Nano Technology, University of Kashan, Kashan P.O. Box 87317-51167, Iran*

^b*Department of Physics, Faculty of Science, Arak University, 38156-8-8349 Arak, Iran*

Received 16 April 2013; received in revised form 6 June 2013; accepted 10 June 2013

Available online 28 June 2013

Abstract

Spherical silica nanostructures have been prepared using the sonochemical method. The silica nanoparticles were obtained by hydrolysis of tetraethyl orthosilicate (TEOS) in an alcohol solution. The influence of different surfactants i.e. cationic, anionic, polymeric and a new Schiff base on the morphology of the synthesized silica has been investigated. Our results show that using acetyl acetanato ethylene diimine as a new capping agent leads to produce nanostructures with suitable size distribution. The effect of different parameters such as concentration, ultrasonic wave power and reaction time on the morphology and size of the products was examined. Nanoparticles were characterized by XRD, SEM, FT-IR and EDS techniques.

© 2013 Elsevier Ltd and Techna Group S.r.l. All rights reserved.

Keywords: Silica; Sonochemical; Nanostructures

1. Introduction

Nanomaterials exhibit a wide range of practical applications in devices such as photocatalytic, supercapacitors, nanoelectronics and nano-optoelectronics. Nanostructures have gained much attention among materials, because the nanocrystal properties not only depend on their composition but also depend on their size, shape, and size distribution. The reactivity of nanoparticles can be adjusted by controlling the morphology because the exposed surfaces of the particles have distinct crystallographic planes depending on the shape. Silica is synthesized in different shapes, i.e. cubic, spherical and mesoporous [1–4]. Silica nanostructures exhibit new physicochemical properties which do not appear in their bulk material.

In the recent years, silica is increasingly used as ceramics, chromatography devices, electronic components, photo electricity devices, catalysis [5], stabilizers [6], pigments [7], pharmaceutical [8] and chemi-mechanical polishing tools [9]. Various methods such as: micro emulsions, Stöber and sonochemical

methods are currently used for synthesizing of spherical SiO₂ nanoparticles [10–17], among them, sonochemical method is one of the best because of its capability to be a facile route operating under ambient conditions. Ultrasonic irradiation causes cavitation in a liquid medium where the formation, growth and implosive collapse of bubbles occurs. The collapse of bubbles with short lifetimes produces intense local heating and high pressure. These localized hot spots can generate a temperature of around 5000 °C and a pressure of over 1800 kPa that these spots are appropriate for many chemical reactions [18–21]. The following reactions take place in a typical sonochemical method:

- (i) Silanol groups are first formed by hydrolysis.
- (ii) Siloxane bridges are then formed by a condensation polymerization reaction.
 - (i) Hydrolysis: $\text{Si}(\text{OR})_4 + \text{H}_2\text{O} \leftrightarrow \text{Si}(\text{OH})_4 + 4\text{ROH}$
 - (ii) Condensation: $2\text{Si}(\text{OH})_4 \rightarrow 2(\text{Si}-\text{O}-\text{Si}) + 4\text{H}_2\text{O}$

By utilizing ultrasound irradiation the formed bubbles collapse, resulting the generation of high speed microjets which can generate nanoparticles.

*Corresponding author. Tel.: +98 361 591 2383; fax: +98 361 555 29 30.

E-mail address: Salavati@kashanu.ac.ir (M. Salavati-Niasari).




Fig. 1. Schematic diagram of (a) formation of nanostructures and (b) effect of CTAB and SDS on the particle sizes.

Using cationic (CTAB) and anionic surfactants (SDS) lead to synthesis of bulk products. Therefore we used a new Schiff base for obtaining nanostructures. Acacen acts as a surfactant and it was used as an additive to control the shape, uniformity and size of nanoparticles. Tetraethyl orthosilicate and ethylene diamine were respectively used as starting precursor and base catalyst. The effects of different parameters such as reaction time, ultrasonic wave power and concentration on the product morphology were also investigated.

2. Experimental

2.1. Materials and physical measurements

Tetraethyl orthosilicate (TEOS), ethylenediamine (en), methanol, cetyl trimethyl ammonium bromide (CTAB) and sodium dodecyl sulfate (SDS), poly vinyl pyrrolidone (PVP) and poly ethylene glycol (PEG) were purchased from Merck Company. All of the chemicals were used without further purifications. A multiwave ultrasonic generator (Sonicator 3000; Bandeline, MS 72, Germany), equipped with a converter/transducer and titanium oscillator (horn), 12.5 mm in diameter, operating at 20 kHz with a maximum power output of 100 W, was used for ultrasonic irradiation. The ultrasonic generator automatically adjusts the power level. The wave amplitude in each experiment was adjusted

as it is required. XRD patterns were recorded by a Philips, X-ray diffractometer using Ni-filtered Cu K α radiation. SEM images were obtained using a LEO instrument. Prior to taking images, the samples were coated by a very thin layer of Pt to make the sample surface conducting and prevent charge accumulation, and therefore obtaining a better contrast. FT-IR spectra were recorded on Galaxy series FTIR5000 spectrophotometer.

2.2. Synthesis of bis(acetyl acetonato) ethylene diimine Schiff bases

Synthesis of Schiff base was based on acetyl acetone (acac) and ethylenediamine (en) at a mole ratio of 2:1. Acac and en was diluted in methanol and ethylenediamine was added slowly under stirring at room temperature. The solvent was removed and the resulting solid was crystallized from methanol.

2.3. Synthesis of spherical SiO₂ nanoparticles

25 ml of methanol and 10 ml of distilled water were sonicated. 4.5 mmol of TEOS and 0.22 mmol of Schiff bases dissolved in 5 ml of methanol were added under stirring. 0.1 ml of ethylenediamine was then added into the mixture as precipitating agent, under ultrasonic. After 30 min the precipitate was isolated by centrifuging and washed with methanol and water several times. The as-obtained products were dried at 80 °C under vacuum for 2 h, then calcinated at 650 °C for another 2 h.

3. Results and discussion

Schematic diagram of formation of nanostructures is depicted in Fig. 1a. SEM images of synthesized product using different surfactants such as anionic (SDS), cationic (CTAB), polymeric (PVP and PEG) are illustrated in Fig. 2a–d, respectively. These results show that using SDS and CTAB lead to synthesis of bulk products. However, by using PVP and PEG surfactants, nanostructure products are obtained. In fact employing of a new Schiff-base as the capping agent for synthesizing of silica nanostructures can be regarded as the novelty of this work. Acacen with high steric hindrance is a suitable capping agent for preparation of nanostructures. Schiff base group causes formation of nucleation rather than the particle growth (Fig. 1b).

In this work, synthesis of SiO₂ by applying ultrasonic waves with a power of 60 W for 20 min has been chosen as a basic reaction and the effect of different parameters on the morphology of the products has been investigated and compared.

SEM images of SiO₂ obtained at different mole ratios of acacen: Schiff base 1:20, 1:10, 1:2, 1:1 are illustrated in Fig. 3a–d respectively. At mole ratio of TEOS/acacen as 1:20, nanoparticles are synthesized. With increasing the mole ratio to 1:10 spherical nanostructures with smaller size are achieved. However at mole ratio of 1:2, the nanoparticle sizes are even smaller and size decrease is noticeable. Ultrasonic irradiation creates bubbles which produces high temperature and energy after decomposition. This process provides a sufficient amount of energy for formation of nanoparticles. The results confirm that in four

Download English Version:

<https://daneshyari.com/en/article/1462286>

Download Persian Version:

<https://daneshyari.com/article/1462286>

[Daneshyari.com](https://daneshyari.com)