

Strength distribution at interface of rotary-friction-welded aluminum to nodular cast iron

SONG Yu-lai(宋雨来), LIU Yao-hui(刘耀辉), ZHU Xian-yong(朱先勇),
YU Si-rong(于思荣), ZHANG Ying-bo(张英波)

Key Laboratory of Automobile Materials, Ministry of Education, College of Materials Science and Engineering,
Jilin University, Changchun 130025, China

Received 23 January 2007; accepted 25 July 2007

Abstract: The morphology, size and composition of intermetallic compound at the interface of Al 1050 and nodular cast iron were studied by electron microprobe analysis(EMPA) and scan electron microscopy (SEM), respectively. The bond strength of the interface was measured by the tensile tests and the morphology of the fracture surface was observed by SEM. The observation of the interface reveals that there are two distinct morphologies: no intermetallic compound exists in the central area at the interface; while numbers of intermetallic compounds (Fe_xAl_y) are formed in the peripheral area due to the overfull heat input. The tensile tests indicate that the distribution of strength in radial direction at the interface is inhomogeneous, and the central area of the interface performs greater bond strength than the peripheral area, which proves directly that the Fe_xAl_y intermetallic compounds have a negative effect on the integration of interface. The morphology on the fracture surface shows that the fracture in the central area at the interface has characteristic of the ductile micro-void fracture. So it is important to restrain the form of the intermetallic compound to increase the bond strength of the Al 1050 and nodular cast iron by optimizing welding parameters and the geometry of components.

Key words: aluminum; nodular cast iron; rotary friction welding; microstructure; strength distribution

1 Introduction

Joining of dissimilar materials is generally more challenging than that of similar metals because of differences in the physical, chemical and metallurgical properties of the parent metals to be joined[1–2]. Many highly efficient solid-state joining processes such as explosion, friction, diffusion, and cold roll welding are being developed to join dissimilar materials. Among these welding techniques, rotary friction welding(RFW) technique is a distinct, favorite method to join dissimilar metal substrates due to its characteristics of high reproducibility, sub-melting temperature, short weld time, low energy input and negligible intermetallic formation[3–4]. At present many dissimilar materials have been bonded by the RFW, such as aluminum[2,5], copper[6,7], titanium[8] and steel[9].

Pure aluminum to nodular cast iron welded joints can be readily produced by RFW, and such joints are extensively used in the various types of components for electrical machinery to obtain lightmass products and reduce manufacturing costs. Studies of the pure aluminum to nodular cast iron welded joint combinations, however, have not yet been well documented. It is well known that the bond strength at the interface is an important criterion to evaluate the mechanical properties of the RFW materials. A large number of references on the RFW of dissimilar metals have indicated that the relations between the bond strength and the microstructure at the interface have been established extensively[10–12]. However, the investigation on the strength distribution in radial direction at the interface has not been found yet. In the RFW process, the heat inputs and the temperature in the radial direction are inevitably different because of the different linear velocity

under the same rotate speed. As a consequence, the strength in the radial direction maybe exhibits obvious distinction, which influences intensively the integration strength on the interface. So the investigation on the strength distribution in the radial direction is of importance for optimizing welding parameters and geometry of components and ultimately improving the integration strength. Until now no detailed measurements of the distribution of strength in the radial direction at interface have been made.

In the present work, Al 1050 and nodular cast iron were successfully joined by the RFW process. The microstructures at the interface and the fracture surface were investigated by electron microprobe analysis (EMPA) and scan electron microscopy (SEM), respectively. The distribution of the bond strength in radial direction at interface was measured by a series of tensile tests, and the fracture behavior was also analyzed. It is expected that the preliminary results can be significant in promoting the properties of the rotary-friction-welded Al 1050/nodular cast iron composite.

2 Experimental

2.1 Rotary friction welding

The commercial Al 1050 (pure aluminum containing 99.823% of Al, mass fraction) and nodular cast iron, which were machined into rods with a diameter of 20 mm, were used for rotary friction welding. The working surfaces of both materials were polished successively with fine grades of emery papers up to 1 000 level before welding. All welds were produced using a continuous-driving machine with the constant parameters, which were optimized by static tensile strength in earlier studies. The interesting parameters were as follows: the friction pressure (p_1) was maintained at 40 MPa with the friction time (t_1) fixed at 1.0 s. The rotational speed (v) was held at 3 000 r/min. The forging pressure and forging time were 100 MPa and 3.0 s, respectively.

2.2 Microstructure of interface

Cross-sectional interfaces of the RFW were ground and polished using an emery paper and diamond powder. Microstructure and elements distribution at the cross-sectional interfaces were investigated by EMPA and SEM, respectively.

2.3 Static tensile testing

In order to measure the distribution of strength in radial direction on the interface, the specimens were machined into a series of tensile rods with different diameters as schematically shown in Fig.1. The tensile

tests were conducted at room temperature using an Instron type testing machine with cross head speed of 2.5×10^{-2} mm/s. The morphologies on the fracture surfaces were observed by SEM.




Fig.1 Schematic illustration of specimens for tensile tests

3 Results and discussion

3.1 Microstructure of interface

The interfaces are separated into five zones in the radial direction as shown in Fig.2. The preliminary observation shows that the microstructures in zone 2 and zone 4 exhibit representative features. Fig.3 and Fig.4 show the cross section microstructures of zone 2 and zone 4, respectively. It can be seen that the interface is smooth and relatively straight, and the reaction layer can




Fig.2 Partition of zones in radial direction at interface




Fig.3 Cross section microstructure in zone 2 at interface

Download English Version:

<https://daneshyari.com/en/article/1640256>

Download Persian Version:

<https://daneshyari.com/article/1640256>

[Daneshyari.com](https://daneshyari.com)