




ELSEVIER

Contents lists available at ScienceDirect

Radiation Physics and Chemistry

journal homepage: www.elsevier.com/locate/radphyschem

Nanocomposites of irradiated polypropylene with clay are degradable?



L.G.H. Komatsu, W.L. Oliani, A.B. Lugao, D.F. Parra*

Nuclear and Energy Research Institute, IPEN-CNEN/SP, Av. Prof. Lineu Prestes, 2242 Cidade Universitária, CEP 05508-000 São Paulo – SP, Brazil

HIGHLIGHTS

- Nanocomposites of PP were aged under environmental and thermal conditions.
- Barrier effect of clay platelets was verified on the nanocomposites.
- Nanocomposites showed more cracks and surface porosity after environmental ageing.
- Carbonyl indexes were lower in nanocomposites than in the irradiated PP.

ARTICLE INFO

Article history:

Received 1 December 2014

Received in revised form

25 May 2015

Accepted 2 June 2015

Available online 17 June 2015

Keywords:

Polypropylene

Montmorillonite

Nanocomposite

Irradiation process

ABSTRACT

In nowadays, polypropylene (PP) based nanocomposites containing organically modified montmorillonite (MMT), have gained great attention in the automobilistic industries, construction, paints, packaging, plastic components of the telecommunication industries. The HMSPP (high melt strength polypropylene) is a polypropylene modified by irradiation process, under acetylene atmosphere, in which irradiation occurs in ^{60}Co gamma source. However, when those materials are submitted to environmental ageing nanocomposites demonstrated high decomposition level after 1 year. This fact can be due to presence the metallic ions present in the montmorillonite. The HMS-PP and the Cloisite 20A (MMT) were mixed in twin-screw extruder using maleic anhydride as compatibilizer. In this work two formulations of nanocomposites at 0.1 and 5 wt% of clay were submitted to the environmental and thermal ageing to analyze the effects of degradation on the HMSPP nanocomposites. The evaluation of thermal properties was analyzed by Differential Scanning Calorimetry (DSC) and the chemical alterations were investigated by Carbonyl Index (CI), through Fourier Transformed Infrared (FTIR) technique. The basal distance was measured by X-ray diffraction (DRX) and the clay elements were analyzed by X-ray Fluorescence (WDXRF). The aim of this work was to understand the effects of degradation of the HMS-PP/clay nanocomposites.

© 2015 Elsevier Ltd. All rights reserved.

1. Introduction

Use of radiation to modify the molecular structure and enhancing strain hardening of PP melt, allows to use in areas such as foaming, thermoforming, extrusion coating and blow molding (Gotsis et al., 2004). The high melt strength of a polymer is either due to long chain branching or high molecular weight (Graebing, 2002).

The chemical modification initiated by radicals and the grafting reactions of different monomers on to polypropylene (iPP) in the solid state with the use of grafting at low reaction temperatures, γ , or electron-ray scattering or special peroxides were studied by Rätzsch et al. (2002). Polypropylene irradiated with electrons or gamma-rays undergoes chain scission, and the macroradicals

generated form branched macromolecules. Information on the irradiation modification of the molecular structure of PP is still limited in the literature, especially with respect to the controlled generation of long-chain-branches (LCB) (Auhl et al., 2012).

The research group of Prof. Busfield and Appleby (1986), reported the effects of crosslink enhancement by the presence of acetylene during gamma irradiation, on the physical and mechanical properties of polypropylene.

Jones and Ward (1996), in experimental analysis of the radiation-induced crosslinking of a linear low density polyethylene (LLDPE) film, measured gel fractions as a function of dose, both in vacuum and in presence of acetylene gas and in fact crosslinking was accelerated by the use of acetylene.

Grafting of long-chain-branches on PP backbone using acetylene as a crosslink promoter was developed for production of branched PP under gamma radiation process and was reported (Lugao et al., 2007; Oliani et al., 2012).

* Corresponding author.

E-mail address: dfparra@ipen.br (D.F. Parra).

Concerning polymer nanocomposites (PNCs) area, it has been attracted substantial scientific interest and developments over the last two decades with a huge market opportunity especially for the automotives and packaging industries (Okamoto, 2006). Composites of HMSPP with montmorillonite have few references in the literature (Bhattacharya et al., 2009), mainly considering the aspect of stability under weather conditions or thermal exposition. Polymers exposed to outdoors can degrade through the action of several agents, including solar ultraviolet (UV) radiation; water; pollutants (in gaseous form or, more potently, as acid-rain); elevated temperature. In a majority of cases, the main cause of property deterioration is photo-oxidation, which is initiated by UV irradiation and, as a consequence, much laboratory photo-ageing testing was conducted to determine the weatherability of polymers and to test the effectiveness of stabilizers to improve their weather resistance (White, 2006; Singh and Sharma, 2008; Rivaton et al., 2005; Attwood et al., 2006; Oliani et al., 2010).

Polypropylene undergoes predominantly chain scission under all processing conditions giving rise to pronounced reduction in the molar mass and melt viscosity of the polymer (Al-Malaika, 2003) other than melting temperature and normally increasing of crystallinity.

Abiotic peroxidation of the polyolefins, gives rise to some vicinal hydroperoxides and this process is particularly favored in the poly- α -olefins, such as polypropylene due to the susceptibility of the tertiary carbon atom to hydrogen abstraction via a hydrogen-bonded intermediate. A major proportion of the peroxide product are hydrogen-bonded vicinal hydroperoxides that break down to small biodegradable molecules such as carboxylic acids, alcohols and ketones (Wiles and Scott, 2006; Morlat et al., 2004).

One of the main aspects in the development of polymer nanocomposites is the matrix degradation. In a work of Ramos Filho et al., (2005) a polycationic bentonite clay was added to isotactic polypropylene (iPP). The compounds were prepared by melt intercalation using a twin extruder, similar to work of Komatsu et al., (2014a,b). Under 110 °C for up to 165 h, the degradation of the composites was more intense than the unfilled polymer and this may be due to the presence of acidic sites on the clay surface that act as a catalyst to the polymer oxidation, and/or due to salt decomposition, initiating the free radical degradation of iPP.

The aim of present work was to understand the degradation effects of HMSPP/Clay nanocomposites, under thermal and environmental conditions, considering the new morphology created by the irradiation in acetylene, and the presence of clay.

2. Experimental

2.1. 1 Materials and methods

The iPP pellets were manufactured by Braskem and compatibilizer agent, propylene maleic anhydride graft copolymer (PP-g-MA) was supplied by Addivant (Polybond 3200). The clay filler was Cloisite 20A by Southern Clay Products montmorillonite clay quaternary ammonium salt-modified (95 Meq/100 g). The iPP was placed in plastic bags with acetylene that were irradiated in ^{60}Co gamma source at dose of 12.5 kGy in order to obtain the HMSPP. The iPP utilized in this work has no nucleating agent or stabilizing in it formulation. Two different formulations containing the clay were prepared and are represented in Table 1. The samples were prepared in molten state using a twin-screw extruder (Thermo Haake Polymer Laboratory) to incorporate the clay in the polypropylene. The operated temperatures were 170–200 °C and speed ranging from 30 to 60 rpm. The dumbbell samples for testing were obtained from thermal molding pressure (80 bar and 190 °C), for type IV dimensions according to ASTM D638-03. After molding,

Table 1
Content of clay and compatibilizer used in the samples.

Samples	Matrix	PP-g-MA (%)	Cloisite 20A (%)
H1	HMSPP	–	–
NC1	HMSPP	3	0.1
NC2	HMSPP	3	5

the dumbbell samples were mounted in appropriated device for environmental and thermal ageing, as illustrated in Fig. 1.

2.1.1. Differential scanning calorimetry

Thermal properties of specimens were analyzed using a differential scanning calorimeter (DSC) 822, Mettler Toledo. The thermal behavior of the films was obtained by: heating from 25 to 280 °C at a heating rate of 10 °C min⁻¹ under nitrogen atmosphere, according to ASTM D 3418-08. The crystallinity was calculated according to the equation:

$$x_c = p \times \frac{\Delta H_f \times 100}{\Delta H_0} \quad (1)$$

where: ΔH_f is melting enthalpy of the sample, ΔH_0 is melting enthalpy of the 100% crystalline PP which is assumed to be 209 kJ kg⁻¹ (Brandrup et al., 1999; Mark, 2007).

2.1.2. Scanning electron microscopy

Scanning electron microscopy was done using an EDAX PHILIPS XL 30. In this study, a thin coat of gold was sputter-coated onto the samples.

2.1.3. Fourier transformed infrared spectroscopy

Infrared spectroscopy was performed at Thermo Scientific (Nicolet 6700) with ATR accessory Smart Orbit Diamond, in the range from 400 to 4000 cm⁻¹.

2.1.4. X-ray diffraction

X-ray diffraction measurements were carried out in the reflection mode on a Rigaku diffractometer Mini Flex II (Tokyo, Japan) operated at 30 kV voltage and a current of 15 mA with CuK α radiation ($\lambda = 1,541841 \text{ \AA}$).

2.1.5. X-ray fluorescence

The sample of Cloisite 20A was placed in a crucible and then placed in a muffle furnace at 900 °C to eliminate volatile components. The pastille was made pressing it under one layer of boric acid. The analysis was operated in spectrometer equipment Rigaku Fluorescence X-ray, model RIX.

3. Results and discussion

To understand the effects of environmental and thermal ageing in the polypropylene nanocomposites, the X-ray fluorescence technique was utilized to evaluate the clay composition, as presented in Table 2.

In Table 2 is observed presence of pro-oxidant elements as: Al, Fe and Mg. In the literature is reported that low quantities of these elements acts as oxidants of polymers by redox reactions with hydroperoxides (Morlat-Therias et al., 2005).

Results of FT-IR are presented in Fig. 2 while carbonyl group was identified at 1720 cm⁻¹ and the peak of 1048 cm⁻¹ is attributed to Si–O–Si bonds.

In the Fig. 3, are represented the carbonyl indexes (CI), calculated utilizing the carboxylic acid band (carbonyl stretching) around 1720 cm⁻¹, and the band 2720 cm⁻¹, as reference. This

Download English Version:

<https://daneshyari.com/en/article/1885796>

Download Persian Version:

<https://daneshyari.com/article/1885796>

[Daneshyari.com](https://daneshyari.com)