



5th International Conference on Recent Advances in Materials, Minerals and Environment (RAMM) & 2nd International Postgraduate Conference on Materials, Mineral and Polymer (MAMIP), 4-6 August 2015

## Tensile Behavior of SiCNP and MWCNTs Filled Toughened Epoxy Nanocomposites: A Comparative Study

S. Ratim<sup>1, 2\*</sup>, S. Ahmad<sup>1</sup>, N.N. Bonnia<sup>2</sup>, E.S. Ali<sup>3</sup>, J.A. Razak<sup>1</sup>

<sup>1</sup> School of Applied Physics, Faculty of Science and Technology, UKM, Bangi, 43600 Malaysia

<sup>2</sup> Materials Technology Programme, Faculty of Applied Sciences, UiTM, 40450 Shah Alam, Selangor Malaysia

<sup>3</sup> Applied Physics Programme, Faculty of Science and Technology, USIM, 71800 Nilai, Negeri Sembilan.

---

### Abstract

This study is conducted to evaluate the tensile properties of silicon carbide nanoparticles (SiCNP) and multiwalled carbon nanotubes (MWCNTs) filled toughened epoxy composites as a function of filler loading. The nanocomposites with different weight percentage of SiCNP and MWCNTs loading were fabricated by mechanical blending operation assisted with an ultrasonic cavitation technique. The loadings utilized were 0, 2, 4, and 6% of total composites weight. The result shows that the optimum filler loading of both systems were obtainable at 4% of SiCNP and MWCNTs of loadings. Composite with SiCNP filler achieved the highest value of tensile strength and Young's modulus at about 11% and 4%, respectively as compared to unfilled system. The enhancement pattern in MWCNTs nanocomposite systems were not significant as compared than SiCNP composite. The tensile strength and Young's modulus of MWCNTs composite were increased at only about 7% and 2%, respectively compared than unfilled system. The strain at break attribute for both filler system had shown reduction pattern at higher loading started from 2% loading and onwards. The variation in tensile properties were further supported by the tensile fracture morphologies and clearly shown that the filler-matrix played an important role in affecting the tensile behavior of nanocomposite produced.

© 2016 Published by Elsevier B.V. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>).

Peer-review under responsibility of School of Materials and Mineral Resources Engineering, Universiti Sains Malaysia

**Keywords:** Toughened epoxy composite; tensile properties; nanofiller

---

\* Corresponding author. Tel.: +6013-3519870; fax: +6-038-921-3777.

E-mail address: [suzanar@salam.uitm.edu.my](mailto:suzanar@salam.uitm.edu.my)

## 1. Introduction

Recently, the growing interest in the use of nanofiller in composite materials creates new innovations in many fields such as electronic devices, communication, defense and aerospace applications. Silicon carbide nanoparticles (SiCNP) and multiwall carbon nanotubes (MWCNTs) are considered to be the most two interesting nanofillers in the polymer matrix due to their outstanding characteristics. The usage of SiCNP has received great attention due to their advantages over the other nanofillers. Besides, SiCNP is among of the hardest materials that have high an oxidation and thermal resistance with excellent electrical and optical characteristics<sup>1-3</sup>. Higher demand on carbon nanotubes (CNTs) in various fields is due to superior characteristics such as lightweight materials and strong microwave absorption properties<sup>4</sup>. MWCNTs also known as stiffest materials with high tensile strength and modulus, therefore, the incorporation of this filler in epoxy is possible to improve mechanical properties of composite<sup>5</sup>. These inherent properties also make the nanofiller was extensively used for a high heat impact, radiation resistance, high chemical stability, strengthening, and enhanced super plasticity properties of materials<sup>6</sup>. However, according to Sun et al.<sup>7</sup>, silicon carbide has better properties and wide application prospect at higher temperature than other dielectric absorbers such as carbon nanotubes, pyrolytic carbon and carbon black.

The mechanical properties of composite are largely depended to the filler and matrix composition. The tensile strength of polymer nanocomposites is influenced by a weight fraction and modification made to nanoparticles<sup>8</sup>. The effects of nanoparticles addition on mechanical behavior of SiCNP reinforced epoxy composites had shown that at 0-10 weight percent of the loading caused reduction in tensile strength and Young's Modulus<sup>9</sup>. Higher loading of nanoparticles led to the agglomeration phenomena in matrices due to their small size and Van de Waals interaction forces between the particles which causing a poor dispersion and weak bonding between the matrix and nanoparticles. Thus, become a major factor had in strength reduction of the produced nanocomposites. In addition, the efficiency of MWCNTs addition in epoxy matrix profoundly caused deterioration to the mechanical properties due to similar aggregation of CNTs<sup>10</sup>. Moreover, another support from the TEM images observation of poor distribution of nanoclays in epoxy matrix caused deterioration in mechanical properties at higher loading filler<sup>11</sup>. In this study, the effects of filler loading to the tensile behavior of two dissimilar composite systems of SiCNP and MWCNT filled was evaluated and further compared.

## 2. Experimental

Commercial grade of Morcote BJC 39 epoxy resin were mixed with liquid epoxidized natural rubber (LENR) by mechanical stirrer for 1 hour at 1300 rpm. After that the SiCNP or MWCNTs was added into the mixture and stirred for 1 hour at the same speed assisted with sonication cavitations. Then, the curing agent was added at ratio of 1:3 of the resin and further mixed for another 15 minutes. The mixture was degassed in vacuum oven for 5 minutes at a room temperature in the vacuum oven to ensure the release of entrapped air and bubbles in the mixture. The mixture was then transferred to the mould and leveled by the roller until uniformly filled the entire mold cavity. Preheating step was then conducted at 80°C and after 1 hour, the molded samples were removed from the mold and trimmed for an excess resin removal. Finally, the samples went through a post curing process by further heating in an oven at 140°C for 3 hours.

Tensile properties were measured by using a Testometric Universal Testing Machine (UTM) with a crosshead speed of 5 mm/min and 500 kN of applied load. The nanocomposites samples were prepared into a dumbbell shape in accordance to the ASTM D 638 type I test specimen with gauge length of 70 mm. At least about five samples of each different filler loadings were tested. Later, an observation of tensile fractured surface was performed through the field emission scanning electron microscope (FESEM). The fractured surface was carefully coated by a thin film layer of gold using the sputter coated model Polaron to enhance the quality of FESEM images and to eliminate the charging effects due to non-conductive nature of the composites samples.

Download English Version:

<https://daneshyari.com/en/article/239818>

Download Persian Version:

<https://daneshyari.com/article/239818>

[Daneshyari.com](https://daneshyari.com)