



5th International Conference on Recent Advances in Materials, Minerals and Environment (RAMM) & 2nd International Postgraduate Conference on Materials, Mineral and Polymer (MAMIP), 4-6 August 2015

Influence of Kenaf (KNF) Loading on Processing Torque and Water Absorption Properties of KNF-Filled Linear Low-Density Polyethylene/Poly (vinyl alcohol) (LLDPE/PVA) Composites

Pang Ai Ling^a, Hanafi Ismail^{a,b,*}, Azhar Abu Bakar^a

^aSchool of Materials and Mineral Resources Engineering, Universiti Sains Malaysia (USM), Engineering Campus, Nibong Tebal, 14300, Penang, Malaysia

^bCluster for Polymer Composites (CPC), Science and Engineering Research Centre (SERC), Universiti Sains Malaysia (USM), Engineering Campus, Nibong Tebal, 14300, Penang, Malaysia

Abstract

The KNF-filled linear low-density polyethylene composites were prepared by using an internal mixer (Thermo Haake Polydrive) at 150°C and 50 rpm rotor speed. The composites were mixed with different KNF loading, i.e., 10, 20, 30 and 40 phr. The effects of KNF loading on processing torque and water absorption of the composites were investigated. The results indicated that stabilization torque and water absorption were increased with increasing KNF loading. Composites with higher KNF loading demonstrate higher equilibrium water absorption.

© 2016 The Authors. Published by Elsevier B.V. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>).

Peer-review under responsibility of School of Materials and Mineral Resources Engineering, Universiti Sains Malaysia

Keywords: LLDPE/PVA; Kenaf Loading; Composites

* Corresponding author. Tel.: 604-599 6113; fax: 604-594 1011.
E-mail address: ihanafi@usm.my

1. Introduction

The utilization of natural fibers (i.e., kenaf, hemp, jute, etc.) as reinforcement or fillers in polymer has been widely explored in the last few years^{1,2}. Kenaf fibers have found advantageous due to its short plantation cycle,

environmental friendly and being inexpensive^{3,4}. A few researchers claimed that mechanical properties of kenaf thermoplastic polyurethane has resulted in best tensile and flexural strength of kenaf reinforced thermoplastic polyurethane composites as reported by⁶. In order to expand the usage of natural fiber polymer composites, it is important to investigate their water resistance. This is due to large water intake by natural fiber polymer composites may result in dimensional changes, and hence deteriorating its mechanical properties⁷. In this study, kenaf fiber was used as filler and added into LLDPE/PVA blends. The effect of increasing kenaf loading on the processing torque and water absorption of KNF-filled LLDPE/PVA composites was studied.

1. Experimental

1.1. Materials

Linear low density polyethylene (LLDPE) was supplied by PT. Lotte Chemical Titan Nusantara, Indonesia with a melt flow rate of 1 g/10 min at 190°C and a density of 0.92 g/cm³. Polyvinyl alcohol (PVA), was supplied by Sigma-Aldrich (M) Sdn. Bhd., with a molecular weight of 89,000 to 98,000 g/mol and density of 1.269 g/cm³. Kenaf (KNF) was obtained from National Kenaf and Tobacco Board (LKTN), Kelantan, Malaysia. KNF was subjected to grinding process to yield average KNF particle size of 75µm.

1.2. Composites preparation

KNF were dried in vacuum oven at 80°C, 24 hours prior being used in the composites preparation. The weight ratio of LLDPE/PVA was maintained at 60:40 (by weight percent, wt. %), with different KNF loading (i.e. 0, 10, 20, 30, 40 phr). The melt compounding of a series of LLDPE/PVA/KNF composites were performed in an internal mixer (Thermo Haake Polydrive, Model R600/610) at temperature and rotor speed of 150°C and 50 rpm, respectively, for 10 min. The compounded samples were then compression molded at 150°C into 1 mm thickness sheet using an electrically heated hydraulic press (GoTech Testing Machine, Model KT-7014 A).

1.3. Water absorption

The water uptake test was carried out in accordance to ASTM D570. The specimens were first dried in an oven for 24 hours at 50°C until a constant weight was obtained. Weight difference after immersion was recorded by weighing them periodically on a Sartorius balance Model: BS224S, with a precision of 1 mg. The excess water on specimen surfaces was removed with tissue paper before weighing. The water uptake test was performed for 30 days and the percentage of water uptake was calculated using Equation (1),

$$W_t(\%) = \frac{W_2 - W_1}{W_1} \times 100 \quad (1)$$

Where W_t is the total water uptake by the specimen, and W_1 and W_2 are the weights of the specimen before and after immersion in distilled water respectively.

2. Results and discussion

2.1. Processing torque

Fig.1 illustrates the processing torque against time of KNF-filled LLDPE/PVA composites. The curves of processing torque for all the composites are of similar trend against time. Initially, the torque increased rapidly when LLDPE were loaded into the mixing chamber. LLDPE then undergo melting which resulted in lower torque value. After 2 min, once again the torque increased rapidly due to loading of PVA. The increment is due to the resistance exhibited by PVA in LLDPE. Ismail *et al.* 2010 also reported the similar finding⁸. Then, the torque

Download English Version:

<https://daneshyari.com/en/article/239858>

Download Persian Version:

<https://daneshyari.com/article/239858>

[Daneshyari.com](https://daneshyari.com)