



ORIGINAL ARTICLE

Mycosynthesis of silver nanoparticles bearing antibacterial activity



Pasha Azmath, Syed Baker, Devaraju Rakshith, Sreedharamurthy Satish *

Bionano Technological Laboratory, Department of Studies in Microbiology, University of Mysore, Manasagangotri, India

Received 4 November 2014; accepted 1 January 2015

Available online 21 January 2015

KEYWORDS

Mycosynthesis;
Nanoparticles;
Andrographis paniculata;
Colletotrichum sp.;
Antibacterial activity

Abstract Mycosynthesis of silver nanoparticles was achieved by endophytic *Colletotrichum* sp. ALF2-6 inhabiting *Andrographis paniculata*. Well dispersed nanoparticles were characterized using UV–Visible spectrometry with maximum absorption conferring at 420 nm. FTIR analysis revealed possible biomolecules reducing the metal salt and stabilization of nanoparticles. XRD analysis depicted the diffraction intensities exhibiting between 20 and 80 °C at 2theta angle thus conferring the crystalline nature of nanoparticles. Morphological characteristic using TEM revealed the polydispersity of nanoparticles with size ranging from 20 to 50 nm. Synthesized nanoparticles exhibited bactericidal activity against selected human pathogens. Nanoparticles mode of action was carried out to reveal DNA damage activity. Thus the present investigation reports facile fabrication of silver nanoparticles from endophytic fungi.

© 2015 The Authors. Production and hosting by Elsevier B.V. on behalf of King Saud University. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>).

1. Introduction

Nanotechnology is emerging field of science which involves synthesis and development of materials at nanoscale (Naveen et al., 2010). It has opened new avenues by intersecting with interdisciplinary field of science for innumerable applications (Morones et al., 2005). These nanomaterials are used in various fields such as electronic devices, sensor technology, signal enhancers, optical sensors, biomarkers, magnetic, catalysis, optical polarizability, electrical conductivity, antimicrobialac-

tivity and drug delivery to tumor cells (Nilsson et al., 2007; Duncan, 2011; Costa-Fernandez et al., 2006; Schrand et al., 2008; Naz et al., 2014; Shiraishi and Toshima, 2000; Ning et al., 2008; Sondi and Salopek-Sondi, 2004; Aliosmanoglu and Basaran, 2012; Syed et al., 2013). Hence nanoparticle research has gained tremendous interest especially use of silver nanoparticles has myriad applications in biomedical sector with large number of products already in market such as ointments, dressing materials and packaging materials (Sadowski et al., 2008). Silver nanoparticles are reported to bear antimicrobial property against array of pathogenic microorganisms. Mode of action of silver nanoparticles as per the scientific records suggests that silver nanoparticles have different mode of action for instance they are known to interact with the thiol groups of vital enzyme, cause pit on the cell wall and damage the DNA of the organism (Baker and Satish, 2012b).

In future decades much more applications of silver nanoparticles are expected to be reported but one of the major

* Corresponding author.

E-mail address: satish.micro@gmail.com (S. Satish).

Peer review under responsibility of King Saud University.



Production and hosting by Elsevier

constraint is the synthesis protocols of nanoparticles. Most popular and widely used conventional methods for the synthesis of nanoparticles are bound with various implications such as use of toxic chemicals and generation of high energy resulting in environmental pollution (Baker et al., 2013a). Owing to which eco-friendly process for nanoparticle synthesis has gained impuportance in recent years with large number of biological entities are constantly being explored for reduction of metal salts and synthesize nanoparticles with desire size and shape (Baker et al., 2013b). Use of microorganisms is known to have better advantage compared to plant species as microorganisms can be cultured and preserved for constant usage whereas use of plant species may pose a risk and imbalance to plant diversity especially the harvesting of endangered species. Among the microbial diversity encompasses the plethora of microorganisms called endophytes which have reported to be one of the untapped and rich sources of bioactive compounds bearing biological activities. Endophytes are of great potentials to secrete structurally diversified metabolites (Baker and Satish, 2012a). But one of the least studied areas in the field of endophytes is their evaluation for nanoparticle synthesis (Baker and Satish, 2012c). The interference of endophytes with nanoparticles is relatively new and is expected to have significant impact. Fungal endophytes are reported to secrete diverse group of biomolecules extracellularly which are capable of reducing metal salts at rapid scale under optimized conditions. One such endophyte is isolated from healthy leaf of *Andrographis paniculata* and employed for rapid synthesis of silver nanoparticles. The synthesized nanoparticles were evaluated for bactericidal activity against significant human pathogens. Mode of action of nanoparticles was determined with treatment of DNA with silver nanoparticles. Thus the study highlights the mycosynthesis of silver nanoparticles bearing bactericidal activity using *Colletotrichum* sp. ALF2-6 and the results obtained are promising enough to envision the emerging role of endophytes for facile reduction of metal ions.

2. Materials and methods

2.1. Sample collection and isolation of endophytes

Healthy leaves of *A. paniculata* were collected from southern part of India. The samples were thoroughly washed in running tap water followed by sterile distilled water to remove adhered soil particles. Samples were excised into small segments (0.4–0.5 cm) using sterile scalpel and segments were subjected to surface sterilization by sequential steps as followed by protocol of Rakshith et al. (2013). Segments were placed on to the surface of water agar media amended with chloramphenicol (150 mg/L) and incubated at 26 °C in an alternate cycle of 12 h dark and 12 h light for 3 weeks. Colonies emerging from surface sterilized plant segments were subcultured until further use.

2.2. Optimization and mycosynthesis of silver nanoparticles

Fermented cell free extract of *Colletotrichum* sp. ALF2-6 was treated with 1 mM of silver nitrate and incubated at different temperatures ranging from 30 to 80 °C and pH of the reaction mixture was varied from acidic to alkaline. Samples were monitored periodically for the synthesis of nanoparticles with the aid of UV–Visible spectrophotometer operating at a resolution of 1 nm (Baker et al., 2014).

2.3. Characterization of mycosynthesized silver nanoparticles

The X-ray Diffraction (XRD) patterns were obtained on desktop X-ray diffractometer operating at 30 kV and at a current of 15 mA with Cu radiation ($k = 1.5404 \text{ \AA}$). The diffracted intensities were recorded from 0° to 80° of 2θ angles. X-ray photoelectron spectra were recorded Rigaku miniflex 2 instrument. FTIR spectra of silver nanoparticle solution were recorded on Perkin Elmer spectrum one B in diffuse reflectance (DRS) mode at a resolution of 2 cm^{-1} . Transmission electron microscopy (TEM) analysis of silver nanoparticles was prepared on carbon-coated copper TEM grids. TEM scan was performed using a TECHNAI-T12 JEOL JEM-2100 Transmission electron microscope operated at a voltage of 120 kV with Bioten objective lens. Subsequently, the particle size was ascertained using a Gatan ccd Camera (Baker et al., 2014).

2.4. Phenotypic and genotypic characterization of the fungal endophyte

Phenotypic characterization was carried out by mounting part of the viable culture and observed under microscope to determine the morphological characteristics (Naveen et al., 2010). Genotypic characterization of fungus was carried out using DNA isolation kit (Hi pura, HiMedia, Mumbai, India) according to manufacturer's instruction. In brief, isolation of fungal genomic DNA and 18S rDNA region was amplified, the PCR product was bi-directionally sequenced using forward (ITS1) and reverse (ITS4) primers which produced an expected amplicon size of ~500–600 base pairs. Sequencing results were processed using Bio Edit software (Hall, 1999). Processed sequences were subjected to BLAST tool at NCBI to assign putative identity, designation of operational taxonomic units based on sequence similarity measures and phylogenetic inference. Partial nucleotide sequences were deposited in NCBI GenBank to procure accession number. Neighbor joining analysis of endophyte mediating silver nanoparticle synthesis and close relatives retrieved from Genbank using Clustal W and Bio Edit softwares (Hall, 1999; Thompson et al., 1997). Alignments were manually edited where necessary and phylogenetic analyses were performed to assess phylogenetic affiliation using Molecular Evolutionary Genetics Analysis software MEGA6 (Tamura et al., 2011).

2.5. Bactericidal activity of mycosynthesized silver nanoparticles

Bactericidal activity of mycosynthesized silver nanoparticles was evaluated against *Escherichia coli* (MTCC 7410), *Salmonella typhi* (MTCC 733), *Bacillus subtilis* (MTCC 121) and *Staphylococcus aureus* (MTCC 7443) and all test pathogens were procured from Microbial Type Culture Collection, Chandigarh, India. Inoculum of test pathogens was prepared to obtain 5×10^5 CFU (Colony forming unit) and bactericidal activity was determined via CFU assay. In brief, Mueller–Hinton agar plates were supplemented with silver nanoparticles with different concentrations (25, 50, 75 and 100 µg/mL). Test inoculum was smeared onto the plates and incubated for 24 h at 37 °C and one control was maintained without addition of silver nanoparticles. The colonies were counted and validated with the control plate to determine the effect of nanoparticles (Sondi and Salopek-Sondi, 2004). Minimal Inhibitory

Download English Version:

<https://daneshyari.com/en/article/2509271>

Download Persian Version:

<https://daneshyari.com/article/2509271>

[Daneshyari.com](https://daneshyari.com)