

Color Changes of Teeth after Treatment with Various Mineral Trioxide Aggregate–based Materials: An *Ex Vivo* Study

Shin-Hong Kang, DDS, MS,* Young-Seob Shin, DDS,* Hyo-Seol Lee, DDS, PhD,*
Seong-Ob Kim, DDS, PhD,*[‡] Yooseok Shin, DDS, PhD,[†] Il-Young Jung, DDS, PhD,^{†‡}
and Je Seon Song, DDS, PhD*[‡]

Abstract

Introduction: Mineral trioxide aggregate (MTA) materials have been used for many years as a pulp therapy material. The most widely used product, ProRoot MTA (Dentsply, Tulsa, OK), has a major drawback in that it causes tooth discoloration. Alternatives have recently been developed such as ENDOCEM Zr (MARUCHI, Wonju, Korea) and RetroMTA (BioMTA, Seoul, Korea). The purpose of this study was to compare the discoloration of these various MTA-based materials. **Methods:** Discoloration of discs prepared from 4 different MTA-based materials (ProRoot MTA, MTA Angelus [Angelus, Londrina, PR, Brazil], ENDOCEM Zr, and RetroMTA) were observed at 15 and 30 minutes after exposure to light at an intensity of 1000 mW/cm². In a tooth model, 12 premolars were used per each group to retrofill the pulp chamber with MTA-based materials. The degree of discoloration was measured over a 16-week period using a digital spectrophotometer. **Results:** Distinct color changes were observed for discs made from ProRoot MTA and MTA Angelus, but no clear change was observed for those made from either ENDOCEM Zr or RetroMTA. In the tooth model, more distinct, time-dependent color changes were observed for teeth filled with ProRoot MTA and MTA Angelus than for those filled with ENDOCEM Zr and RetroMTA. **Conclusions:** Less discoloration was observed with ENDOCEM Zr and RetroMTA (which contain zirconium oxide) than with ProRoot MTA and MTA Angelus (which contain bismuth oxide) in both of the test models used. (*J Endod* 2015;41:737–741)

Key Words

Bismuth oxide, discoloration, ENDOCEM Zr, mineral trioxide aggregate, RetroMTA, zirconium oxide

Mineral trioxide aggregate (MTA) was approved as a root canal treatment material by the US Food and Drug Administration in 1998; since then, it has been used in various areas of the root canal treatment process, such as apexogenesis, pulpotomy, direct pulp capping, and root perforation repair, because of its excellent biocompatibility and sealing ability (1–5). There have been many researches and clinical case reports on the use of MTA or MTA-like materials as pulp treatment materials in deciduous teeth and immature permanent teeth (6–8).

Despite its reported advantages, the use of MTA has the following drawbacks: it is difficult to handle, expensive, difficult to remove, and discolors over time (9). Of major importance esthetically, the discoloration that occurs produces results that are not esthetically good, which is particularly problematic when direct pulp capping or pulpotomy are required in the anterior jaw area (10, 11).

The first MTA material to be developed for use in teeth, gray MTA (GMTA), was a dark color and was found to cause tooth discoloration; therefore, white MTA (WMTA) was developed, which had similar clinical properties to GMTA but produced more esthetically pleasing results (12). The difference between WMTA and GMTA lies in their respective contents of metal oxides (eg, iron, aluminum, and magnesium oxides), which are the main cause of discoloration (13). However, WMTA also causes some tooth discoloration because it still contains various metal oxides, although the content is low, together with bismuth oxide, which was added to improve the radiopacity of the material (10, 11, 14). The degree of discoloration that occurs depends on the content of the components of metals such as bismuth, iron, aluminum, and magnesium oxides. Therefore, within a range that does not change the properties of MTA, the content of bismuth oxide could be reduced to minimize any color change. ENDOCEM Zr (MARUCHI, Wonju, Korea) and RetroMTA (BioMTA, Seoul, Korea) are products that have recently become available commercially in which bismuth oxide has been replaced by zirconium oxide as an alternative radiopacifier. Although the manufacturers claim that this product does not cause discoloration either *in vivo* or *ex vivo*, as yet there have been no studies to confirm this. Based on this discussion, we established the following null hypothesis: ENDOCEM Zr and RetroMTA (which contain zirconium oxide) show less discoloration than MTA Angelus (Angelus, Londrina, PR, Brazil) and ProRoot MTA (Dentsply, Tulsa, OK) (which contain bismuth oxide) in an *ex vivo* model.

Therefore, the aim of the present study was to compare the degree of tooth discoloration that occurs over time in specimens and extracted teeth filled with ENDOCEM Zr, RetroMTA, MTA Angelus, and ProRoot MTA.

From the Departments of *Pediatric Dentistry and †Conservative Dentistry and ‡Oral Science Research Center, College of Dentistry, Yonsei University, Seoul, Republic of Korea.

Address requests for reprints to Dr Je Seon Song, Department of Pediatric Dentistry, Yonsei University College of Dentistry, 250 Seongsanno, Seodaemun-gu, Seoul 120-752, Korea. E-mail address: songjs@yuhs.ac
0099-2399/\$ - see front matter

Copyright © 2015 American Association of Endodontists.
<http://dx.doi.org/10.1016/j.joen.2015.01.019>

Materials and Methods

Disc Discoloration Experiment

Discs were fabricated by mixing distilled water with ProRoot MTA, MTA Angelus, ENDOCEM Zr, or RetroMTA according to the manufacturer’s recommendations using a rubber mold (8 mm × 1 mm). In addition, bismuth oxide powder (Duksan, Ansan, Korea) and zirconium oxide powder (Sigma-Aldrich, St Louis, MO) were put into 4-well plates and then soaked for 15 minutes in glycerin (Duksan). The disc and bismuth/zirconium specimens were then irradiated with light for 15 minutes or 30 minutes using a VALO light irradiator (Ultradent, South Jordan, UT) in standard power mode (1000 mW/cm²). The specifications of the ProRoot MTA, MTA Angelus, ENDOCEM Zr, and RetroMTA used in the present study are given in Table 1.

Preparation of Extracted Teeth for the Discoloration Experiment

Sixty premolars (30 maxillary premolars and 30 mandibular premolars) that had been extracted for orthodontic purposes from 20 people aged 10–29 years (11 males and 9 females) were used. Teeth with dental abnormalities, restorations, or more than moderate dental caries were excluded. The experiment was performed under guidelines approved by the Institutional Review Board of the Dental Hospital, Yonsei University. Written, informed consent for their teeth to be used was obtained from all of the subjects and their parents (form # 2-2013-0036).

After cutting the teeth horizontally about 2 mm below the cemento-enamel junction, the pulp tissue was removed using a barbed broach (Mani, Tokyo, Japan), and any organic materials on the surface of the teeth were physically removed by curettage; persistent organic material was removed by soaking the teeth for 10 minutes in 2.5% sodium hypochlorite solution (Duksan). The teeth were then washed several times with normal saline and stored at 4°C until required for the experiment.

The teeth were assigned to 1 of 5 groups (*n* = 12 teeth per group) named according to the MTA product that would be used to fill their pulp chamber: control (no MTA material), ProRoot MTA, MTA Angelus, ENDOCEM Zr, and RetroMTA. The materials were prepared as instructed by the manufacturer and then used to retrofill the teeth to the level of the cemento-enamel junction in the pulp chamber. After the early setting phase, the lower area was sealed with light-cured compomer base (Ionosit-Baseliner; DMG, Hamburg, Germany). In the control group, the pulp tissue was removed from the teeth, which were then only sealed with Ionosit-Baseliner compomer.

Molds were fabricated for each tooth using rubber impression material (Aquasil Soft Putty, Dentsply). Holes with diameters of about 6 mm were created in the molds using a biopsy punch (SFM Medical Devices, Wächtersbach, Germany) so that the extent of discoloration could be measured at the same site. The hole was located so that it revealed an area between the midbuccal third and cervical third to facilitate observation of any MTA-induced internal discoloration (Supplemental Figure S1 is available online at www.jendodon.com).

Measurement of Tooth Color

All of the specimens were put into 12-well plates (BD Falcon, Franklin Lakes, NJ) and stored next to a window in artificial saliva (Tariba; Hanlim Pharm, Seoul, Korea), which was changed every 2 weeks. The tooth color was measured using the VITA Easyshade Compact device (Vita Zahnfabrik, Bad Sackingen, Germany) at the following time points: 0 (baseline), 1, 2, 4, 8, 12, and 16 weeks. The color measurement was made in triplicate for all experimental groups using the *L*a*b** value, where *L** is the light intensity, *a** is the red-green parameter, and *b** is the yellow-blue parameter. Using these *L*a*b** values, the differences between the color measured at the initial time point (time 0) and those measured at the various time points (ΔE) were calculated as follows:

$$\Delta E = [(\Delta L)^2 + (\Delta a)^2 + (\Delta b)^2]^{1/2}$$

where ΔL , Δa , and Δb are the changes in *L**, *a**, and *b**, respectively, between the initial time point and the next time point being compared.

Statistical Analysis

All statistical analyses for differences in color change among the products between the initial time point and the 6 other time points after the initiation of light treatment were conducted using SPSS Statistics (versions 21.0; SPSS IBM, Armonk, NY). One-way analysis of variance (*P* < .05) was performed, and the Scheffé test (Bonferroni correction, *P* < .01) was used as a post hoc test.

Results

Disc Discoloration Experiment

After 15 and 30 minutes of light exposure, the discs made from MTA Angelus and ProRoot MTA discs were darkly discolored, whereas there was no color change for the RetroMTA and ENDOCEM Zr discs. The discoloration was darker for the ProRoot MTA disc compared with the MTA Angelus disc. In addition, although there was a clear color

TABLE 1. Mineral Trioxide Aggregate–based Materials Used in the Study

Material	Manufacturer	Ingredients
ProRoot MTA	Dentsply, Tulsa, OK	Portland cement 75% Calcium sulfate dehydrate (gypsum) 5% Bismuth oxide 20%
MTA Angelus	Angelus, Londrina, PR, Brazil	Calcium oxide 55%–60% Silicon dioxide 17%–20% Aluminum oxide 2%–4% Bismuth oxide 18%–22%
ENDOCEM Zr	MARUCHI, Wonju, Korea	Calcium oxide 27%–37% Silicon dioxide 7%–11% Aluminum oxide 3%–5% MgO, Fe ₂ O ₃ 3%–5%
RetroMTA	BioMTA, Korea	Zirconium dioxide 43%–46% Calcium carbonate 60%–80% Silicon dioxide 5%–15% Aluminium oxide 5%–10% Calcium zirconia complex 20%–30%

Download English Version:

<https://daneshyari.com/en/article/3150302>

Download Persian Version:

<https://daneshyari.com/article/3150302>

[Daneshyari.com](https://daneshyari.com)