



Wood species affects laboratory colonization rates of *Chlorociboria* sp.

Sara C. Robinson*, Peter E. Laks

Michigan Technological University, UJ Noblet Forestry Building, 1400 Townsend Dr., Houghton, MI 49931, USA

ARTICLE INFO

Article history:

Received 12 January 2010

Received in revised form

4 March 2010

Accepted 23 March 2010

Available online 22 April 2010

Keywords:

Acer saccharum

Chlorociboria sp.

Populus spp.

Spalting

Xylindein

ABSTRACT

This research attempted to determine conditions and wood species required to maximize xylindein production from a *Chlorociboria* sp. under laboratory conditions for use in induced spalting. A pure culture of a *Chlorociboria* species was isolated from fruiting bodies and grown on 2% malt extract agar. The colonies reached a maximum diameter of 18 mm in four weeks, although the blue-green xylindein pigment continued to diffuse through the culture media for at least eight months. In vermiculite jar tests, this *Chlorociboria* isolate colonized *Populus tremuloides* more heavily than *Acer saccharum* or *Betula alleghaniensis*, and did not colonize *Tilia americana* at all. Pre-inoculation of test blocks with white rot fungi did not significantly affect xylindein production, regardless of wood species.

© 2010 Elsevier Ltd. All rights reserved.

1. Introduction

Chlorociboria spp. are green stain ascomycete fungi found throughout North America (Dixon, 1975). They produce small, blue-green disc-like apothecia on hardwood logs, although the fruiting bodies can be difficult to locate. Wood stained by *Chlorociboria* is abundant and can be found in many hardwood stands, commonly on wood that has already been colonized by white rot (Johnston and Park, 2005).

Only two species of *Chlorociboria* occur in North America: *Chlorociboria aeruginascens* (Nyl.) Kanouse and *Chlorociboria aeruginosa* (Oeder) Seaver. The species are primarily differentiated by spore size, with the ascospores of *C. aeruginascens* ranging from 5 to 7 μm and those of *C. aeruginosa* ranging from 8 to 14 μm (Dixon, 1975). In the literature, differences in growth rate and pigmentation between the two species are not noted, and it appears that the species are essentially identical in most aspects. As such, green stained wood is often identified as being colonized by *Chlorociboria* spp., and not by a specific species.

The unique blue-green pigment produced by *Chlorociboria* spp. is xylindein, which has been extensively researched (Blackburn et al., 1965; Edwards and Kale, 1965; Giles et al., 1979, 1990; Saikawa et al., 2000). Although produced within the hyphae, xylindein often diffuses into the surrounding substrate (Berthet, 1964). This diffusion leads to a greater amount of colored wood per colonization area

as compared to fungi that do not produce diffusible pigments. Hence, the diffusion of xylindein can produce a relatively large volume of pigmented substrate without extensive colonization by the fungus. Despite the research by Berthet, however, this diffusion has not been confirmed by microscopy.

Little research has been conducted on laboratory growth of either of the North American *Chlorociboria* species. *C. aeruginascens* appears to be slightly more common than *C. aeruginosa*, grows slowly on culture plates, and does not consistently produce blue-green pigment (Fenwick, 1993; Dixon, 1975). Dixon notes that *C. aeruginascens* pigment typically diffuses through culture medium well beyond the colony diameter (1975). There is currently no published information on the growth rate or xylindein diffusion ability of *C. aeruginosa*. Although both species have been isolated from numerous hardwood and softwood species, the decay ability, wood species preference, and growth rate of North American *Chlorociboria* spp. on wood is currently unknown.

Wood colonized by *Chlorociboria* sp. has been utilized for artistic purposes since the 15th century, when it was used by intarsia artists for inlay pieces that required blue-green tones, such as plants and water (Blanchette et al., 1992). Sampling of stained pieces from intarsia works found that the green-stained wood pieces were all from the *Populus* species. The stained wood is still utilized today for artistic purposes; in fact the vernacular term 'green oak' has evolved due to the predominant growth of *Chlorociboria* sp. on oak (*Quercus* spp.) in some regions (Dennis, 1956).

The green stain of *Chlorociboria* is a type of spalting. Spalting is defined as any coloration of wood due to fungal colonization

* Corresponding author. Tel.: +1 309 530 3924; fax: +1 906 487 2915.

E-mail addresses: scrobins@mtu.edu (S.C. Robinson), plaks@mtu.edu (P.E. Laks).

(Robinson et al., 2007). The three types of spalting include bleaching, caused by the removal of lignin and other colored wood constituents; zone lines, caused by intra- and inter-fungal antagonism; and pigmentation, caused by a large mass of pigmented fungal hyphae concentrated in one area and/or the diffusion of that pigment into the surrounding wood. The Ohio DNR notes that maple (*Acer* spp.), birch (*Betula* spp.), and beech (*Fagus* spp.) are the three most commonly spalted woods, with spalted oak (*Quercus* spp.) rarely occurring due to the high extractive content of the wood (Ohio DNR, 2009).

Research into controlled spalting for commercial and artistic purposes has expanded within the past five years. Most research has focused on zone line formation by white rot fungi, primarily because these fungi are capable of both forming zone lines and causing bleaching (Phillips, 1987; Robinson et al., 2007). However, pigment fungi have the potential to produce a higher quality of spalted wood, as most do not consume structural wood components. Recent studies have begun investigating the use of pigment fungi for spalting applications (Robinson et al., 2009a, 2009b), although results from these studies have not shown that fungal pigments readily penetrate into wood.

This research attempts to expand current knowledge of North American *Chlorociboria* species and investigate possible stimulatory mechanisms by which these fungi might be utilized in spalting applications.

2. Materials and methods

Fruiting bodies of *Chlorociboria* sp. were obtained in September 2008 from a *Populus* sp. log in a mixed hardwood forest in Keweenaw County, MI. The culture was grown on 2% malt extract agar and maintained at room temperature (22 °C). The culture was transferred to fresh agar plates every three months to maintain active growth.

Kiln-dried wood from four tree species was chosen for inoculation: sugar maple (*Acer saccharum* Marsh.) (12% SG = 0.66, 12% MC density = 710 kg/m⁻³), basswood (*Tilia americana* L.) (12% SG = 0.41, 12% MC density = 430 kg/m⁻³), paper birch (*Betula alleghaniensis* Britt.) (12% SG = 0.59, 12% MC density = 636 kg/m⁻³), and trembling aspen (*Populus tremuloides* Michx.) (12% SG = 0.45, 12% MC density = 483 kg/m⁻³). Sugar maple and yellow birch were chosen due to the prevalence of spalting occurring in these species (Robinson et al., 2007; Ohio DNR, 2009). Basswood was chosen due to its popularity among woodworkers as a low-density, easy-carving wood, and trembling aspen was chosen due to the test culture having been isolated from a *Populus* spp. wood. Although xylindrin is commonly found in oak wood, this species was not utilized in this experiment due to its high extractive content and therefore its lack of potential to be utilized with any other spalting fungus.

Fifteen 14 mm cubes of each wood type were oven dried at 40 °C for 24 h and weighed. Blocks were steam sterilized for 30 min and then placed in vermiculite jars (4 × 4 × 12 cm flint jars), which were prepared as described in Robinson et al. (2009b). Jars were autoclaved for 30 min prior to block placement. The blocks were placed in the jars so that the vermiculite just covered the surface of the block. A strip of inoculum roughly 2 × 2 cm was placed on the top of the block and then covered with an aspen feeder strip measuring approximately 3 × 28 × 34 mm. A total of 45 jars were prepared, and each jar contained only one block.

Fifteen blocks were utilized per wood species. Five were pre-inoculated with *Trametes versicolor*, 5 with *Xylaria polymorpha*, and 5 were inoculated directly with *Chlorociboria* sp.

2.1. Pre-inoculation

Five blocks from each wood species were pre-inoculated with *T. versicolor* (L.) Lloyd SR003 and an additional five blocks from each

were pre-inoculated with *X. polymorpha* (Pers.) Grev. SR001. *T. versicolor* was isolated from an *A. saccharum* log in Houghton Co., MI. *X. polymorpha* was isolated from an *A. saccharum* log in Baraga Co., MI. The pre-inoculated jars were incubated for eight weeks in a humidity and temperature-controlled room (27 °C ± 2 °C, 80% ± 5% relative humidity). After incubation, the jars were autoclaved for 35 min, allowed to cool, and then reinoculated with the *Chlorociboria* isolate. Jars that were not pre-inoculated were inoculated with *Chlorociboria* along with sterilized pre-inoculation jars. All 45 jars were then incubated for 24 weeks under the same conditions outlined above.

2.2. Analysis

After incubation, the blocks were removed from the jars, washed to remove any adhering mycelium and vermiculite, dried overnight, and then weighed to determine weight loss. After drying, the transverse face with the most green stain was scanned at 2400 dpi using an Epson Perfection V100 photo scanner. Blocks were then cut in half to expose a radial face, then scanned again for internal spalting. Spalting amounts (amount of visible pigmentation per block) were analyzed using the procedure outlined in Robinson et al. (2009a). All data were analyzed using a two-way analysis of variance (ANOVA) with wood species and pre-treatment as independent variables. If differences were found, a Tukey HSD was run to determine the location of the significant difference. Percentage data were transformed using arcsine square root to meet ANOVA assumptions of error term variance and normality. All statistical procedures were performed using SAS, version 9.2 of the SAS (2009) system for Windows.

3. Results

Growth of the *Chlorociboria* isolate on agar plates was slow, with colonies never exceeding 18 mm in diameter regardless of incubation time or plate size (Fig. 1). Xylindrin diffusion into the culture media began after approximately four weeks of incubation, and continued up to four months, with colony size not increasing after four weeks of incubation. The cultures never completely covered the surface of the plate, however xylindrin diffused throughout an entire 60 × 15 mm plate by eight months.

Of the wood species tested, the *Chlorociboria* isolate colonized all but basswood (Table 1), with significantly more colonization on aspen than on any other wood species ($\alpha = 0.05$). No weight loss occurred with any wood species. Birch was lightly colonized with only three of the fifteen blocks showing any amount of external green stain – one from the *X. polymorpha* pre-treatment group (3.5% green surface area) and two from the control group (3.5% and 7%). Of those three blocks, only the one from the pre-treatment group had internal green stain (5%).

The sugar maple blocks as a group were colonized moderately well by the *Chlorociboria* isolate. The control group and *T. versicolor* pre-treatment group had almost the same amount of external green stain (around 2.5% ± 4.75% SD). External green stain occurred much more frequently in the *X. polymorpha* pretreated blocks, which had an average of 6.79 ± 4.45% surface area covered by green stain. However, the green stain did not penetrate internally into the blocks.

The *Chlorociboria* isolate was most successful at colonizing the aspen blocks (Fig. 2, Fig. 3). Blocks pretreated with *T. versicolor* were most heavily stained (17.98 ± 15.01% SD external green and 8.34 ± 10.66% SD internal green). There was more external green stain on the control blocks than the *X. polymorpha* pre-treatment blocks, and of the two, only the control blocks exhibited any internal green stain. None of the pre-treatment results were statistically significant.

Download English Version:

<https://daneshyari.com/en/article/4365570>

Download Persian Version:

<https://daneshyari.com/article/4365570>

[Daneshyari.com](https://daneshyari.com)