Engineering 3 (2017) 130-135

Contents lists available at ScienceDirect

Engineering

journal homepage: www.elsevier.com/locate/eng



Research Medical Instrumentation—Article

Quality Monitoring of Porous Zein Scaffolds: A Novel Biomaterial Yue Zhang, Wei-Ying Li, Run Lan, Jin-Ye Wang *

School of Biomedical Engineering, Shanghai Jiao Tong University, Shanghai 200240, China

ARTICLE INFO

Article history: Received 30 June 2016 Revised 15 November 2016 Accepted 13 December 2016 Available online 20 January 2017

Keywords: Zein Amino acid analysis SDS-PAGE Gamma-ray sterilization MTT assay CCK-8 assay

ABSTRACT

Our previous studies have shown that zein has good biocompatibility and good mechanical properties. The first product from a porous scaffold of zein, a resorbable bone substitute, has passed the biological evaluation of medical devices (ISO 10993) by the China Food and Drug Administration. However, Class III medical devices need quality monitoring before being placed on the market, and such monitoring includes quality control of raw materials, choice of sterilization method, and evaluation of biocompatibility. In this paper, we investigated four sources of zein through amino acid analysis (AAA) and sodium dodecyl sulfate polyacrylamide gel electrophoresis (SDS-PAGE) in order to monitor the composition and purity, and control the quality of raw materials. We studied the effect of three kinds of sterilization method on a porous zein scaffold by SDS-PAGE. We also compared the changes in SDS-PAGE patterns when irradiated with different doses of gamma radiation. We found that polymerization or breakage did not occur on peptide chains of zein during gamma-ray (γ -ray) sterilization in the range of 20–30 kGy, which suggested that γ -ray sterilization is suitable for porous zein scaffolds. Regarding cell compatibility, we found a difference between using a 3-(4,5-dimethylthiazol-2-yl)-2,5-diphenyl tetrazolium bromide (MTT) assay and a cell-counting kit-8 (CCK-8) assay to assess cell proliferation on zein film, and concluded that the CCK-8 assay is more suitable, due to its low background optical density.

© 2017 THE AUTHORS. Published by Elsevier LTD on behalf of the Chinese Academy of Engineering and Higher Education Press Limited Company. This is an open access article under the CC BY-NC-ND license (http://creativecommons.org/licenses/by-nc-nd/4.0/).

1. Introduction

Zein is one of the major storage proteins of corn, and is the main byproduct in the corn-processing industry [1]. Its unique hydrophobicity causes researchers to study it for possible applications beyond the food industry [2]. Our group is the first to study zein as a biomaterial in tissue engineering, and we have proved its good biocompatibility and mechanical properties. The first product from a porous scaffold of zein may be used as a bone substitute [3–6]. As a Class III medical device, quality monitoring for raw materials, a suitable sterilization method, and biocompatibility are required.

Firstly, the quality of the raw materials must be stable and controllable. We found that zein purchased from different sources had a different appearance, affecting its scaffold shaping and mechanical properties; this prompted us to investigate the differences in zein from different sources. Sterilization process control is important for the quality management system of sterile medical device manufacturers. The control level of the sterilization directly affects the quality and safety of the sterile medical devices. The most traditional method of sterilization for manufacturers is ethylene oxide sterilization. However, this method may cause the problem of ethylene oxide residue in the porous scaffolds [7,8]. Therefore, we investigated other traditional methods such as moist-heat sterilization, dry-heat sterilization, and gamma-ray (γ -ray) sterilization. However, these methods may also be problematic for the structural stability of zein because heat and pressure may influence the structure of zein [9]. For example, the use of gamma radiation involves a great deal of energy, which may cause molecule ionization [10].

A traditional way to assess the proliferation of cells is a 3-(4,5dimethylthiazol-2-yl)-2,5-diphenyl tetrazolium bromide (MTT) assay [11,12], a method that we have applied in our previous work [3–6].

* Corresponding author.

http://dx.doi.org/10.1016/J.ENG.2017.01.001



E-mail address: jinyewang@sjtu.edu.cn

^{2095-8099/© 2017} THE AUTHORS. Published by Elsevier LTD on behalf of the Chinese Academy of Engineering and Higher Education Press Limited Company. This is an open access article under the CC BY-NC-ND license (http://creativecommons.org/licenses/by-nc-nd/4.0/).

Recently, we found that the background optical density (OD) of zein scaffolds was significantly high in MTT assays, which may affect the evaluation of data [13,14]. Therefore, we tried another method, a cell-counting kit-8 (CCK-8) assay [15], and compared these two methods in the evaluation of cell proliferation on zein film. We also considered possible factors causing a high background OD of zein in the MTT assay.

2. Materials and methods

2.1. Amino acid analysis, sodium dodecyl sulfate polyacrylamide gel electrophoresis, and microscopy characterization

Zein 1 was purchased from Kobayashi Perfumery Co., Ltd. (Japan), zein 2 (260-01283) and zein 3 (261-00015) were both purchased from Wako Pure Chemical Industries, Ltd. (Japan), and zein 4 (in sheet form) was purchased from Wujiang Bache Pharmaceutic Adjuvant Co. (China). We obtained the zein 4 powders by grinding sheets of zein 4 using a grinder (Q-100A2, Shanghai Bingdu Electric Co., Ltd., China) and then sifting. All were dispersed in 6 mol·L⁻¹ HCl with a ratio of 1:6 (g·mL⁻¹). The mixture was kept in an oil bath at 110 °C for 22 h. After acidolysis, the mixture was first rotary evaporated to concentrate it, and then lyophilized (FreeZone 4.5, Labconco, USA) to obtain the powder. The powder was dissolved in citric acid-sodium citrate buffer (pH = 2.2) and analyzed using a High-Speed Amino Acid Analyzer (L-8900, Hitachi, Japan) [16].

Samples of the four sources of zein were dissolved in 75 vt% ethanol solution at a concentration of 1 mg·mL⁻¹. Next, 20 µL of the sample solution was mixed with 20 µL of the loading buffer, and the mixture was heated in a water bath at 90 °C for 15 min. The loading buffer was made of 2 mL glycerol, 2 mL 10 wt% sodium dodecyl sulfate (SDS), 1 mL 2-mercaptoethanol, 0.5 mL 0.1% bromophenol blue, and 0.625 mL stacking gel buffer. Denaturing gel electrophoresis was carried out with a vertical slab gel apparatus (Bio-Rad, USA). The gel was made of a stacking gel of 5% and a resolving gel of 12% acrylamide concentration. It was run at room temperature at 110 V for 30 min and then at 150 V for about 1 h, using a running buffer made of 3.05 g of Tris base, 14.4 g of glycine, and 1 g of SDS dissolved in 1 L of Milli-Q water. The bands were visualized by Coomassie blue R250 staining [17].

The micro-morphology of the zein powders was investigated using scanning electron microscopy (SEM) (S-3400N, Hitachi, Japan) and fluorescence microscopy (IX71, Olympus, Japan) with an optical filter (U-MSWB2, Olympus, Japan) to produce the excitation light.

2.2. Porous zein scaffolds: Fabrication and sterilization

Zein 1 was mixed with sodium chloride (particle sizes from 0.3 mm to 0.425 mm) at a mass ratio of 1:1.5, and the mixture was molded into 3D scaffolds using a stainless steel mold (ϕ = 1.75 mm) at 0.1 MPa for 2 min on both sides. Next, the scaffolds were leached in a water bath at 55 °C for 30 min, cut to a cylindrical rod with a diameter of 2 mm and a height of 4 mm, and lyophilized for 6 h [4].

 γ -ray sterilization was performed by keeping porous zein scaffolds under 20 kGy, 25 kGy, and 30 kGy [18]. The zein powder and the porous zein scaffolds were monitored by sodium dodecyl sulfate polyacrylamide gel electrophoresis (SDS-PAGE) before and after sterilization.

Dry-heat sterilization was performed by keeping the zein powder in an electro-thermostatic blast oven (DHG-9053A, Shanghai Jing Hong Laboratory Instrument Co., Ltd., China) at 160 °C for 3 h. Moist-heat sterilization was performed by keeping the zein powder in an autoclave sterilizer (HVE-50, Hirayama, Japan) at 121 °C for 20 min. The zein powders were monitored by SDS-PAGE before and after sterilization.

2.3. Cell culture and proliferation

L929 cells (Type Culture Collection of the Chinese Academy of Sciences, China) were used in cell studies and cultured in GIBCO[®] Dulbecco's Modified Eagle Medium (DMEM) (Life Technologies Co., USA) supplemented with 10% newborn calf serum (Shanghai Yuanmu Biological Technology Co., Ltd., China) and antibiotics (100 U·mL⁻¹ penicillin and 100 µg·mL⁻¹ streptomycin) (Sinopharm Chemical Reagent Co., Ltd., China) in a 37 °C 5% CO₂ incubator (NU-4750E, NuAire, Ltd., USA).

Zein film slides were made by coating 10 μ L of zein 1 glacial acetic acid solution at a concentration of 0.1 g·mL⁻¹ on a glass slide of 8 mm in diameter. Before cell seeding, all slides were sterilized at 160 °C for 3 h, and then immersed in culture medium for 2 h in 48-well plates. L929 cells were seeded at a density of 2 × 10⁴ mL⁻¹ on both glass slides and zein film slides, and 500 μ L of the cell suspension was added to each test well, while 500 μ L of the culture medium was added to each background well. The plates were incubated for 6 d.

2.4. MTT and CCK-8 assays

The proliferation of L929 cells on glass slides and zein film slides was assessed using an MTT assay and a CCK-8 assay. Before assessment, the solution in each test or background well was replaced with 500 µL of culture medium. Then 50 µL of MTT (AMRESCO, USA) at a concentration of 5 mg·mL⁻¹, or a CCK-8 kit (YEASEN, China), was added to each well, and the plates were incubated for another 4 h. After incubation, 100 µL of the solution per well was transferred to a 96-well plate for the CCK-8 assay, while for the MTT assay, the solution was replaced with 300 µL of dimethyl sulfoxide (DMSO) and transferred to a 96-well plate at 150 µL per well, after shaking for 10 min. The OD of the plate was measured at 450 nm (n = 6) using a microplate photometer (Multiskan FC, Thermo Scientific, USA) for the CCK-8 assay, and at 490 nm (n = 6) for the MTT assay. After measurement, the wells for the CCK-8 assay were washed carefully with phosphatebuffered saline (PBS) solution; 500 µL of culture medium was then added per well to continue incubating. The assays were assessed at the same time every day for 6 d.

To investigate the background in the MTT assay, zein film slides and glass slides were immersed in culture medium or PBS for 12 h. After being incubated with or without MTT for another 4 h, the solution was replaced with 300 μ L of DMSO and transferred to a 96-well plate at 150 μ L per well, after shaking for 10 min. Next, the OD of the plate was measured at 490 nm (*n* = 6).

2.5. Statistical analysis

Where applicable, all data were expressed as means \pm standard deviation (n = 6). The significance of the differences between data was assessed by one-way analysis of variance (ANOVA). Statistical significance was set at P < 0.05.

3. Results and discussion

3.1. Characterization of four sources of zein

In appearance, both zein 1 and zein 2 are white, while zein 3 and zein 4 are yellow. The morphologies of the zein powders from the four sources could easily be observed due to the autofluorescence of zein protein, as shown in Fig. 1(a-d). As this figure shows, the powders of both zein 1 and zein 2 are pebble-like, while the powders of zein 3 and zein 4 are clastic. Regarding the size of the powders, the subsize powder of zein 3 appears to be

Download English Version:

https://daneshyari.com/en/article/4959227

Download Persian Version:

https://daneshyari.com/article/4959227

Daneshyari.com