

30th Eurosensors Conference, EUROSENSORS 2016

Titanium dioxide nanostructures chemical sensor

A. Bertuna^{a*}, E. Comini^a, N. Poli^a, D. Zappa^a, G. Sberveglieri^a^a*SENSOR Laboratory University of Brescia and CNR-INO, Via D. Valotti 9, 25133 Brescia, Italy*

Abstract

Titanium dioxide (TiO₂) nanostructures were grown directly on the sensitive area of the transducer. A titanium thin film was deposited on 2 · 2 mm² alumina substrates by RF magnetron sputtering and hydrothermal method was used to achieve TiO₂. This method is characterized by the use of different solutions (KOH, NaOH), a not stirred pressure reactor and a heating system. As-prepared samples require an acid treatment followed by a calcination step to obtain pure TiO₂ nanostructures. The nanostructured morphology was confirmed by a scanning electron microscope (SEM) and their structural properties were investigated by RAMAN spectroscopy. Obtained samples were used as gas sensors, and their behaviour towards several gaseous species was analysed in a wide range of working temperatures. Measurements were carried out in a test chamber, investigating the change in the electrical conductance due to the surrounding atmosphere.

© 2016 The Authors. Published by Elsevier Ltd. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>).

Peer-review under responsibility of the organizing committee of the 30th Eurosensors Conference

Keywords: Titanium dioxide; nanostructures; hydrothermal treatment; chemical sensor; Raman spectroscopy

1. Introduction

Titanium dioxide is widely used in several technological fields such as photo-catalysis, hydrogen production by water splitting, solar cells, gas sensors and biological applications. It can also be used for the preparation of paper, plastic, toothpaste and in paints as white pigment. TiO₂ is intensely studied thanks to its numerous characteristics such as non-toxicity, chemical stability and electrical properties [1]. Nowadays titanium dioxide and other metal oxides in the form of nanostructures are used, for their thermal, electric, mechanic, optics properties, in many fields, like sensors, biomedical, solar cell, safety, energy storage and in many other applications [2]. Furthermore,

* Corresponding author. Tel.: +39-030-371-5873; fax: +39-030-209-1271.

E-mail address: a.bertuna@unibs.it

in one-dimensional structures the surface/volume ratio increases and the crystallinity is high. These two factors make them more sensitive in the detection of target gases [3]. One of the most used techniques to growth nanostructures is the hydrothermal treatment, thanks to the possibility to work at low temperatures and to obtain a homogeneous growth [1, 4].

In this work, we present different types of TiO₂ nanostructures grown directly on the sensitive area of transducers to avoid transferring of nanostructures after the growth in order to improve mechanical and electrical stability of devices. The technique used to growth titanium dioxide nanostructures was hydrothermal treatment. This work shows also the functional properties of chemical sensors based on as prepared TiO₂ nanostructures.

2. Experimental

Alumina 2 · 2 mm² substrates were ultrasonically cleaned in acetone for 15 minutes in order to eliminate all the compounds on the surface that can interact during the metal deposition, contaminating it. Afterwards substrates were dried under a flow of synthetic air. Once finished cleaning, RF magnetron sputtering was used to deposit a film of metallic titanium of 100 nm. An electrical power of 75 W was applied to the target, the argon flow was set to 7 sccm and the duration of deposition was 24 minutes. A better adhesion of the film to alumina substrate was guaranteed by heating samples at 100 °C during the deposition.

The growth of several types of nanostructures was performed with hydrothermal treatment using two different hydroxide solution, KOH and NaOH, and different working conditions. Inside a not stirred pressure reactor, solution and samples were added. Thanks to a heating system it was possible change the working temperature. We obtained three different kinds of nanostructures: nanosponge (KOH 0.12 M, 160 °C, 6 hours), nanoflakes (NaOH 0.1 M, 170 °C, 25 hours) and a mix of nanosponge and nanoflakes, which will be defined hereafter nanomix (KOH 0.05 M, 170 °C, 25 hours). All the samples after the hydrothermal treatment were treated in acid (HCl 0.1 M, 1 o hours) and annealed in air in two steps, at first at 50 °C for 1 hour and than at 400 °C for 2 hours.

Samples surface was investigated by a field emission scanning electron microscope (FE-SEM) LEO 1525 operated at 5 kV beam voltage, in order to analyze the morphology of as prepared samples.

Raman spectroscopy was performed on as obtained nanostructures in order to investigated their structural properties. The Raman system is composed by a fibre-coupled confocal optical microscope (HORIBA), a He-Cd blue laser (442 nm), a HORIBA monochromator iHR320 and a Peltier-cooled Synapse CCD.

To fabricate chemical sensors, platinum interdigitated contacts and platinum heating element were deposited by DC Magnetron sputtering (75 W, 7 sccm of argon, 300 °C, 20 minutes for both the depositions) on the top of nanostructures and on the backside of alumina, respectively. Thanks to gold wires, substrates were bonded to a TO case, then devices were placed in a stainless-steel homemade test chamber, with a volume of 1 L, and they were exposed to several gaseous species (carbon monoxide, ethanol, methanol, acetone and hydrogen). Measures were carried out using three different concentration for each gas and setting relative humidity at 40%@20°C. The working temperature of each device was changed from 300 °C to 600 °C and the power applied to each sensor was 1 V.

The changing in the value of electrical conductance gives information about the ability of sensors to detect the different gases injected in the test chamber. The following laws, for oxidizing (1) and reducing (2) gases regulate this variation (in case of n-type metal oxide).

$$\text{Re sponse} = \frac{G_{\text{air}} - G_{\text{gas}}}{G_{\text{gas}}} \quad (1)$$

$$\text{Re sponse} = \frac{G_{\text{gas}} - G_{\text{air}}}{G_{\text{air}}} \quad (2)$$

Download English Version:

<https://daneshyari.com/en/article/5029378>

Download Persian Version:

<https://daneshyari.com/article/5029378>

[Daneshyari.com](https://daneshyari.com)