



Influence of oxygen pressure on the structural, electrical and optical properties of Nb-doped ZnO thin films prepared by pulsed laser deposition

Muying Wu^{a,*}, Shihui Yu^b, Lin He^a, Geng Zhang^a, Dongxiong Ling^a, Weifeng Zhang^c

^a School of Electronic Engineering, Dongguan University of Technology, Guangdong Dongguan 523808, China

^b School of Electronic and Information Engineering, Tianjin University, Tianjin 300072, China

^c Key Laboratory of Photovoltaic Materials of Henan Province and School of Physics and Electronics, Henan University, Kaifeng 475004, China

ARTICLE INFO

Article history:

Received 4 June 2013

Received in revised form 17 October 2013

Accepted 21 November 2013

Available online 1 December 2013

Keywords:

NZO

Pulsed laser deposition

Oxygen pressure

TCO

ABSTRACT

Nb-doped zinc oxide (NZO) transparent conductive thin films with highly (002)-preferred orientation were deposited on glass substrates by pulsed laser deposition method in oxygen ambience under different oxygen pressures. The as-deposited films were characterized by X-ray diffraction (XRD), Field emission-scanning electron microscopy (FE-SEM), electrical and optical characterization techniques. It was found that a desirable amount of oxygen can reduce the related defect scattering and enhance the carrier mobility. The resistivity and average optical transmittance of the NZO thin films are of $10^{-4} \Omega \text{ cm}$ and over 88%, respectively. The lowest electrical resistivity of the film is found to be about $4.37 \times 10^{-4} \Omega \text{ cm}$. In addition, the influence of oxygen pressure on optical properties in NZO thin films was systematically studied as well.

© 2013 Elsevier B.V. All rights reserved.

1. Introduction

Transparent conducting oxides (TCOs), owing to their high electrical conductivity and high optical transmittance in the visible, and high infrared reflectance [1–5], have been widely used as transparent electrodes in various fields such as solar cells, optoelectronic devices, flat panel displays, heat mirrors, and gas sensor. Compared with the more widely used indium tin oxide (ITO), ZnO thin films have lots of advantages, such as low cost, good thermal stability, and convenient fabrication, which show a big potential use for the various applications of solar cells [6], flat panel displays and so on.

Presently, many dopants, such as aluminium (Al) [2,3], gallium (Ga) [4], fluorine (F) [7], niobium (Nb) [8], manganese (Mn) [9], indium (In) [10], titanium (Ti) [11], zirconium (Zr) [12], tin (Sn) [13], boron (B) [5], bismuth (Bi) [14] and chlorine (Cl) [15], have been investigated to improve the electrical and optical properties of ZnO thin films. Among these, Nb doping in ZnO is quite attractive because there is a valence difference of 3 between Nb^{5+} and Zn^{2+} . Therefore, only a tiny amount of Nb doping can produce enough free carriers to reduce the ion scattering effect [16]. In addition, Nb doping also seems to be the most successful and promising due to its smaller ionic radius of 0.70 Å [17] (0.74 Å [18]), as compared

with corresponding values of Zn given in parentheses. Furthermore, Nb has high thermal stability that is enhanced even further when doped into ZnO. As a result, ZnO-based TCO thin films have a great potential in numerous applications.

There are numerous deposition techniques used to grow ZnO thin films (either doped or undoped) including molecular beam epitaxy (MBE) [19], sol-gel processing [13], magnetron sputtering [3,5], metal-organic chemical vapor deposition (MOCVD) [15], thermal evaporation [20] and spray pyrolysis [10,12], and pulsed laser deposition (PLD) [2,4]. Among these fabrication methods, PLD provides several advantages for the growth of multi-component oxide thin films. The composition of films grown by PLD is quite close to that of the target, and it is true even for a multi-component target. Also, PLD films crystallize at relatively lower substrate temperatures compared to other physical vapor deposition (PVD) processes due to the high kinetic energies (>1 eV) of the ejected species in the laser produced plasma [21].

The low resistivity of ZnO thin films is due to defects of oxygen vacancies and zinc interstitials [22]. It is important to study the effect of oxygen pressure on its optoelectrical properties. Literature survey revealed that there was no report on effect of oxygen pressure on optoelectrical properties of Nb doped ZnO thin films by pulsed laser deposition technique. A key to achieve better electrical properties may lie in a good understanding of the role of oxygen in this material system. Therefore in this paper, we study the effects of oxygen pressure on structural, electrical and optical properties of Nb-doped ZnO thin films.

* Corresponding author. Tel.: +86 769 22861102.

E-mail addresses: wumy@dgut.edu.cn, wumy01@163.com (M. Wu).




Fig. 1. X-ray diffraction patterns as a function of oxygen pressure for NZO thin films.

2. Experimental

NZO thin films were deposited on glass substrates with PLD method. A KrF excimer laser (248 nm, 300 mJ, 5 Hz) was employed as the ablation source. The NZO targets were prepared from ZnO powder (purity 99.99%) and Nb₂O₅ powder (purity 99.9%) in a mol proportion of 98:2. The materials are mixed in an agate mortar with fine grinding for 5 h, pressed into 50 mm diameter and 4 mm thickness pellet at a pressure of 20 tone and then sintered in an alumina crucible at 1150 °C for 8 h in air. The substrates were first cleaned with alcohol for 30 min, rinsed in de-ionized water and subsequently dried in a flowing nitrogen gas before being loaded into the chamber. Prior to irradiations, the deposition chamber is evacuated down to a base pressure of 2×10^{-4} Pa and then oxygen (99.99%) was used as the ambient gas. The NZO films were deposited onto the substrate at a temperature of 350 °C and under various oxygen pressures (10^{-3} to 5 Pa). The target–substrate distance was kept at 5 cm. The deposition time of 60 min was maintained. The laser repetition rate was 5 Hz and the energy per pulse was 500 mJ. Before deposition, the target was pretreated in O₂ atmosphere for 15 min to remove any impurity on the surface of the target. After deposition, the films deposited at higher temperature are cooled to room temperature at the same oxygen pressure. All of the films with a typical thickness of about 300 nm obtained from the step height measurement instrument.

To confirm the properties of the films, the XRD patterns were collected on a DX-2700 diffractometer with Cu K α radiation ($\lambda = 1.5418 \text{ \AA}$), the room temperature Hall effect measurements were carried out using a Hall Effect measurement system (Ecopia HMS-3000), the surface morphologies were investigated by scanning electron microscopy (JEOL JSM-7600F, Akishima, Tokyo, Japan) and the transmittance of the films in the wavelength range 300–800 nm was measured using an ultraviolet–visible–near infrared (UV–Vis–NIR) spectrophotometer (Varian Cary 5000).

3. Results and discussions

Fig. 1 shows the XRD patterns of Nb: ZnO (NZO) thin films deposited under various oxygen pressures. All the samples exhibit (002) preferred orientation due to a self-texturing mechanism as discussed by Jiang et al. [23], which indicates that all the films are highly c-axis oriented. The texture coefficients of oxygen pressures of 10^{-3} , 5×10^{-3} , 2×10^{-2} , 1×10^{-1} , 8×10^{-1} and 5 Pa are 57.3%, 58.1%, 62.3%, 71.6%, 68.3% and 66.1%, respectively. With the increment of the oxygen pressure, the (002) peak intensity initially




Fig. 2. Grain size and FWHM of (002) peak of NZO thin films prepared at various oxygen pressures.

increases, to a maximum at 2×10^{-2} Pa, and then decreases gradually. No extra peaks due to the addition of niobium in zinc oxide films were observed, indicating the absence of an impurity phase in the films. That is, the diffractograms provide evidence of single phase crystalline zinc oxide (wurtzite structure).

These phenomenons can be explained as follows. For NZO thin films deposited at low oxygen pressure, there exist lots of oxygen vacancies, thus resulting in the fact that the chemical composition of them is non-stoichiometric and then they have worse crystalline. The excess of oxygen might induce defects in the NZO thin films, which interfere with the nucleation and growth of the films, thus lead to the degradation of the crystalline quality. In addition, the adatoms, with a smaller diffusion path length at higher oxygen pressure, will have less time to adopt a preferred in-plane orientation. Understandably, this reduction in surface adatom mobility can also lead to poor crystallinity. In our experiment, the condition of oxygen pressure at 2×10^{-2} Pa has produced the most highly oriented NZO films, being the critical oxygen partial pressure.

Fig. 2 displays FWHM (Full Width at Half Maximum) of NZO thin films grown at various oxygen pressures. The value of FWHM for the films decreases significantly with the increase of the oxygen pressure. The decrease of the FWHM indicates the increase of grain size of the NZO films. In order to attain the detailed structure information, we calculated the grain size along the c-axis according to the Scherrer's formula [24,25]

$$D = \frac{0.9\lambda}{\beta \cos \theta} \quad (1)$$

where D is the mean grain size, λ is the wave length of Cu K α radiation (1.5418 \AA), β is the (002) peak width and θ is the Bragg diffraction angle. We have corrected β by considering the effect of instrumental broadening. The grain sizes of the thin films deposited at various oxygen pressures are plotted in Fig. 2. The D values increase from 22 to 33 nm with the increase of oxygen pressure, due to the interaction and agglomeration with each other at high oxygen pressure.

Surface morphology of the NZO thin films prepared at different oxygen pressures are studied by SEM. The SEM images in Fig. 3 indicate that the surface morphology is strongly dependent on the oxygen pressure. The average particle size of the NZO film is relatively small when prepared at a low oxygen pressure. With the increasing of oxygen pressure, the average particle size of the NZO film increased. This consists well with the above XRD analysis results. Fig. 3(g) shows the cross-sectional SEM micrograph of the NZO thin film deposited at oxygen pressure of 2×10^{-2} Pa. According to the cross-section images, the film exhibits a columnar crystal

Download English Version:

<https://daneshyari.com/en/article/5353342>

Download Persian Version:

<https://daneshyari.com/article/5353342>

[Daneshyari.com](https://daneshyari.com)