




Contents lists available at ScienceDirect

Applied Surface Science

journal homepage: www.elsevier.com/locate/apsusc



Preparation and characterization of electron-beam treated HDPE composites reinforced with rice husk ash and Brazilian clay

A.V. Ortiz^{a,*}, J.G. Teixeira^a, M.G. Gomes^a, R.R. Oliveira^a, F.R.V. Díaz^b, E.A.B. Moura^a

^a Nuclear and Energy Research Institute, IPEN-CNEN/SP Av. Prof. Lineu Prestes 2242, São Paulo, SP 05508-000, Brazil

^b Metallurgical and Materials Engineering Department, Polytechnic School, University of São Paulo Av. Prof. Mello de Moraes 2463, São Paulo, SP 05508-900, Brazil

ARTICLE INFO

Article history:

Received 1 December 2013

Received in revised form 12 March 2014

Accepted 12 March 2014

Available online xxx

Keywords:

HDPE

Electron-beam

Composite

Clay

Ash

Waste

ABSTRACT

This work evaluates the morphology, mechanical and thermo-mechanical properties of high density polyethylene (HDPE) composites. HDPE reinforced with rice husk ashes (80:20 wt%), HDPE reinforced with clay (97:3 wt%) and HDPE reinforced with both rice husk ashes and clay (77:20:3 wt%) were obtained. The Brazilian bentonite chocolate clay was used in this study. This Brazilian smectitic clay is commonly used to produce nanocomposites. The composites were produced by melting extrusion process and then irradiation was carried out in a 1.5 MeV electron-beam accelerator (room temperature, presence of air). Comparisons using the irradiated and non-irradiated neat polymer, and the irradiated and non-irradiated composites were made. The materials obtained were submitted to tensile, flexural and impact tests. Additionally HDT, SEM and XRD analyses were carried out along with the sol–gel analysis which aimed to assess the cross-linking degree of the irradiated materials. Results showed great improvement in most HDPE properties and a high cross-linking degree of 85% as a result of electron-beam irradiation of the material.

© 2014 Published by Elsevier B.V.

1. Introduction

The objective of this study is to evaluate possible changes in high density polyethylene (HDPE) composite properties when it is reinforced with clay, rice husk ashes, or a combination of both reinforcements, and when the resulting HDPE composites are electron-beam irradiated.

A composite is a material resulting from the combination of two or more materials in order to optimize the properties of each component. Traditional reinforcements used in composites are common materials and do not require high technology, for example, fibers, silica and graphite. The polymer is generally viewed as the weakest link from the mechanical point of view and researchers mostly focused efforts on increasing the content of reinforcement in the final material or improving interaction with reinforcements. Nanoparticles lead to an opposite direction. While a traditional composite may contain up to 40% of reinforcement in weight, the introduction of nanoparticles as reinforcement often shows

important gains in material properties in concentrations not exceeding 5% [1].

Currently, one can observe an increasing use of reinforcements coming from renewable resources [2]. Environmental issues have led to the development of biodegradable as well as traditional materials with an increasing level of additives, fillers and reinforcements from vegetable origin as well as renewable polymeric materials [3,4]. The use of agricultural sub-products has been extensively studied as a source of these reinforcements [5,6]. But such organic wastes have also been widely used in energy co-generation and as a result of burning, large amounts of ash are produced. Because of its characteristics, ash can be used as reinforcement. In addition to its cementitious material nature, studies have shown the capability of adding costless ashes of vegetable origin as a substitute for talc and other mineral fillers [3,5,7].

Among the various natural fibers and ashes that can be used as a dispersed phase in polymer composites is rice husk. The husk is a coating or protective layer formed during the growth of rice grains. Removed during the refining of rice, this shell has low commercial value, since it has little nutritional value and therefore is not used in human or animal food. A few years ago, almost all of this material would end up in the bottom of rivers and fields. Concerned with the growing environmental contamination by this

* Corresponding author. Tel.: +55 11 31339883.

E-mail addresses: angelortiz@ipen.br, angelortiz@uol.com.br (A.V. Ortiz).

waste, some groups have dedicated themselves to the study of its use for power generation. Rice husk ashes may be used as a component in the composition of ceramics and refractory insulation as well as in the construction and rubber industries, and also applied as reinforcement for polymers [9].

Besides the use of green materials and waste, recent research has demonstrated that the addition of little amount of natural clays (less than 10%) may improve mechanical, thermal and barrier properties, and also dimensional stability of a composite when compared with the pure polymer [8–10]. When clay can generate particle sizes at the nanometric level (up to 100 nm) in its processing with the polymer, a nanocomposite is generated. The most common method to obtain a nanocomposite is the processing of a polymer and organoclay mixture in the molten state to allow intercalation of polymer chains between clay lamellae [11–13].

In this study the polymer used was high density polyethylene (HDPE) that is a thermoplastic resulting from the polymerization of ethylene, and is widely used in various industries due to its mechanical properties, chemical resistance, water impermeability, ease of processing and low cost.

HDPE is an inexpensive commodity polymer, but its use in some engineering applications may depend on improving its properties by crosslinking [14]. The use of radiation on the molecules of a polymer, particular for HDPE, is a method often used for modification of its properties, as it promotes a process involving simultaneously crosslinking and scission of the material polymeric chains, leading to greater degrees of compatibility and stabilization. Electron beams applied for radiation processing for crosslinking are usually used within electron energy range 0.5–3 MeV and absorbed dose up to a few hundreds of kGy. Radiation crosslinking involves the formation of three dimensional structures by the abstraction of a hydrogen atom from the PE backbone. The free radical left on the carbon chain then finds another free radical site on a neighboring carbon on another molecule to form a crosslink. Crosslinking is located primarily in the non-crystalline phase and along the lamellar amorphous interphase [15]. Because the cross-linking process changes a linear network into a three-dimensional one, it can produce materials with high thermal stability, better strength, and better resistance to impact [16–19].

2. Experimental methods

The materials used in this study were HDPE JV060U (by Braskem S/A), rice husk ashes disposed by the agroindustry in Uruguay and sodic bentonite chocolate clay powder from the northeast of Brazil (by Pegmatech Especialidades Tecnológicas Ltda.). Rice husk ashes were prepared by first drying them at $130 \pm 2^\circ\text{C}$ for 24 h in an air-circulating oven. Then dry ashes were reduced to fine powder, with particle sizes equal or smaller than 250 μm by using a ball mill, and dried again at $130 \pm 2^\circ\text{C}$ for 24 h to reduce the moisture content. In order to make the sodic clay more organophilic, it was modified by the addition of quaternary ammonium salt and sodium carbonate. Then it underwent dispersion into water and finally it was filtered and dried.

Composites made out of HDPE and one or a combination of the two reinforcements were obtained by hand mixing the materials and then making the final combination undergo melting extrusion in a twin screw extruder. The extruded composites were pelletized, then fed into an injection molding machine and test samples were obtained. Finally, for each composite produced, part of it was submitted to electron-beam radiation. The electron-beam radiation process was carried out at 250 kGy using a 1.5 MeV electrostatic accelerator (Dynamitron II, Radiation Dynamics Inc., 1.5 MeV energy, 25 mA current and 37.5 kW power), at room temperature, in air, dose rate 28.02 kGy/s. Irradiation doses were

Table 1
List of materials used in this study.

M1	Non-irradiated composite consisting of 100% HDPE
M2	Non-irradiated composite consisting of 80% HDPE/20% ash (wt%)
M3	Non-irradiated composite consisting of 97% HDPE/3% clay (wt%)
M4	Non-irradiated composite consisting of 77% HDPE/20% Ash/3% clay (wt%)
M5	Composite consisting of 100% HDPE irradiated at 250 kGy
M6	Composite consisting of 80% HDPE/20% ash (wt%) irradiated at 250 kGy
M7	Composite consisting of 97% HDPE/3% clay (wt%) irradiated at 250 kGy
M8	Composite consisting of 77% HDPE/20% Ash/3% clay (wt%) irradiated at 250 kGy

measured using cellulose triacetate film dosimeters “CTA-FTR-125” from Fuji Photo Film Co. Ltd.

Eight different materials were generated and were available to be analyzed. Table 1 lists the materials produced for this study. The decision on the concentration of ash and clay to be added in the HDPE for this study was based on previous tests comparing different concentrations of each reinforcement in HDPE. No important property improvements were observed in the HDPE/ash composite when the HDPE carried more than 20% of ash. And for the sodic clay, studies evaluating concentrations up to 5% showed that no important improvement in the HDPE/clay composite properties were observed when more than 3% of clay were incorporated in HDPE.

Material characterization was carried out. Characterization involved mechanical and thermo-mechanical testing, scanning electron microscopy, X-ray diffraction and sol–gel analysis. Mechanical and thermo-mechanical properties studied were tensile properties according to ASTM D638 standard [20], flexural strength according to ASTM D790 standard [21], heat distortion temperature according to ASTM D648 standard [22] and Izod impact resistance according to ASTM D256 standard [23]. The results presented in this work are the average for 5 tested specimens and variation between specimens are not greater than 15%. Scanning electron microscopy (SEM) analyses were carried out using a LX30 (Phillips). The samples were cryofractured under liquid nitrogen and then the fractured surface was coated with a fine layer of gold and observed by scanning electron microscopy. X-ray diffraction (XRD) analyses were carried out on a Rigaku Denki Co. Ltd., Multiflex model diffractometer, with $\text{CuK}\alpha$ radiation ($\lambda = 1.5406 \text{ \AA}$) at 40 kV and 20 mA, with 2θ varying between 2° and 50° . Sol–gel analyses for detecting crosslinking degree was carried out in a system set up with round bottom flasks, Soxhlet extractors, condensers and heating units. Tests were made in triplicate with boiling xylene as solvent and heating for 12 h. Variation between results is not greater than 2%.

3. Results and discussion

Table 2 summarizes the results obtained for the tensile testing. As it can be seen in Table 2, the inclusion of reinforcement in the polymeric matrix greatly increased the tensile strength at break. But the effect in the elongation at break was the opposite. It is also important to notice that the use of irradiation led to superior gains in tensile strength. The irradiated HDPE/clay combination led to a material presenting 23.16 MPa as its tensile strength at break which is 314% greater than the original HDPE property of only 5.60 MPa. The stress–strain curves for the studied materials are shown in Fig. 1.

Table 3 presents the results obtained for the flexural property. As it can be seen from the results in Table 3, for the studied materials most of the time there was loss in the flexural property when the reinforcement was added to the polymeric matrix. Although most of the studied composites presented loss in flexural properties, it

Download English Version:

<https://daneshyari.com/en/article/5356690>

Download Persian Version:

<https://daneshyari.com/article/5356690>

[Daneshyari.com](https://daneshyari.com)