



An ultra-sensitive Au nanoparticles functionalized DNA biosensor for electrochemical sensing of mercury ions

Yanyan Zhang, Cong Zhang, Rui Ma, Xin Du, Wenhao Dong, Yuan Chen, Qiang Chen *

The Key Laboratory of Bioactive Materials, Ministry of Education, College of Life Science, Nankai University, Weijin Road No. 94, Tianjin 300071, China

ARTICLE INFO

Article history:

Received 6 July 2016

Received in revised form 31 October 2016

Accepted 14 February 2017

Available online 16 February 2017

Keywords:

DNA probe

Mercury ions

Biosensor

Ultra-sensitivity

ABSTRACT

The present work describes an effective strategy to fabricate a highly sensitive and selective DNA-biosensor for the determination of mercury ions (Hg^{2+}). The DNA 1 was modified onto the surface of Au electrode by the interaction between sulfhydryl group and Au electrode. DNA probe is complementary with DNA 1. In the presence of Hg^{2+} , the electrochemical signal increases owing to that Hg^{2+} -mediated thymine bases induce the conformation of DNA probe to change from line to hairpin and less DNA probes adsorb into DNA 1. Taking advantage of its reduction property, methylene blue is considered as the signal indicating molecule. For improving the sensitivity of the biosensor, Au nanoparticles (Au NPs) modified reporter DNA 3 is used to adsorb DNA 1. Electrochemical behaviors of the biosensor were evaluated by electrochemical impedance spectroscopy and cyclic voltammetry. Several important parameters which could affect the property of the biosensor were studied and optimized. Under the optimal conditions, the biosensor exhibits wide linear range, high sensitivity and low detection limit. Besides, it displays superior selectivity and excellent stability. The biosensor was also applied for water sample detection with satisfactory result. The novel strategy of fabricating biosensor provides a potential platform for fabricating a variety of metal ions biosensors.

© 2017 Elsevier B.V. All rights reserved.

1. Introduction

Mercury, a potent toxin, can be accumulated in the vital tissues and organs binding with proteins and enzymes, which results in cell functions abnormality and all kinds of diseases [1,2]. The detection of mercury contaminants has played an important role in environmental bioinorganic chemistry, clinical toxicology, waste management and bio-remediation of metal ions [3].

Recently, many detection techniques have been developed for detecting a variety of environmental factors, including fluorescence, surface plasmon resonance, electrochemistry, colorimetric sensors and other analytical techniques [4–6]. Among these methods, electrochemical method has been widely applied for accurate determination of metal ions for its high sensitivity, low detection limit and low cost [7–15]. Despite many advances in this field, there is still a quest for new schemes and strategies for improvement of the sensitivity, simplicity and selectivity of metal ion sensors.

It's clear that thymine bases (T) could specifically capture Hg^{2+} ions as the intrinsic interaction between Hg^{2+} ions and thymine bases [16–18]. So, a series of mercury biosensors based on T- Hg^{2+} -T have been appeared because this strategy possesses high selectivity towards Hg^{2+} ions against other related environmental heavy metal ions. Many

reported mercury biosensors have obtained lower detection limit, such as the Mirkin's group used Au NPs to combine with DNA for detecting Hg^{2+} ions with the detection limit of 10 nM [19], the Liu's group synthesized hydrogel microparticles with covalently attaching DNA probes and detected Hg^{2+} ions by the fluorescence change with the detection limit of 10 nM [20,21] and the Zhang's group developed a graphene-DNA biosensor for detecting Hg^{2+} ions with the detection limit of 5 nM [22], however, it's difficult to meet the need of water sample detection. Besides, some other T- Hg^{2+} -T biosensors for Hg^{2+} ions detection are also reported [23,24]. As the limit amount of mercury ions in drinking water recommended by the World Health Organization (WHO) is 5 nM [25], it is urgent to develop an effective strategy for improving the sensitivity of analyzing mercury ions.

Electrochemical sensor has been widely applied to detect Hg^{2+} ions because of its superior sensitivity, facile fabrication and low cost. Herein, we develop an ultra-sensitive, facile and reusable electrochemical biosensor for detecting Hg^{2+} ions. Initially, DNA modified Au electrode captured complementary probe forming double helix structure, which blocks the electrochemical signal transfer. Once DNA probe was specifically combined with Hg^{2+} ions, the electrochemical signal would increase. Au NPs functionalized reporter DNA was combined with DNA 1 to achieve signal amplification. Although Au NPs as signal amplifier has been reported, in this paper, the strategy of fabricating biosensor is facile and displays high sensitivity. Methylene blue (MB) was used as a signal indicating molecule and specifically combined with guanine

* Corresponding author.

E-mail address: qiangchen@nankai.edu.cn (Q. Chen).

(G) bases of reporter DNA [26,27]. The Au NPs functionalized DNA 3-DNA 2-DNA 1-modified electrode exhibits excellent performance.

2. Experimental

2.1. Reagents

The oligo-nucleotides were purchased from Dingguo Co. Ltd. (China). The sequence of DNA 1 is 5'-SH-AAAAAAAAAAAAACGC GCG-3', the sequence of probe DNA 2 is 5'-TTTTTTTTTTTTTTT-3' and the sequence of reporter DNA 3 is 5'-SH-CGCGCGCGCGCG-3'. Sulfuric acid (H₂SO₄) and hydrogen peroxide (H₂O₂) were purchased from Tianjin Yingda Rare Chemical Reagent Co. (China). Au electrodes (3 mm diameter) were purchased from Tianjin Aidahengsheng technology Co. Ltd. (China). HAuCl₄, HgCl₂, PdCl₂, NiCl₂, CuCl₂, CoCl₂, MnCl₂ and CdCl₂ were purchased from Aldrich Co. (USA). All aqueous solutions were prepared by double distilled water. All other reagents used in this work were analytical grade without further purification.

2.2. Measurements

A 283 Potentiostat–Galvanostat electrochemical workstation (EG & GPARC with M 270 software) and Lanlike 2010 electrochemical workstation (Lanlike chemical & electronic high-tech Co. Ltd.) were applied to electrochemical experiments. Au NPs functionalized reporter DNA 3-DNA 2-DNA 1-modified Au electrode (3 mm diameter) was used as working electrode, Ag/AgCl (saturated with KCl) was used as reference electrode and a Pt wire was applied as auxiliary electrode which develops a conventional three-electrode system.

2.3. Preparation of Au NPs functionalized reporter DNA 3

Au NPs were synthesized by a traditional method [28]. Briefly, 39.97 mg of HAuCl₄ was dissolved in 25 mL of distilled water, then, 2.5 mL of sodium citrate (19.4 mM) was added to above boiling solution obtained dark amaranth solution. Au NPs functionalized reporter DNA by S–Au bond was prepared by incubating 50 μ L of sulfhydryl-modified reporter DNA (10 μ M) with 5 mL of Au NPs solution at 37 °C. After that, 100 μ L of 6-mercapto-hexanol was added to the solution, which blocked the sulfhydryl group of reporter DNA to directly adsorb onto the surface of Au electrode.

2.4. Fabrication of DNA modified mercury biosensor

Au electrodes employed in this report were polished by powder of aluminum oxide and cleaned in the solution of H₂SO₄ (0.5 M) and H₂O₂ (30%) (3/1, v/v) for 10 min, then, ultrasonically rinsed with distilled water. The polished electrodes were dried with nitrogen gas. 50 μ L of sulfhydryl-modified DNA 1 was mixed with 5 mL of tris (2-carboxyethyl) phosphine (TCEP) (1 mM) to prevent the disulfide bond producing and assure the DNA 1 stayed on the electrode as single layer.

DNA 1-modified Au electrode was obtained by immersing the cleaned Au electrode into the above DNA 1 solution for 2 h at 37 °C. Then, the modified electrode was incubated with Au NPs functionalized reporter DNA 3 for 2 h at 37 °C. DNA 2 probes were incubated with various concentrations of Hg²⁺ for 2 h. Thereafter, Au NPs functionalized DNA 3-DNA 1 modified electrode was immersed into above DNA 2 probe for 2 h. At last, the modified electrode was immersed into 5 mg/mL MB for 1 h followed by being cleaned with distilled water. The approach of the fabricated biosensor is illustrated in Scheme 1. As shown in Scheme 1, when Hg²⁺ was added to DNA 2 probe, Hg²⁺-mediated thymine bases formed mismatched T-Hg²⁺-T stable bases pairs and the conformation of DNA probe changed from line to hairpin, which resulted in less DNA probes adsorbing onto DNA 1. Therefore, the electrochemical signal increased and the electrochemical responses of

the fabricated biosensor were in accordance with various Hg²⁺ concentrations.

3. Results and discussion

3.1. Electrochemical characterization of the DNA modified electrode

In order to study the signal indicating role of MB, the Au NPs functionalized DNA 3-DNA 2-DNA 1-modified Au electrode without being immersed into 5 mg/mL MB (a) and with being immersed into 5 mg/mL MB (b) for detecting 100 nM Hg²⁺ ions were investigated. As shown in Fig. 1, the biosensor immersed into MB (b) displays a sharp reduction peak whereas the reduction peak of (a) is weak. This phenomenon can be explained that the MB possesses excellent reduction property under the electrochemical environment and the reduction current is increased obviously.

To study the electrochemical response of DNA modified electrode towards Hg²⁺ ions and the signal amplified role of Au NPs, cyclic voltammetry (CV) responses of the Au NPs functionalized DNA 3-DNA 2-DNA 1-modified electrode towards 100 nM Hg²⁺ ions (a) and without Hg²⁺ ions (b) and DNA 1-modified biosensor towards 100 nM Hg²⁺ ions (c) were recorded in 0.1 M phosphate buffer solution (PBS) (pH 7.0) (Fig. 2). For Au NPs functionalized DNA 3-DNA 2-DNA 1-modified electrode, an obvious reduction peak is appeared at appropriately -0.9 V owing to the reduction of MB. Effective electro-active area is a vital factor for evaluating electrochemical behavior. According to the following Randles-Sevcik equation [29], microscopic effective electro-active area could be calculated.

$$I_p = 2.69 \times 10^5 A D^{1/2} n^{3/2} \gamma^{1/2} C \quad (1)$$

In this equation, A corresponds to effective electro-active surface area of working electrode (cm²); D represents the diffusion coefficient in solution and it approximately is 6.70×10^{-6} cm² s⁻¹; n is the amount of electron which transfer in the reaction, the value is equal to 1; γ is the scan rate (V s⁻¹); C is the concentration of detected molecule, in this system the concentration of detected molecule is 100 nM and I_p represents the current of redox peak. By calculating, the effective electro-active area of the Au NPs functionalized DNA 3-DNA 2-DNA 1-modified electrode towards 100 nM Hg²⁺ ions is 2 and 1.5 times higher than without Au NPs functionalized electrode and without addition of Hg²⁺ ions, respectively. In Fig. 2, the reduction peak current of (a) is much higher than that of (c), indicating that the Au NPs can be regarded as signal amplifier which is in accordance with the reported literature [30]. Besides, the electrochemical response of the biosensor with adding of Hg²⁺ ions is much higher than that of without Hg²⁺ ions. This phenomenon could be caused by Hg²⁺ ions insert into the T-T base pairs forming stable T-Hg²⁺-T interaction, which results in the DNA 2 conformation changing into double helix structure. Thereafter, while DNA 1 modified Au electrode was incubated with DNA 2, the electrochemical response was decreased, which resulted of that single linker was easier to electron transfer than double helix structure. Thus, more Hg²⁺ ions are added to DNA 2 solution, higher reduction current is appeared. Excellent electrochemical response of the modified electrode verifies that this strategy is worthy for detecting mercury ions.

The transfer coefficient (α) value was calculated via Eq. (2) [31]. α was found to be 0.41.

$$E_p - E_{p/2} = 48 / (\alpha n_a) \quad (2)$$

3.2. Optimization of the fabricated biosensor

For achieving the optimal performance of the biosensor, scan rate, pH value of PBS solution, incubation time of DNA 1-modified electrode with DNA 2 solution and incubation time of DNA 1 with Au electrode

Download English Version:

<https://daneshyari.com/en/article/5434815>

Download Persian Version:

<https://daneshyari.com/article/5434815>

[Daneshyari.com](https://daneshyari.com)