

Accepted Manuscript

Damping properties of coatings at elevated temperatures

Oliver Easterday, Anthony Palazotto, William Baker, Richard Branam



PII: S0257-8972(17)30371-7
DOI: doi: [10.1016/j.surfcoat.2017.04.025](https://doi.org/10.1016/j.surfcoat.2017.04.025)
Reference: SCT 22268
To appear in: *Surface & Coatings Technology*
Received date: 9 December 2016
Revised date: 10 April 2017
Accepted date: 11 April 2017

Please cite this article as: Oliver Easterday, Anthony Palazotto, William Baker, Richard Branam , Damping properties of coatings at elevated temperatures. The address for the corresponding author was captured as affiliation for all authors. Please check if appropriate. Sct(2017), doi: [10.1016/j.surfcoat.2017.04.025](https://doi.org/10.1016/j.surfcoat.2017.04.025)

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Damping Properties of Coatings at Elevated Temperatures

Oliver Easterday^a (Retired), Anthony Palazotto^{a,*}, William Baker^a, Richard Branam^b

^a Air Force Institute of Technology, WPAFB, Ohio, 45433

^b University of Alabama, Tuscaloosa, Al., 35487

ABSTRACT

The research reported upon in this paper is an evaluation of the complex modulus (both storage and loss modulus) of a TBC thin coating, 8% stabilized yttrium stabilized zirconium (8YSZ). The specimen incorporated is supported in a free-free fashion and placed in a vacuum chamber surrounded by 200W halogen lamps that allow for an isothermal temperature up to 482degrees C. The use of a free-free support and the vacuum chamber enclosure is meant to remove external agents which may inject overall effects on the loading dynamic properties. The dynamic excitation was developed with a series of permanent magnets placed strategically, creating a magnetic field developed with up to 7500 mA(7500 milli amps) current. In order to separate the combined effect of the base material (a titanium beam) from the coating, a method incorporating finite elements was carried out. A strain energy ratio (SER) was used equal to the amount of elastic energy stored in the coating over that stored in the metallic beam. The results led to the dynamic moduli. In order to determine these dynamic coefficients, a vibration ring down technique was incorporated requiring time to reach a steady state. A low value for the loss factor of about 0.02 exists that is applicable across all strain levels, temperatures, and amplitudes. The strain dependency can be approximated using a lower boundary form:

$\eta_c = 0.00621 \ln(\varepsilon_{11}) + 0.021$; ε_{11} in micro strain In addition, it was found that 8YSZ is a strain softening material. The material is strongly nonlinear with room temperature values obtained close to those of previous work but varying in strain amount and amplitude of excitation. It has a storage modulus value of 30-35 GPa like other references. Similar to previous studies, much

Download English Version:

<https://daneshyari.com/en/article/5464568>

Download Persian Version:

<https://daneshyari.com/article/5464568>

[Daneshyari.com](https://daneshyari.com)