



9th International Conference on Photonic Technologies - LANE 2016

Influence of laser power on the shape of single tracks in scanner based laser wire cladding

A. Barroi^{a,*}, D. Albertazzi Gonçalves^a, J. Hermsdorf^a, S. Kaierle^a, L. Overmeyer^a

^aLaser Zentrum Hannover e.V., Hollerithalle 8, 30419 Hannover, Germany

Abstract

The shape of the cladding tracks is extremely important for producing layers or structures by adding them sequentially. This paper shows the influence of the laser power of a diode laser in the range of 500 to 1000 W on the shapes of single tracks in scanner based laser wire cladding. The scanner was used to oscillate the beam perpendicular to the welding direction. Stainless steel (ER 318 Si) wire with a 0.6 mm diameter was used as deposition material. Height, width, penetration, molten area and weld seam angles of single tracks were obtained from cross-sections at three different positions of each track. The influence of these different positions on the results depends on the traverse speed. The paper discusses this influence in respect to the heat dissipation in the substrate material.

© 2016 The Authors. Published by Elsevier B.V. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>).

Peer-review under responsibility of the Bayerisches Laserzentrum GmbH

Keywords: laser cladding; wire; shape; laser scanner

1. Introduction

In industry, many tools and parts have a reduced life cycle due to wear. Cladding technologies are commonly used to apply a wear-resistant layer over them. The use of the laser cladding technology is increasing because of advantages such as reduced dilution and thermal deformations when compared to other cladding technologies. The wire feeding option – instead of powder feeding – is also growing in industry because of storage ease, increased health safety and reduced waste of material.

To fit a clad to a specific welding situation it is crucial to be able to determine the shape of the tracks that are used to form the desired deposition geometry. A flat track, for example, is well suited when welding a protective layer.

* Corresponding author. Tel.: +49-511-2788-174 ; fax: +49-511-2788-100 .
E-mail address: a.barroi@lzh.de

When welding on the edge of a work piece or when building up a structure, a higher track with steep sides is more beneficial.

Many different approaches relating process parameters to track geometry are presented in the literature, most of them modeling powder fed processes. Kumar et al. (2012) predict a single track geometry in two dimension based on a detailed finite element model, taking process parameters as input data. Their data was experimentally verified, obtaining low average errors for track height and width. Costa et al. (2003) also predicted track geometry, but with a simpler semi-empirical model based on combined roles of different process parameters. De Oliveira et al. (2005) also performed some experiments relating combined parameters to the main clad dimensions, after calculating the required energy to melt separately substrate and additive material. The combined parameters found differed from each author, which was expected due to the results experimental nature. Paulo Davim et al. (2008) successfully established relations between process parameters and geometry features by multiple regression analysis. Saqib et al. (2014) proved that those relations can also be found running simple statistical methods on experimental data. El Cheikh et al. (2012) modeled the track upper section as a circle and calculated its center and radius based on the process parameters. Pinkerton and Li (2004) modeled not only the upper part, but both sections of the track as detached arc circles. After that, they used mass and energy balance to define the boundaries of the molten pool, obtaining the track geometry. In both papers the models were tested experimentally, obtaining good correlations. The geometry of clad layers was also investigated. Nenadl et al. (2014) and Ocelik et al. (2014) predicted a layer geometry with a recursive geometrical model based mostly on a single track profile and the overlap between tracks. Their works were experimentally verified, successfully predicting the layer geometry. All those models, however, were based on powder fed systems.

Models relating track geometry and process parameters for wire fed process, however, lack on references in the literature. Syed and Li (2005) researched the effects of wire position, angle and direction on surface finish and geometry stability. In their study, front feeding with the wire tip near the molten pool's leading edge was the optimum setup. Klocke et al. (2012) found a relation of laser power and traverse speed to maintain the track shape constant. Pekkarinen (2015) adjusted the power distribution with a scanner system to influence the track shape. Barroi et al. (2011) used a laser assisted electrical arc process for build up welding and determined the layer height and a method to overcome geometrical problems at the start and end of the tracks. Kim and Peng, (2000) studied the plunging method for laser cladding with wire, being able to stabilize it, obtaining solid bonding and good surface finish. First steps towards geometry modelling for wire based cladding are the topic of this work. One of the most important parameters, the laser power and its influence on the track shape was investigated.

2. Experimental

The experiments were performed using a 2 kW Laserline diode laser emitting at 1025 nm. A 400 μm fiber delivered the radiation, which was shaped with a 100 mm focal length collimator lens and a 400 mm focal length focusing lens. The projected laser spot was moved perpendicular to the welding direction by an oscillating mirror - a laser scanner. This scanner is controlled by a function generator, which allows to vary its amplitude, frequency and waveform. The deposition material is supplied by a wire-feeding system produced by Dinse, which is able to handle the 0.6 mm diameter wire and monitor the feeding speed. Fixed parameters of this investigation were the argon shielding gas with a flow rate of 6 l/min, wire type (ER 318 Si), wire feed speed of 0.6 mm/min and the scanner parameters. The scanner was oscillated at a frequency of 50 Hz with a symmetrical ramp function and an amplitude of 1.1 mm peak-to-peak on the workpiece. With a laser spot size of 2.9 mm, the oscillation leads to an elliptical spot with 2.9 mm in direction of the weld and 4 mm perpendicular to this direction. The traverse speed of 2.2 mm/s was chosen due to two reasons: low deviation of the cladding area, which allows a better evaluation of the results and low deviation of the height, which means that the cumulated heat in work piece has a small influence on the results. The latter point will be further discussed in the results section. The tests performed to determine these deviations were done at a constant laser power of 640 W and with seven traverse speeds ranging from 0.83 mm/s to 5.83 mm/s.

The variable parameter in this investigation on the shape of the track was the laser power. It was varied in 7 equally spaced steps from 475 W to 805 W.

Download English Version:

<https://daneshyari.com/en/article/5497400>

Download Persian Version:

<https://daneshyari.com/article/5497400>

[Daneshyari.com](https://daneshyari.com)