



Research Paper

Eucalyptus short-rotation coppice for solid fuel production



Humberto de Jesus Eufraide Junior^a, Gabriela Tami Nakashima^b, Fábio Minoru Yamaji^{b,*},
Saulo Philipe Sebastião Guerra^a, Adriano Wagner Ballarin^a

^a Sao Paulo State University – School of Agricultural Sciences (UNESP/FCA), Jose Barbosa Barros St., 1780, Botucatu, Sao Paulo, Brazil

^b Biomass and Bioenergy Research Group Federal University of São Carlos (UFSCar), Rodovia João Leme dos Santos, km 110, Sorocaba, São Paulo, Brazil

ARTICLE INFO

Keywords:

Briquettes
SRC biomass
Heating value
Mechanical properties

ABSTRACT

Briquetting provides a homogenous product that has high density, and reduced transport and storage costs in the wood chips supply chain. Few studies evaluated briquettes from eucalypt short-rotation coppice (SRC) managed under tropical conditions and also its energy potential was not clearly defined. The aim of this paper was to assess the quality of briquettes produced from *Eucalyptus* SRC. The SRC biomass was separated into stem, branches, leaves and mix (produced according to the actual availability in the forest). The physical, chemical and mechanical properties were analyzed. A SEM-EDS (scanning electron microscopy equipped with an energy-dispersive spectroscopy detector) analysis of ashes from SRC biomass was carried out. Results showed higher energy properties in leaves than for woody fractions, however, its use was limited due to higher content of ash (3.1%) and a poor mechanical performance. Stem and mix were more suitable for energy purposes, and both treatments reached an energy potential of 14.2 GJ m⁻³. SEM-EDS analysis showed that the elements Ca, K and Mg represented approximately 80% of the mineral component. It was found that the presence of other regular structures predominantly comprising the elements Fe and Al may lead to a serious technical problem. However, briquetting appears as a feasible option to increase added value of forest products from young energetic plantations.

1. Introduction

Biomass has an important role to play in the production of energy (REN21, 2014), mainly in developing countries (Demirbas et al., 2009; Goldemberg, 1998). The short-rotation coppice (SRC) appears to be a major advancement in alternative renewable energy due to production of high-yielding biomass in a short time (Guerra et al., 2014; Kauter et al., 2003). Harvesting of these dedicated energy crops included all above-ground biomass (stems, branches and leaves) that were chipped by a forage harvester (Guerra et al., 2016; Spinelli et al., 2009).

Whole-tree chips present a high moisture content and low density while presenting some difficulties in transportation, storage and use. The briquetting process presents as an alternative to producing a homogenous and high-density solid product (Grover and Mishra, 1996), improving the biomass quality and reducing supply chain costs (Demirbas, 2010; Kaliyan and Morey, 2009).

Knowledge about the physical and chemical characteristics of briquettes is important to be able to understand the behavior of the burnt fuel, and to consolidate the viability of the biomass supply chain. The briquetting process was consolidated for use in agroindustrial residues

(Felfli et al., 2011). However, few studies evaluated briquettes from SRC managed under tropical conditions, and its energy potential was not clearly defined.

It is known that raw material has a great influence on the quality of briquettes. For forest biomass, the leaves have superior heating value than woody fractions (Cuiping et al., 2004; Pérez et al., 2011), but they have a higher ash content which implies several industrial problems such as encrustation and abrasive wear in metal machines. These aspects also influence its market price (Stolarski et al., 2013).

This paper aims to assess the quality of the briquettes produced from 2 years of eucalyptus plantations managed on SRC. To accomplish this objective, the SRC biomass was separated into stem (wood and bark), branches and leaves, and the physical, chemical and mechanical properties of briquettes were studied.

2. Materials and methods

2.1. Sampling and material preparation

The sample trees were obtained from an interspecific hybrid of

* Corresponding author.

E-mail addresses: hdjejunior@fca.unesp.br (H.d.J. Eufraide Junior), gabrielatn@ufscar.br (G.T. Nakashima), fmyamaji@ufscar.br (F.M. Yamaji), ssguerra@fca.unesp.br (S.P.S. Guerra), awballarin@fca.unesp.br (A.W. Ballarin).

<http://dx.doi.org/10.1016/j.indcrop.2017.07.025>

Received 25 January 2017; Received in revised form 13 June 2017; Accepted 10 July 2017
0926-6690/ © 2017 Elsevier B.V. All rights reserved.

Eucalyptus urophylla × *Eucalyptus grandis* (clone C219) plantations that were 2 years old, located at Botucatu City (22°58'S and 48°25'W) Sao Paulo State – Brazil. The local region has an average altitude of 872m, a mean annual precipitation of about 1428 mm year⁻¹ and an annual average temperature of 20 °C. The soil of experimental area was a Red-Yellow Latosol (Oxisol). The crops were managed with a high density of trees per hectare, plots with 2.8 × 1.5 m (2380 trees/ha) and 2.8 × 0.5 m (7142 trees/ha).

The equipment used for harvest was New Holland harvester (FR9060 model) fitted with the 130FB header. Twelve medium-sized trees (6–8 cm of diameter breast height and 9–11 m of mean height) were selected for sampling in the different density planting of *Eucalyptus* SRC. The trees were separated in the following proportions: stem (wood and bark), branches and leaves. There were collected 8.5 kg of stem, 1.7 kg of branches and 1.5 kg of leaves. After air drying, each portion of the biomass from 12 trees was grinded in a Wiley-type mill and homogenized in a plastic bag.

The material was conditioned to equilibrium in a climate-controlled room under 65% relative humidity, and 21 °C (approximately 12% equilibrium moisture content). The briquettes were produced using a hydraulic press (Marcon, model MPH-30). The briquetting process was performed with 122 MPa of compaction pressure with 30 s of press time, without the use of temperature and binder. It was used a cylindrical shape metallic support with 35 mm diameter and 160 mm height to apply this pressure. It was used approximately 1200 g of mass for briquetting process (20 g per briquette) with 35 mm diameter and 20 mm height.

Four treatments (15 specimens per treatments) were studied considering the different biomasses: 1. stem; 2. branches; 3. leaves and 4. mix (produced according to the real proportions of forest – 72.4% stem, 14.5% branches and 13.1% for leaves). The tests were conducted in the Laboratory of Bioenergy and Lignocellulosic Materials at the Federal University of São Carlos in Sorocaba-SP, Brazil.

2.2. Physical tests

The physical characterization was carried out with the following tests: particle size distribution by sifting on 40–200 mesh screens, bulk density of raw materials at dry-air moisture content, briquettes density and expansion (volumetric, axial and radial) at 12% of moisture content. The briquette density was determined by the ratio of the mass and volume, and the dimensions measurements were obtained within an accuracy of 0.001 mm. The expansions were evaluated at 0, 4, 12, 24, 48 and 120 h after production of briquettes. They were maintained in plastic bags throughout this period of the test to avoid humidification.

2.3. Chemical tests

The higher heating value (HHV) was obtained by calorimeter, and the lower heating value (LHV) was estimated according to CEN 14918 (2005) using default values found in the Annexure H. Also, the energetic density of briquettes was obtained product-wise between stabilized briquette density and lower heating value. The volatile matter (ASTM E872-82, 2006), ash (ASTM D1102-84, 2007) and fixed carbon (summation of percentage moisture, ash and volatile matter subtracted from 100) were also obtained. All chemical properties were determined in triplicate.

2.4. Mechanical tests

The briquettes were mechanically tested in diametrical compression according to NBR 7222 (2011). A computer-controlled electro-mechanical testing machine EMIC DL30000 (Fig. 1) with 5 kn load cell was used.

Additionally, friability tests were carried out in five samples using a dustproof rotating drum (internal dimensions: 300 mm × 300 mm × 100 mm) with 35 rpm during 15 min, resulting in 500 spins. After the procedure, the material was removed from the drum and separated by a sieve with a mesh aperture of 6.3 mm. The material retained on the sieve was weighed. This property is commonly used to evaluate any mechanical action which mainly takes place during transportation, handling and storage of briquettes (Kaliyan and Morey, 2009; Mkini and Bakari, 2015).

2.5. SEM-EDS analysis of ashes from SRC biomass

Owing to relevant importance of ash in the industrial process, qualitative and quantitative analyses were realized using a scanning electron microscope (SEM) of Hitachi model TM3000, equipped with an energy-dispersive spectroscopy detector (EDS).

Ten positions, randomly for each sample fraction, were captured with 500× zoom and 15 kV potential difference in EDS mode operation, and the chemical elements were identified by Quantax 70 software.

2.6. Statistical methods of analysis

Basic statistics (central tendency and dispersion) were used in the reporting of properties and SEM-EDS analysis.

The treatments were evaluated by analysis of variance, complemented by a Tukey test (significant at $p < 0.05$). It was used the software R (R Development Core Team, 2013).



Fig. 1. Briquettes samples and diametrical compression test.

Download English Version:

<https://daneshyari.com/en/article/5761874>

Download Persian Version:

<https://daneshyari.com/article/5761874>

[Daneshyari.com](https://daneshyari.com)