

Synthesis of pillared bentonite starting from the Al–Fe polymeric precursor in solid state, and its catalytic evaluation in the phenol oxidation reaction

Nancy Sanabria, Andrea Álvarez, Rafael Molina, Sonia Moreno^{*}

Grupo Estado Sólido y Catálisis Ambiental, Departamento de Química, Facultad de Ciencias, Universidad Nacional de Colombia, Carrera 30 No. 45-03, Bogotá, DC, Colombia

Available online 19 February 2008

Abstract

A new methodology for the modification of a bentonite via pillaring was evaluated in this work, employing a mixed Al–Fe polyhydroxocation and clay powder, placing the two solid materials in contact into a dialysis membrane. The modified solids were characterized by X-ray diffraction (XRD) and elemental chemical analysis and their catalytic activity is probed on the phenol oxidation reaction in diluted aqueous phase. The results show that pillared clay with the solid Al–Fe polyhydroxocation has similar properties to the solid modified by the conventional method, which involves the use of a large quantity of water in the synthesis (clay suspension 2% and dilute pillaring solution). The catalytic tests with the modified solids show, in all cases, 100% of phenol conversion after 2 h and total organic carbon (TOC) elimination between 49 and 53%, in 4 h of reaction, results which can be compared with pillared bentonite from diluted suspensions.

© 2007 Elsevier B.V. All rights reserved.

Keywords: Al–Fe polyhydroxocation; Pillared clays; Catalytic wet peroxide oxidation

1. Introduction

Barrer and MacLeod (1955) were the first to introduce the concept of transformation of laminar solids in porous structures by the insertion of molecules in the laminar spacing of clay-like minerals of the smectite type. The terms “pillared” and “pillaring” originated from the works of Brindley and Semples (1977) and Vaughan and Lussier (1980), who found that inorganic robust molecules could be intercalated between layers in clays through an ionic exchange mechanism, followed by the removal of the solvent [1]. During calcination, the metal polyhydroxocation is transformed into an oxide which fixes itself to the clay in a strong manner [1–3]. The introduction of pillars, besides increasing the material’s resistance and stability, provides porosity, a greater surface area, access to acid areas existing in natural clay, and the presence of potentially active species for a specific reaction [4,5].

The pillared clays synthesis method (PILC’s) at the laboratory level is essentially based on the mixture of a clay diluted suspension (2%) with a pillaring solution, a process generally involving considerable time and high volumes of water [6]. So that the pillaring process can be scaled at the industrial level, simplification of the procedures and optimization of the unitary operations involved are required, particularly the reduction in the water volume.

The current trend in the pillaring process focuses on the synthesis of concentrated suspensions, both for clay and for the pillaring agent. Schoonheydt and Leeman synthesize Al-saponite through the addition of clay dust to the aluminium pillaring solution [7]. Storaro et al. use a solid pillaring agent (solid chlorhydrol) and clay suspensions in acetone [8]. Recently, Vicente and Lambert have described a new synthetic pillaring path, by using a dialysis membrane, clay dust and small volumes of a pillaring solution [9]. Aouad et al. have developed a procedure for the pillaring of clays with aluminium, which minimizes the time of the process and the amount of water used, allowing for its extension to the industrial level. To simplify the Al-PILC synthesis, natural clay is used without purifying, besides solid Al₁₃ nitrate, both

^{*} Corresponding author.

E-mail address: smorenog@unal.edu.co (S. Moreno).

contained in a dialysis membrane. The solid pillared through this method has similar characteristics to the one synthesized by the conventional method using diluted suspensions [6].

On the other hand, clays modified with mixed pillars offer a great potential as catalysts in several reactions of environmental interest, due to the possibility of introducing metal cations with properties leading to the desired reaction. In this way, recent works point out the possibility to eliminate highly refractory compounds at room temperature and atmospheric pressure, by using hydrogen peroxide as an oxidizing agent, whose activation is catalyzed by Fe in a clayish matrix [10,11]. Research on the treatment of industrial wastewaters has been reinforced in the past few years, particularly regarding low cost methods for their recuperation. Catalytic wet peroxide oxidation (CWPO) is one of the most promising emerging processes for the treatment of waters polluted by organic matter [12–14].

In this work, the synthesis of mixed Al–Fe polyhydroxocations in solid state was made as an extension to the method developed by Furrer et al. for the aluminium polymer [15], but including iron as a second cation. The intercalation of clay dust and the mixed pillaring agent in the previously synthesized solid form was performed in a dialysis membrane, following a procedure similar to the one used by Aouad et al. [6]. The solids obtained were characterized by chemical analysis and X-ray diffraction, and the catalytic activity was assessed in the phenol oxidation reaction in aqueous phase. In addition, the Fe content in the leaching of the reactions was quantified by atomic absorption.

2. Experimental

2.1. Synthesis of the Al–Fe polyhydroxocation

The polymeric precursor in aqueous solution was prepared based on the procedure described by Raythatha et al., according to which discrete species are formed with the formula $[Al_xFe_y(OH)_{24}]Cl_7$, where x and y depend on the Al and Fe proportion [16]. Starting from $AlCl_3 \cdot 6H_2O$, $FeCl_3 \cdot 6H_2O$ and Na_2CO_3 three solutions were prepared with the following proportion: $[Al_{12.5}Fe_{0.5}(OH)_{24}]Cl_7$, $[Al_{11.7}Fe_{1.3}(OH)_{24}]Cl_7$ and $[Al_{10}Fe_{3.0}(OH)_{24}]Cl_7$ with 3.9, 10 and 23% molar Fe, considering the molar ratio as $100n_{Fe}/(n_{Fe} + n_{Al})$ and a hydrolysis ratio $OH/metal = 2.0$. The three aqueous solutions of discrete species were submitted to the process of crystallization with Na_2SO_4 and $Ba(NO_3)_2$, according to the methodology proposed by Furrer et al. for obtaining Al_{13} nitrate [15].

2.2. Synthesis of pillared clays

The starting clay is a commercially available, natural bentonite issued from Valle del Cauca, Colombia, provided by Bentocol (Colombia), which has been previously separated by particle size ($<2 \mu m$) and homoionized with a 0.5 M solution of calcium chloride [17,18]. The homoionized clay dust and the Al–Fe polyhydroxocation in powder are mixed and placed in

the dialysis membrane (Spectra/Por, flat width 45 ± 2 mm, diameter 29 mm) in a ratio of 2 g of the blend per 1 cm of the membrane. The clay and Al–Fe polymeric precursor ratio used in the synthesis of all solids was 20 mequiv. metal/g clay. The membrane is then put into a beaker with the minimum quantity of distilled water to cover it, and the whole system is kept under constant agitation for 60 h not allowing any contact between the agitator and the membrane. Then, six washings with distilled water are performed in the same container where intercalation took place until conductivity is lower than $20 \mu S/cm$. The intercalated clay suspensions are dried at $60^\circ C$ for 48 h, then sifted through a 100 mesh and then calcinated at up to $400^\circ C$, with a heating ramp of $100^\circ C/h$ and for 2 h at $400^\circ C$.

The solids obtained are labelled: B1–AlFe, B2–AlFe and B3–AlFe, where B refers to bentonite; 1, 2 and 3 refer to the three mole ratios of Fe/metal used in the Al–Fe polymer synthesis (3.9, 10 and 23%). As a reference material, natural bentonite calcinated at $400^\circ C$ is taken, whose chemical analysis and catalytic behavior have been documented in the existing literature [10,11].

2.3. Characterization of the solids

The X-ray diffraction analysis is carried out by means of a Bruker D8 Advance diffractometer (Cu $K\alpha$ radiation) in Bragg–Brentano geometry, graphite secondary monochromator, steps of $0.05^\circ 2\theta$ at 2 s/step. The chemical analysis was performed by X-ray fluorescence (Philips MagiX Pro PW2440, samples prepared in pearls).

2.4. Catalytic evaluation

Solids modified with the solid Al–Fe polymeric precursor were evaluated in the phenol oxidation reaction in diluted aqueous medium according to the catalytic test procedure reported in prior works [12,13], using a 5×10^{-4} M phenol solution, 0.5 g catalyst, a solution of hydrogen peroxide 0.1 M and pH 3.7. Monitoring of the phenol conversion in time and the appearance of subproducts in the oxidation reaction are carried out by high performance liquid chromatography (HPLC) by means of a Hitachi D-7000 (LaChrom) appliance fitted with a self sampler L-7200, using an RP-18 Lichrosphere 60 Select B column, absorbance detector UV–vis L-7400 and as a mobile phase, a mixture of water, H_3PO_4 and methanol [19]. To assess the selectivity of catalysts towards CO_2 and H_2O , total organic carbon analysis was used (TOC), by means of an AnaTOC piece of equipment.

3. Results and discussion

Through chemical analysis by X-ray fluorescence, the effective incorporation of Al and Fe in the modified solids was established (Table 1). In general, the higher the content of Fe used in the synthesis, the greater the amount of this metal incorporated to the final solid.

X-ray diffraction patterns for the three modified solids (Fig. 1) reveal the effective introduction of the metal

Download English Version:

<https://daneshyari.com/en/article/58313>

Download Persian Version:

<https://daneshyari.com/article/58313>

[Daneshyari.com](https://daneshyari.com)