




ELSEVIER

Contents lists available at ScienceDirect

Chemical Engineering Science

journal homepage: www.elsevier.com/locate/ces

A computational study of short-range surface-directed phase separation in polymer blends under a linear temperature gradient




Mohammad Tabatabaieyazdi, Philip K. Chan*, Jiangning Wu

Department of Chemical Engineering, Ryerson University, 350 Victoria Street, Toronto, Ontario, Canada M5B 2K3

HIGHLIGHTS

- Model composed of Cahn–Hilliard and Flory–Huggins–deGennes theories is solved.
- Growth is fastest in the early stage of phase separation.
- Thickness of the wetting layer increased with increasing temperature.
- Transition time occurs earlier with higher surface potential.
- Spinodal wave became more visible in the bulk as the surface potential increased.

GRAPHICAL ABSTRACT



ARTICLE INFO

Article history:

Received 29 January 2015

Received in revised form

13 June 2015

Accepted 14 July 2015

Available online 26 July 2015

Keywords:

Surface-directed phase separation

Spinodal decomposition

Polymer blend

Surface potential

Wetting

Morphology development

ABSTRACT

The nonlinear Cahn–Hilliard theory and the Flory–Huggins–deGennes theory were used to study numerically the surface-directed phase separation phenomena of a model binary polymer blend quenched into the unstable region of its binary symmetric upper critical solution temperature phase diagram. Short-range surface potential within a square geometry, where one side of the binary polymer blend is exposed to a surface with preferential attraction to one component of the blend that is under a linear temperature gradient along the direction perpendicular to the surface, was integrated into the model. The structure factor analysis showed a faster exponential growth at the early stage of phase separation and a slower growth rate at the intermediate stage with a slope of 0.31 within the bulk, which is consistent with the Lifshitz–Slyozov growth law. The investigation of surface enrichment rate at the surface wall demonstrated faster growth rate at the early stage with the slope of 0.5. This growth rate became slower at the intermediate stage with a slope of 0.13 near the surface. The effect of various temperature gradient values on the surface enrichment rate with constant temperature T_1^* at the surface preferentially attracting one of the polymer components and different temperature T_2^* at the opposite surface, where $T_1^* > T_2^*$, was studied for the first time. The results showed that the thickness of the wetting layer increased with increasing temperature difference ΔT^* , where $\Delta T^* = T_1^* - T_2^*$. The structure factor analysis of the surface potential h_1 effect on the phase separation within the bulk close to the surface showed earlier transition time for higher values of h_1 . However, there was no difference observed for transition time within the bulk at distances farther away from the surface. As the surface potential increased, spinodal wave became more visible in the bulk and the transition time from complete wetting to partial wetting occurred at a later time on the surface.

© 2015 Elsevier Ltd. All rights reserved.

* Corresponding author.

E-mail address: p4chan@ryerson.ca (P.K. Chan).

1. Introduction

The surface-directed phase separation (SDPS) mechanism has attracted much attention and has been intensively studied (Jones et al., 1991; Krausch et al., 1994; Geoghegan et al., 1995, 2000; Brown and Chakrabarti, 1992; Puri and Binder, 1992; Henderson and Clarke, 2005; Yan and Xie, 2006a,b). The presence of a surface may alter the course of phase separation by spinodal decomposition in polymer blends by breaking translational and rotational symmetry. SDPS in polymer blends at a range of conditions could lead to a variety of structural morphology. Therefore, it is important to understand the phase separation behavior of polymeric materials and also the effect of different external fields (such as surface effect and temperature gradient) that could lead to the formation of structural anisotropy in polymer blends and could help produce new products with enhanced property and functionality. The adsorption of polymers onto surfaces, whether preferred or not, has great consequences in polymer product formation. Moreover, understanding and controlling such processes is significant and is necessary in many technological features varying from paper industry and paint formulation to pharmaceutical applications (Dalmoro et al., 2012; Evans and Wennerstrom, 1999), biophysics (Norde, 2003; Gray, 2004; Yaseen et al., 2008), and nanocomposite materials (Mishra et al., 2013; Ramanathan et al., 2008).

Phase separation induced through a temperature jump (for polymer blends with a lower critical solution temperature) or quench (for polymer blends with an upper critical solution temperature) into the unstable region of the phase diagram is known as thermally-induced phase separation (TIPS). Phase separation in the TIPS method occurs via spinodal decomposition (SD); this particular process of phase separation does not require an activation energy and proceeds spontaneously in the presence of minimal concentration fluctuations or thermal noise (Cahn, 1965).

Phase separation of polymer blends can lead to different morphologies, such as the bi-continuous interconnected structure and the droplet-type morphology when altering the system characteristics such as the composition, molecular weight and structure, film thickness, solvent, or changes in the exterior environment, including the substrate, pressure, temperature, and external fields. This offers a means to create patterns in polymeric materials by controlling the phase separation conditions in thin polymer blend films.

The first experimental observation of surface-directed phase separation (SDPS) via spinodal decomposition (SDPS) was reported by Jones et al. (1991). They found that in a poly(ethylenepropylene) and perdeuterated poly(ethylenepropylene) blend there is a preferential attraction of the latter component to the surface, and that phase separation by spinodal decomposition occurs with a wavevector normal to the surface which extends for some distance into the bulk. Since then, there have been numerous experimental (Krausch et al., 1994; Geoghegan et al., 1995, 2000) and numerical (Krausch et al., 1994; Henderson and Clarke, 2005; Yan and Xie, 2006a,b) work published on the SDPS of polymeric materials with various polymers and processing conditions.

Krausch et al. (1994) studied the SDPS in a symmetric poly(ethylenepropylene) and perdeuterated poly(ethylenepropylene) blend with off-critical concentrations. They found experimentally that the growth rate of the wetting layer grows slower if the minority phase wets the surface, while the reverse is true if the majority phase wets the surface. Furthermore, their numerical studies indicate that this growth rate follows the $t^{1/3}$ diffusive scaling law when the majority phase wets the surface. Geoghegan et al., (1995, 2000) studied the quench depth effect of the SDPS in a deuterated polystyrene and poly(α -methylstyrene) blend. They found that the growth law of the surface wetting layer follows $t^{1/3}$ for the deepest quenches, while the growth law is logarithm with time for the shallower quenches.

Brown and Chakrabarti (1992) studied numerically the SDPS in a two-dimensional model incorporating the Cahn-Hilliard-Cook

theory for spinodal decomposition and a free energy functional composing of the Ginzburg-Landau free energy and a long range surface interaction term. They found that the thickness of the wetting layer varies with $t^{1/3}$. Moreover, although the length scales $l(t)$ in the direction parallel and perpendicular to the surface are different, they both scale as $l(t) \sim t^{1/3}$. Puri and Binder (1992) used the Cahn-Hilliard equation derived from a semi-infinite model with Kawasaki spin exchange dynamics to study the SDPS. Their numerical results confirm that there exists a concentration wave growing with wavevector perpendicular to the surface. Henderson and Clarke (2005) model the SDPS in a symmetric polymer blend using a model composed of the Cahn-Hilliard-Cook theory for phase separation and the Flory-Huggins-de Gennes free energy. They concluded that to model the SDPS and to be capable of replicating experimental observations, only one length scale should be used. Yan and Xie (2006a,b) simulated the SDPS in a polymer system by cell dynamic system. For the case of short range potential, they found that the wetting layer grows according to the logarithmic growth law if the noise term is absent, while it will grow according to the Lifshitz-Slyozov 1/3 growth law if the noise term is present. Furthermore, the length scale parallel to the surface also obeys the Lifshitz-Slyozov 1/3 growth law as well. They also found that the thickness of the wetting layer and degree and speed of phase separation all increase with surface potential.

According to the authors' knowledge of published work, the temperature has always remained constant during the SDPS in polymeric materials. Lee et al. (2002, 2003, 2004) and Hong and Chan (2010) studied numerically the effect of a temperature gradient on the thermal-induced and polymerization-induced phase separation processes in polymer solutions. The presence of a temperature gradient during phase separation by spinodal decomposition significantly alters the transient morphology being formed. Temperature gradients inherently exist during the fabrication of polymeric products, such as in the extrusion, and injection molding and blow molding processes. Moreover, temperature gradients may be introduced deliberately in the phase separation process to strategically achieve a graded morphology which is required in product specifications. In this present paper, we present and solve a mathematical model composed of the Cahn-Hilliard (CH) theory for spinodal decomposition (Cahn, 1965) and the Flory-Huggins-de Gennes (FHdG) free energy function (deGennes, 1980; Flory, 1953). The model also incorporates the following two external forces: (1) a surface with short-range surface potential, and (2) a linear temperature gradient normal to the surface. The wetting layer formation mechanisms on the surface and morphology development and evolution are examined under different conditions. The results are presented and discussed in the form of morphology formation and surface enrichment growth rate. The effects of diffusion coefficient, quench depth, temperature gradient and surface potential on the surface enrichment are as well investigated.

2. Model development

This section explains the model development for the thermal-induced SDPS method in a binary polymer blend, involving a short-range surface potential field and an externally imposed spatial linear temperature gradient. This model is developed using the nonlinear CH theory for spinodal decomposition (Cahn, 1965) and the FHdG free energy (deGennes, 1980; Flory, 1953). The CH theory is derived using the following continuity equation:

$$\frac{\partial c}{\partial t} = -\nabla \cdot \mathbf{j} \quad (1)$$

where c is the concentration of the solvent taken as volume fraction in this paper, and \mathbf{j} is the interdiffusional flux. The flux

Download English Version:

<https://daneshyari.com/en/article/6589566>

Download Persian Version:

<https://daneshyari.com/article/6589566>

[Daneshyari.com](https://daneshyari.com)