



Full Length Article

Chemo-morphological coupling during serpentine heat treatment for carbon mineralization

Meishen Liu, Greeshma Gadikota*

Department of Civil and Environmental Engineering, Environmental Chemistry and Technology Program, Geological Engineering Program, Grainger Institute for Engineering, University of Wisconsin-Madison, Madison, WI 53706, United States

ARTICLE INFO

Keywords:

Serpentine
Heat treatment
X-ray scattering
Morphology
Crystal structure

ABSTRACT

One of the safest and permanent routes for potentially capturing and storing CO₂ is via carbon mineralization which involves converting CO₂ into environmentally benign and thermodynamically stable calcium and magnesium carbonates. One of the most abundant Mg-bearing minerals in the world suitable for carbon mineralization is serpentine (Mg₃Si₂O₅(OH)₄). To enhance the reactivity of serpentine with CO₂, dehydroxylation by heating to temperatures in the range of 600 °C–700 °C was proposed. To establish a fundamental structural and morphological basis for the enhanced reactivity of serpentine (e.g. lizardite) on heating to temperatures in this range, *in-operando* synchrotron multi-scale X-ray scattering measurements were performed, with complementary analyses of the changes in the porosity, particle size, and surface morphology. The detailed transformation of lamellar serpentine to a pseudo-amorphous state on heating to temperatures in the range of 600 °C–700 °C, and the subsequent conversion to denser crystalline phases such as Al_{2.35}Si_{0.64}O_{4.82} (mullite), SiO₂ (cristobalite), Mg₂SiO₄ (forsterite), and Fe_{0.3}Mg_{0.7}(SiO₃) (enstatite) was determined from the wide and small angle X-ray scattering measurements. Increasing roughness of the pore-solid interface on heating to 700 °C followed by enhanced smoothness due to the formation of crystalline phases at higher temperatures was established from the combined ultra small and small angle X-ray scattering measurements. The transformation of lamellar lizardite to its pseudo-amorphous state corresponded to an increase in the porosity and surface area, while the formation of crystalline phases reduced the porosity and surface area while increasing the particle size.

1. Introduction

One of the challenges at the forefront of sustainable energy production is the safe and permanent capture and storage of CO₂ with potential for utilization. One option is to capture and convert CO₂ into calcium and magnesium carbonates using earth-abundant calcium and magnesium-bearing silicates as the sources of alkalinity [1–9]. Serpentine (Mg₃Si₂O₅(OH)₄) is one example of an earth-abundant hydrated magnesium silicate mineral that has been extensively studied for carbon mineralization [2,4,10–15]. Various routes for serpentine carbonation have been explored including the conversion of CO₂ and serpentine into magnesium carbonate via direct gas-liquid-solid routes [2], or accelerated extraction of Mg followed by magnesium carbonate precipitation [4,13].

To accelerate the kinetics of CO₂ conversion to magnesium carbonate, the thermal activation of serpentine was proposed. Thermal activation of serpentine to temperatures up to 700 °C dehydroxylates the crystal lattice resulting in a more reactive amorphous material [16]. Previous studies reported carbonate conversions of heat-treated

serpentine as high as 73.5% at 185 °C, P_{CO2} of 150 atm in 1.0 M NaCl + 0.64 M NaHCO₃ on reaction for 1 h [17]. More recent studies reported using flue gas concentrations for successfully converting heat-treated serpentine to magnesium carbonate [11,18]. Despite significant research efforts directed towards converting heat-treated serpentine to magnesium carbonate, there is a limited fundamental understanding of the structural and morphological changes that occur in serpentine on heating and the influence of these changes on the reactivity of the mineral.

While McKelvy and co-workers evaluated the changes in the structure of heat-treated serpentine using X-ray diffraction (XRD) and Fourier transform infrared spectroscopy (FTIR) analyses [19], the corresponding morphological changes such as the porosity, pore-solid interfacial structure, and the surface area were not reported. Recent advances in synchrotron radiation have now allowed us to probe the changes in the morphologies and structures of porous materials from the angstrom to the micrometer-scale using ultra small, small, and wide angle X-ray scattering (USAXS/SAXS/WAXS) measurements [20–23]. In the case of serpentine, the changes in the lamellar structure and the

* Corresponding author.

E-mail address: gadikota@wisc.edu (G. Gadikota).

Table 1
Composition of lizardite.

Components	Weight%	Components	Weight%
MgO	37.00	MnO	0.10
CaO	0.42	Na ₂ O	0.04
Fe ₂ O ₃	8.09	K ₂ O	< 0.01
SiO ₂	38.90	TiO ₂	0.04
Cr ₂ O ₃	0.40	P ₂ O ₅	< 0.01
Al ₂ O ₃	1.79	V ₂ O ₅	0.02
		LOI%	13.20

interlayer basal spacing [24] were determined using wide angle X-ray scattering (WAXS) and small angle X-ray scattering (SAXS) measurements. Ultra small angle X-ray scattering (USAXS) measurements in conjunction with Brunauer–Emmett–Teller (BET) porosity measurements and particle size analyses were used to determine the morphological changes in serpentine on thermal treatment.

2. Experimental methods

The serpentine morph used in this study was lizardite. The chemical composition of the unreacted lizardite listed in Table 1 was determined using Wavelength Dispersion X-ray Fluorescence (WD-XRF, Pananalytical Axios, The Netherlands). The mean particle size, surface area and cumulative pore volume of the ground unreacted serpentine were found to be 10.80 μm, 36.3 m²/g and 0.115 ml/g, respectively. In addition to lizardite, the other major phase present was identified as quartz (Fig. S1).

2.1. Heat treatment of serpentine

To determine the *in-operando* structural and morphological changes in serpentine on heat treatment, USAXS/SAXS/WAXS measurements were performed at Sector 9-ID at Advanced Photon Source (APS) in Argonne National Laboratory (ANL), Argonne, IL. Lizardite was prepared by grinding the material to a size smaller than 100 μm followed by compaction into pellets. The thickness of the pellet used in this experiment was 1 mm (± 0.2 mm). The heat treatment of the lizardite-bearing serpentine was performed by placing the pellet in a Linkam TS1500 heating stage (Linkam Scientific Instruments Ltd., Tadworth, UK) with temperature control of ± 0.1 °C. The temperature ramp rate was set at 3.3 °C/min and the temperature range was from 30 °C to 1150 °C. The heater was then aligned with the USAXS/SAXS/WAXS instrument at Sector 9-ID.

The USAXS/SAXS instruments are based on the original Bonse-Hart double-crystal configuration, which used multiple dispersive reflections from perfect crystals to reach a region of scattering vector q , where $q = (4\pi/\lambda)\sin\theta$, λ is the wavelength of the X-ray, and 2θ is the scattering angle [25,26]. All measurements (USAXS/SAXS/WAXS) could be made within about 3 min, reducing uncertainties bringing by the change of sample configuration within the beam [26]. The total X-ray flux of the measurement was 10^{-13} photon s⁻¹. The wavelength of the X-ray used in the experiment was 0.59 Å, which corresponded to the energy of 21.0 keV. Calibrations were made using silver behenate and the NIST standard reference material, SRM 640d (Si). Collected data were reduced and analyzed by the Irena and Nika software packages embedded in IgorPro (Wavemetrics, Lake Oswego, OR) [26–28].

Several complementary measurements were performed to complement the scattering measurements. Powdered lizardite was thermally treated to 350 °C, 650 °C, 900 °C, and 1150 °C in an oven for 3 h for determining the changes in the porosity, surface area, surface morphology and particle size on heating. The changes in the porosity and the specific surface area of the powdered lizardite on heating were determined using the BET technique (Quantachrome Autosorb1 Analyzer), while particle size distributions were determined via a laser

diffraction method (Beckman Coulter, Inc., LS 13 320 MW). The surface morphological features were determined using a scanning electron microscopy (SEM, Hitachi High Technologies America, Hitachi S3400-N). The changes in the weight of the sample on heating was determined using thermogravimetric analysis (TGA, TA Instruments TGA550).

3. Results and discussion

3.1. Structural changes in lizardite on thermal treatment

Heating lamellar structures such as lizardite produced several changes across the material hierarchy. One of the characteristic features of hierarchical materials is the interlayer basal spacing which was observed in the SAXS regime. The interlayer space is the distance between the silicate layers in case of lizardite. One measure of the interlayer space is the basal reflection or the d (001) peak corresponding to the scattering from one hydrated magnesium silicate nanosheet and the interlayer space. The position and the intensity of the characteristic interlayer peak indicate the distance corresponding to the interlayer space and the quantity of interlayer nanopores, respectively. The interlayer basal reflection is a characteristic of other hierarchical natural materials such as clays [29,30].

In swelling clays such as Na- or Ca-montmorillonite, the interlayer basal spacing changes with the layers of intercalated water in these regions [21,26,27], unlike in non-swelling clays such as kaolinite [22]. In swelling clays bearing intercalated water, a reduction in the interlayer basal spacing is noted on heating to 150 °C [21,26,27]. Unlike swelling clays, phyllosilicates such as lizardite do not contain intercalated water. On heating to 150 °C, no significant changes in the positions of the d (001) or d (002) peaks or their intensities were noted (Figs. 1 and S2). This observation is attributed to the absence of the characteristic ability to shrink or swell due to the loss or gain of water, and no structural changes in the hydrated magnesium silicate nanosheet (see Fig. S3 which represents d (202) reflection in lizardite).

Further heating above 550 °C reduced the intensity of the interlayer basal reflection with the peak disappearing on heating to 825 °C. This observation is consistent with previous studies reporting changes in the lamellar structure of lizardite to an amorphous form due to the removal of –OH groups [16,19,31]. Thermogravimetric analyses of untreated lizardite showed the onset of weight loss around 500 °C with near complete loss achieved on heating to 825 °C which corresponds to lizardite dehydroxylation (Fig. 2). Various lizardite samples were also heat-treated at 350 °C, 650 °C and 900 °C in an *ex-situ* environment prior to thermogravimetric analyses. Heat treatment of lizardite at 350 °C did not change the weight of the sample significantly compared to the untreated serpentine. On heating to 650 °C, a weight loss of 2.25% was observed suggesting the presence of residual –OH groups. No significant changes in the weight of the sample were noted on heating to 900 °C suggesting the complete removal of –OH groups at those conditions. The observations of the changes in the weight of serpentine due to dehydroxylation in Fig. 2 are consistent with the loss in the crystalline structure of serpentine noted in Figs. 1, S2 and S3. In the context of carbon mineralization, the structural disorder achieved due to serpentine dehydroxylation on heating to temperatures in the range of 600 °C–700 °C was noted as a factor in accelerating carbon mineralization behavior [19].

On heating serpentine beyond 650 °C, the recrystallization of amorphous serpentine to denser phases was observed. The onset of Al_{2.35}Si_{0.64}O_{4.82} (mullite), SiO₂ (cristobalite), Mg₂SiO₄ (forsterite), and Fe_{0.3}Mg_{0.7}(SiO₃) (enstatite) phases was observed in the range of 700 °C–800 °C in the WAXS regime [32–35]. These observations are consistent with previous studies that reported a strong exotherm at 782 °C indicating the onset of new phase formation [19]. The intensity of these phases increased on further heating suggesting the growth of these phases (Fig. 3). These phases are indexed in serpentine heat-treated at 1150 °C (Fig. S4). The respective densities of mullite,

Download English Version:

<https://daneshyari.com/en/article/6630828>

Download Persian Version:

<https://daneshyari.com/article/6630828>

[Daneshyari.com](https://daneshyari.com)