



Existing cell wall fragments modify the thermal properties and hydrolysis of potato starch

Jinhu Tian^a, Shiguo Chen^a, Huiling Zhang^b, Haitian Fang^b, Yujing Sun^c, Donghong Liu^a, Robert J. Linhart^d, Xingqian Ye^{a,*}

^a Department of Food Science and Nutrition, Zhejiang University, Hangzhou, 310058, China

^b Ningxia Key Laboratory for Food Microbial-Applications Technology and Safety Control, Ningxia University, Yinchuan, 750021, China

^c Department of Food Science and Technology, Ocean College, Zhejiang University of Technology, Hangzhou, 310014, China

^d Center for Biotechnology & Interdisciplinary Studies, Department of Chemistry & Chemical Biology, Rensselaer Polytechnic Institute, Biotechnology Center 4005, Troy, NY, 12180, USA

ARTICLE INFO

Keywords:

Potato
Cell wall fragments
Morphology
Thermal property
Hydrolysis

ABSTRACT

The effect of cell wall fragments on the thermal properties and hydrolysis of potato starch were investigated. The relative degree of crystallinity of purified starch and starch with cell wall fragments were 19.7% and 20.7%, respectively. The onset temperature (T_o) and peak temperature (T_p) of the starch with cell wall fragments were much higher than those of purified starch, whereas the ΔH value of purified starch (9.5 ± 0.5 J/g) was much higher than that of the starch with cell wall fragments (7.6 ± 0.7 J/g). Moreover, slightly lower equilibrium hydrolysis of starch with cell wall fragments ($78.8 \pm 6.3\%$) and different morphologies changes between those two samples during heating were also observed. Our study demonstrated that it might be an alternative way to improve or extend the property of potato starch with the remaining of its cell wall fragments.

1. Introduction

Potato (*Solanum tuberosum* L.) has been widely planted and consumed around the world as an important source of carbohydrate in human diet (Singh, Kaur, & Moughan, 2012). However, processed potato also has a high content of rapid digested starch (RDS), and is classified as a food having an intermediate or a high glycemic index (GI). Thus, the long-term consumption of processed potato is considered a potential contributor to hyperglycemia, type II diabetes, and other chronic diseases (Ek, Brand-Miller, & Copeland, 2012). A number of studies have looked into ways of decreasing the GI of the potato and the results of such studies have demonstrated that the GI could be affected by multiple factors, including cultivars, maturity, starch structure, amylose content, and cooking methods (Nayak, De J. Berrios & Tang, 2014). Current studies aimed at reducing the GI of the potato are mainly focused on the cooking/processing methods or improving the amylose content through transgenic engineering (Tian, Chen, Chen, & Ye, 2016a). Few studies have examined whether the cell wall can affect the digestibility of potato starch. The cell wall, which is mainly comprised of cellulose and hemicellulose, is the second most important component of potato, followed only by starch (Bordoloi, Kaur, & Singh, 2012). In the raw potato, the cell wall forms a honeycomb structure in

which small starch granules are embedded. The cell wall might impede the water swelling of starch during gelatinization or play as a barrier to reduce the contact between enzymes and starch during its digestion (Tian et al., 2018). Frost et al. (2016) analyzed the effect of composition and structure of tuber cell walls on the digestibility of potato and found that the higher amounts of RG-I galactan in potato cell walls could impede access of digestive enzymes to potato starch effectively. However, whether the cell wall will affect the crystallinity degrees as well as the thermal properties of potato starch have not been well studied, thus a better understanding of the impact of the cell wall on the thermal properties and digestibility of potato is needed.

With the aim of making up the insufficiency of the current studies, the thermal properties and crystal forms of purified potato starch and potato starch with cell wall fragments were analyzed using a DSC and X-ray diffraction. An enzyme hydrolysis experiment was also undertaken, and the microstructural changes of starch granules and starch with cell walls, incubated in water at different temperatures (60 °C and 90 °C), were also examined by scanning electron microscopy (SEM).

* Corresponding author.

E-mail address: psu@zju.edu.cn (X. Ye).

<https://doi.org/10.1016/j.foodhyd.2018.07.033>

Received 18 May 2018; Received in revised form 18 July 2018; Accepted 19 July 2018

Available online 20 July 2018

0268-005X/ © 2018 Elsevier Ltd. All rights reserved.

2. Material and methods

2.1. Materials and chemicals

Potato tubers (*Xiapodi sp.* of similar size and weight 200–230 g) were purchased from a local supermarket in Hangzhou, China. Porcine pancreatic α -amylase (900 U/mg) and invertase (Invertase, grade VII from baker's yeast, 401 U/mg solid) were purchased from Sigma-Aldrich Ltd. (St Louis, USA). Amyloglucosidase (3260 U/ml), total starch assay kit and glucose oxidaseperoxidase (GOPOD) kit were purchased from Megazyme International Ireland Ltd. (Wicklow, Ireland). Other chemicals and reagents were analytical grade and purchased from Aladdin (Shanghai, China).

2.2. Preparation of potato starch and starch with cell wall fragments

The purified potato starch was prepared according to Frost et al. (2016) with some modification. Briefly, the peeled potatoes were cut into thin slices and immersed in a solution containing 20 mM sodium bisulfite and 10 mM citric acid for 2 h at room temperature to avoid browning. Then, the slices were blended and suspended in 500 mL water and filtered with gauze. The starch milk was allowed to sediment for 1.5 h, after which the supernatant were decanted and the starch precipitate was re-suspended in 500 mL water for three-times or more, decanting the supernatant each time. Starch was recovered by vacuum filtration with repeated washes, immersed in liquid nitrogen and freeze-dried ($-50\text{ }^{\circ}\text{C}$, pressure lower than 0.1 mBar) (FreeZone 6, Labconco, USA) for future analysis. Starch with cell wall fragments was prepared from potatoes that were peeled manually, cut into small cubes (1 cm^3) and immediately immersed in liquid nitrogen and freeze dried as mentioned above, the dried samples were ground using a commercial grinder (JYL-C022, Jiuyang, China), passed through a number 100 sieve and stored at $-80\text{ }^{\circ}\text{C}$ for future analysis.

2.3. Microscopy observation

One gram of purified potato starch, starch with cell wall fragments and intact potato tissues were mixed thoroughly with 25 mL of distilled water in a plastic tube respectively and maintained in a water bath at $60\text{ }^{\circ}\text{C}$ or $90\text{ }^{\circ}\text{C}$ for 20 min. The tubes were centrifuged at $1500 \times g$ for 3 min and the supernatants were decanted and the precipitates were collected and freeze dried. Finally, the samples were coated with gold (SCD 050, Balzers, Liechtenstein) and their microstructures were observed with a SEM (TM-1000, HITACHI, Japan).

2.4. X-ray diffraction analysis

X-ray measurements were made with an X-ray diffractometer (X'Pert PRO, PANalytical B.V., Netherlands). X-ray diffraction patterns were acquired at room temperature under the following conditions: 40 kV and 20 mA for the Cu-K α radiation source at a wavelength of 0.15418 nm; a scanning rate of $2^{\circ}/\text{min}$ in the scattering range (2θ) of $5\text{--}40^{\circ}$. Diffraction data were analyzed with Jade software (Version 6.5, Material Date, Inc. Livermore, California, USA). The crystallinity (X_c) was calculated as the ratio of $A_c/(A_c + A_a)$, where A_c and A_a are the areas of crystalline and amorphous phases, respectively (Tian et al., 2016b).

2.5. Analysis of thermal properties

The thermal properties of the samples were analyzed with a Modulated Differential Scanning Calorimeter MDS1 instrument (Mettler, Toledo, Switzerland). Detailed procedures for DSC measurements and analysis, described by Tian et al. (2016b), were used with some modifications. Briefly, 10 mg freeze-dried starch sample was accurately weighed, mixed with 20 μL of deionized water and

hermetically sealed in an aluminum pan. After equilibrating at room temperature ($25\text{ }^{\circ}\text{C}$) for 24 h, the pan was heated from $20\text{ }^{\circ}\text{C}$ to $100\text{ }^{\circ}\text{C}$ at a rate of $10\text{ }^{\circ}\text{C}/\text{min}$. An empty pan was also used as a reference and the onset temperature (T_o), peak temperature (T_p), Endset (T_c) and melting enthalpy (ΔH) were calculated using DSC software (Mettler, Toledo, Switzerland).

2.6. Hydrolysis analysis

The hydrolysis analysis was performed according to Gularte and Rosell (2011) with some modification. Briefly, certain samples were weighed, mixed with distilled water thoroughly and pre-incubated at $90\text{ }^{\circ}\text{C}$ for 30 min; the solutions were cooled down and maintained at $37\text{ }^{\circ}\text{C}$ in a water bath to analyze the hydrolysis of purified starch and starch with cell wall fragments. Porcine pancreatic α -amylase was added to obtain a final concentration of starch and α -amylase of 10 mg/mL and 0.33 U/mL, respectively. Five hundred microliters supernatant was collected at 5, 15, 30, 60, 90, 120, 150 min and diluted immediately in 2.5 mL of 95% ethanol to inactivate the enzyme. The mixture was centrifuged at $2000 \times g$ for 10 min. Supernatant (0.1 mL) was recovered and incubated with 0.5 mL amyloglucosidase/invertase solution (37.5 mg invertase and 1 mL amyloglucosidase dissolved in 100 mL of 0.05 M potassium acetate) for 10 min at $37\text{ }^{\circ}\text{C}$ to convert all the oligosaccharides and disaccharides produced during hydrolysis to glucose (Tamura, Singh, Kaur, & Ogawa, 2016). Glucose concentrations of the incubated mixtures were measured with a glucose oxidaseperoxidase (GOPOD) kit; the absorbance was measured with a spectrophotometer (UV-2550, Shimadzu, Japan) at 510 nm. And the kinetics of starch hydrolysis was modelled with a first-order equation (1) according to Goñi, Garcia-Alonso, and Saura-Calixto (1997), where C represents the hydrolysis percentage of starch at time t , C_{∞} is the equilibrium concentration of hydrolyzed starch and k represents the kinetic constant.

$$C = C_{\infty}(1 - e^{-kt}) \quad (1)$$

2.7. Statistical analysis

All the experiments were carried out in triplicate, and the results reported as mean value \pm standard deviation. One-way Analysis of Variance (ANOVA) was performed to determine significance between variables using an SPSS Program, version 20.0 (SPSS, IBM, US). Significant differences of means were determined by the Duncan's test at 95% ($p < 0.05$).

3. Results and discussion

3.1. Microstructure changes during heating

The microstructure of purified starch, starch with cell wall fragments and intact potato tissues are shown in Fig. 1. The potato starch granules showed oval shapes of various sizes (Fig. 1A). The samples of starch with cell wall fragments showed small starch granules aggregated together imbedded inside cell wall structures. Some of the cell walls were partly broken, possibly attributed to the grinding process, exposing some of the starch granules (Fig. 1B). In contrast to these microstructures, the intact potato tissues exhibited a compact cell structure with most of the small starch granules on the inside (Fig. 1C). These morphologies are consistent with previous reports (Blazek & Gilbert, 2010; Bordoloi et al., 2012).

When potato starch granules are heated in water at $60\text{ }^{\circ}\text{C}$, the granules swelled and fused together. Some small granules remained, indicating that the starch granules were only partly gelatinized (Fig. 1D). Similar changes were also observed in starch with cell wall fragments and intact potato tissues, but the sizes of the fused starch granules in those samples were much smaller (Fig. 1E and F). This

Download English Version:

<https://daneshyari.com/en/article/6985353>

Download Persian Version:

<https://daneshyari.com/article/6985353>

[Daneshyari.com](https://daneshyari.com)