



Multimethod quantification of Ag⁺ release from nanosilver

Madjid Hadioui, Simon Leclerc, Kevin J. Wilkinson*

Department of Chemistry, University of Montreal C.P. 6128, Succursale Centre-Ville Montreal, Canada H3C 3J7

ARTICLE INFO

Article history:

Received 15 August 2012

Received in revised form

21 November 2012

Accepted 22 November 2012

Available online 30 November 2012

Keywords:

Nanosilver

Free metal ion

Nanoparticles

Ion-exchange technique

Single particle ICP-MS

Centrifugal ultrafiltration

ABSTRACT

There is a significant interest in determining the effects of nanomaterials on the environment and human health. Part or all of the toxicity attributed to silver nanoparticles (nAg) may be due to the release of free silver (Ag⁺). Therefore, it is necessary to have techniques that will allow the precise determination of free Ag⁺ within suspensions of nAg particles. Among the different methods used for the determination of free metals in natural waters, the ion-exchange technique (IET), has promise to both distinguish Ag⁺ from nAg and to attain the low detection limits required for the analysis of natural samples. In this paper, IET, centrifugal ultrafiltration and single particle inductively coupled plasma mass spectrometry (SP ICP-MS) were used to determine very low concentrations of free or dissolved Ag in commercial suspensions of nAg. Dilution of the silver nanoparticles played an important role in the measured Ag⁺ concentrations. The relative release of Ag⁺ from nAg increased as samples were increasingly diluted, implying that it is critical to determine Ag⁺ concentrations under the precise conditions used for determinations of toxicological or environmental fate.

© 2012 Elsevier B.V. All rights reserved.

1. Introduction

The production and applications of nanomaterials are growing rapidly but their impacts on human health and the environment have not yet been determined unambiguously. Nanosilver (nAg) is among the most common nanomaterials found in consumer products. It is used in a variety of applications including medical, water treatment, cosmetics, clothing and the food industry.

Even though nAg is used for its antimicrobial properties, it is not yet clear whether its toxic effects are due to the release of free silver (Ag⁺), nAg or a combination of both species [1–3]. Many studies have identified the potent antimicrobial toxicity of Ag⁺ [4] and a few cases of bioavailable Ag complexes [5]. Recently, several research groups have demonstrated the apparent antimicrobial effects of silver nanoparticles [6,7]. For example, in studies using *Escherichia coli*, Kim et al. [6] determined that the antimicrobial activity of nAg was similar to a solution of silver nitrate. Asharani et al. [8] suggested that phenotypical defects in zebrafish were not due to Ag⁺ but rather nAg, while both Foldbjerg et al. [9] and Miura and Shinohara [10] reported observing similar biological responses due to nAg and Ag⁺. Nonetheless, in most of the studies, nanoparticulates were assumed to predominate in nAg suspensions—free silver was rarely quantified.

Suspensions of nAg contain at least three distinct forms of silver: Ag⁰, free Ag⁺ (and its soluble complexes) and adsorbed silver [11]. Ions are released from nAg due to oxidation, which can result in the

total dissolution of Ag⁰ under some conditions. It is difficult to predict the chemical speciation of nAg suspensions, especially in the presence of biological organisms, since equilibrium is not always attained. For example, Navarro et al. [12] suggested that silver particles contributed to toxicity via a Ag⁺ release process that was enhanced in the presence of algae due to the production of H₂O₂ (a metabolic product of the algae). Therefore, in order to determine the relative toxicity of Ag⁺ with respect to nAg, it is essential to precisely quantify nAg dissolution *under the conditions that are most relevant to the biological or environmental media of interest* (e.g. complex matrices, low nAg concentrations, etc.).

A number of analytical techniques can potentially be used to quantify nAg dissolution in natural and biological media [13]. For example, electrochemical approaches such as anodic stripping voltammetry (ASV), competing ligand exchange with adsorption cathodic stripping voltammetry (CLE-AdCSV) and ion selective electrodes [12,14] have long been used for chemical speciation measurements. Membranes or resins have also been used to separate species on the basis of their charge, size or chemical affinity (e.g. ion exchange technique, IET; Donnan membrane technique, DMT; permeation liquid membrane, PLM; diffusive gradients in thin films, DGT [12]). Finally, it is possible to physically separate dissolved Ag (Ag⁺ and its complexes) from nAg using ultracentrifugation, ultrafiltration or centrifugal ultrafiltration [11,12,15,16]. Each of the methods has its own advantages and limitations, based upon implementation, cost, detection limits and whether or not free ions can be measured independently from the labile metal complexes.

In this study, three analytical techniques (IET; centrifugal ultrafiltration; single particle inductively coupled plasma mass spectrometry, SP ICP-MS) were evaluated for their ability to

* Corresponding author. Tel.: +1 514 343 6741; fax: +1 514 343 7586.
E-mail address: kj.wilkinson@umontreal.ca (K.J. Wilkinson).

quantify free or dissolved Ag in suspensions of nAg. Particle dissolution was quantified for a wide range of nAg concentrations and under variable physicochemical conditions.

2. Materials and methods

2.1. Reagents

Dowex 50W-X8 (50–100 mesh, exchange capacity of 5.1 ± 1 meq/g, Sigma) was used as the cation exchange resin for the IET. Sodium hydroxide ($\geq 98\%$, 0.1 M) was used to convert the resin to its Na^+ form prior to use and sodium nitrate (99%, Sigma) was used as the swamping electrolyte. High purity nitric acid (65%, TraceSelectUltra) was purchased from Fluka. In some experiments, 2-[N-morpholino]-ethanesulfonate sodium salt (NaMES, Sigma-Aldrich) was used to buffer solutions to pH 6. Silver standards were prepared from a reference solution of 1000 ppm Ag in 2% HNO_3 purchased from Fisher Scientific. Commercial suspensions of silver nanoparticles were purchased from Vive Crop Protection (formerly ViveNano, product no. AD0223SRFD) and Ted Pella (Product nos. 15705-20SC, 15707-20SC and 15710-20SC). The Vive Nano product was provided as a 1.5 g/L aqueous suspension of nAg (measured by gravimetry) stabilized by sodium polyacrylate (silver content of the dried sample = 31%). The product has been well characterized in previous work, with results by transmission electron microscopy and fluorescence correlation spectroscopy showing that $> 90\%$ of the nanoparticles were in the size range of 1–10 nm [17]. The products purchased from Ted Pella corresponded to aqueous (non-stabilized) suspensions of three different particle sizes (20, 40, and 80 nm). These samples are used as electron microscopy size standards. However, in aqueous solution; they do have a tendency to aggregate in the absence of a stabilizer such as citrate. Free ion concentrations in the concentrated nAg stock solutions were below 2%. In order to approach equilibrium conditions as much as possible, all samples analyzed in this study were first equilibrated for 3 days at room temperature in a pH buffered media.

2.2. Instrumentation

Total Ag concentrations in solution were determined using a Varian AA240Z Zeeman atomic absorption spectrometer or a PerkinElmer NexION 300 \times ICP-MS. SP ICP-MS experiments were also carried out using the NexION 300 \times . pH measurements were made using a 744 Metrohm pH-meter. Nanoparticle Tracking Analysis (NTA; Nanosight LM10) was used to verify particle diameter variations of the nAg. Centrifugal ultrafiltration was performed in a Heraeus Multifuge 1 S-R centrifuge.

2.3. Ion-exchange technique (IET)

The ion-exchange approach is based upon the equilibration of the free ion with a small amount of cation exchange resin. The resin mass is small enough so that it will not cause any perceptible changes to the equilibrium distribution of chemical species in solution. Nonetheless, several conditions must be satisfied in order to measure equilibrium concentrations of free ion (M^{n+}) [18,19]. First, M^{n+} should be the only species exchanged with the resin counter-ions (Na^+). Second, at equilibrium, the total number of exchange sites should be much greater than those occupied by the adsorbed metal ion. Finally, the sample should contain counter-ions at a concentration that is not affected by the ion-exchange process. Equations describing the ion-exchange equilibria are given in the Supporting information.

Prior to use, fine particles of the resin were removed by sedimentation–decantation in MilliQ water ($R > 18 \text{ M}\Omega \text{ cm}$, organic

carbon $< 2 \mu\text{g L}^{-1}$) [18]. The resin was then washed with 1.5 M nitric acid, rinsed with MilliQ water and oven dried at 60°C . For each ion exchange column, 10 milligrams of dry resin were suspended in MilliQ water and the slurry was carefully drawn into cut polypropylene tubes (inner diameter: 1.65 mm, length: 15 mm) where it was maintained with a small amount of glass wool. Four replicate columns were used for each experimental condition. In this study, optimized steps were as follows: resin wash with 20 mL of 1.5 M HNO_3 , resin rinse with 20 mL of MilliQ water, conversion of the resin to its Na^+ form with 20 mL of 0.1 M NaOH, rinse with MilliQ water to neutral pH, pre-equilibration with 20 mL of a solution of similar pH and ionic strength as the sample to be analyzed, equilibration with the sample, rinse with MilliQ water (ca. 5 mL) and elution of adsorbed silver into pre-weighed polypropylene containers using 1.5 M HNO_3 . At the end of each step, air was passed through the column to remove any remaining interstitial solution. Samples and wash solutions were pumped (Gilson Minipuls 3 peristaltic pump) through the resin columns at 5 mL/min while the elution was performed at 0.5 mL/min.

2.4. Single particle ICP-MS (SP ICP-MS)

SP ICP-MS was used for the simultaneous measurement of dissolved and nAg. The theoretical basis of SP ICP-MS has been described by Degueldre et al. [20–22] for natural metal colloids and by Laborda et al. [23] for the discrimination of ionic and nano silver. SP ICP-MS distinguishes between dissolved and particulate silver based upon their differing signal intensities in a highly diluted sample. Indeed, the sample must be sufficiently diluted so that, during the defined short detection interval (dwell time), only a single particle attains the mass spectrometer. Since dissolved metal is homogeneously distributed in the nebulized sample droplets, it will produce a constant signal, whereas the observation of additional, discrete signal pulses can be attributed to the ionization of nanoparticles (Fig. S1). The relative proportions of ions and nanoparticles are then determined from a statistical distribution of their pulse intensities. In this work, data acquisition parameters in the single particle mode were as follows: sweeps per reading: 1; readings per replicate: 20,000; dwell time: from 0.1 to 5 ms (3 ms dwell times were reported here, however, all studied dwell times led to similar conclusions); integration time 2.5 s.

2.5. Centrifugal ultrafiltration

The centrifugal filter units (Amicon ultra, 3 kDa molar mass cutoff) were first pre-equilibrated with the sample matrix (free of Ag, same I and pH). Subsequently, 4 mL of each sample were centrifuged at $3700 \times g$ for 20 min over four centrifugation cycles in order to equilibrate the filters with the Ag (Fig. S2), which reduces adsorptive losses of Ag^+ . At the end of each centrifugation cycle, all liquid was removed from the devices. Following the final cycle, dissolved silver concentrations were determined in the filtrate while nAg was determined from an analysis of the silver remaining in the retentate. Samples indicating a deviation of greater than 10% from the theoretical mass balance were rejected.

3. Results and discussion

3.1. Optimization of the IET for determinations of Ag^+

For measurements of Ag^+ to be valid, the resin must be at equilibrium with the sample. Equilibrium is verified by percolating the samples through the column until $[\text{Ag}]$ in the sample = $[\text{Ag}]$ in the effluent (Fig. 1). Equilibration was assured by employing sufficiently large sample volumes, corresponding to relatively long

Download English Version:

<https://daneshyari.com/en/article/7683483>

Download Persian Version:

<https://daneshyari.com/article/7683483>

[Daneshyari.com](https://daneshyari.com)