



# Cysteine modified polyaniline films improve biocompatibility for two cell lines



Edith I. Yslas<sup>a,\*</sup>, Pablo Cavallo<sup>b</sup>, Diego F. Acevedo<sup>b</sup>, César A. Barbero<sup>b,\*</sup>, Viviana A. Rivarola<sup>a</sup>

<sup>a</sup> Departamento de Biología Molecular, Universidad Nacional de Río Cuarto, Agencia Postal Nro3, X580BYA Río Cuarto, Argentina

<sup>b</sup> Departamento de Química, Universidad Nacional de Río Cuarto, Agencia Postal Nro3, X580BYA Río Cuarto, Argentina

## ARTICLE INFO

### Article history:

Received 25 April 2014

Received in revised form 3 August 2014

Accepted 24 February 2015

Available online 26 February 2015

### Keywords:

Tissue engineering  
Conducting polymers  
Polyaniline

## ABSTRACT

This work focuses on one of the most exciting application areas of conjugated conducting polymers, which is cell culture and tissue engineering. To improve the biocompatibility of conducting polymers we present an easy method that involves the modification of the polymer backbone using L-cysteine. In this publication, we show the synthesis of polyaniline (PANI) films supported onto Polyethylene terephthalate (PET) films, and modified using cysteine (PANI-Cys) in order to generate a biocompatible substrate for cell culture. The PANI-Cys films are characterized by Fourier Transform infrared and UV–visible spectroscopy. The changes in the hydrophilicity of the polymer films after and before the modification were tested using contact angle measurements. After modification the contact angle changes from  $86^\circ \pm 1$  to  $90^\circ \pm 1$ , suggesting a more hydrophilic surface. The adhesion properties of LM2 and HaCaT cell lines on the surface of PANI-Cys films in comparison with tissue culture plastic (TCP) are studied. The PANI-Cys film shows better biocompatibility than PANI film for both cell lines. The cell morphologies on the TCP and PANI-Cys film were examined by fluorescence and Atomic Force Microscopy (AFM). Microscopic observations show normal cellular behavior when PANI-Cys is used as a substrate of both cell lines (HaCaT and LM2) as when they are cultured on TCP. The ability of these PANI-Cys films to support cell attachment and growth indicates their potential use as biocompatible surfaces and in tissue engineering.

© 2015 Elsevier B.V. All rights reserved.

## 1. Introduction

The use of polymers in biomedical applications has increased considerably in the past decades [1,2]. Polymers conductors (CPs) were also shown to tune cellular activities through electrical stimulation such as cell growth [3,4] and cell migration [5] and this led to a considerable interest in conducting polymers and their derivatives for tissue engineering applications [6–8]. CPs have electrical and optical properties similar to those of metals and inorganic semiconductors, but they also possess attractive properties similar to those of common polymers, such as ease of synthesis and good processability compared to metals [9–11]. Polyaniline (PANI) is one of the most promising candidates moreover; many studies have been devoted to this polymer. The PANI is one of the best characterized conducting polymers, it shows diversity of structural forms, high environmental stability, and it can transport charges in an easy way [12,13]. The first researchers who demonstrated that this polymer is biocompatible in vitro and in vivo were Mattioli-Belmonte et al. [14]. The published studies dealing with PANI biocompatibility can be divided into two main groups. The first group is focused on in-vivo testing [15,16]. The second, prevailing group is dealing with

assessment of in vitro proliferation and/or differentiation of cells on PANI surfaces [17–19].

Toward efficient development of biomaterials with higher biocompatibility, it is of critical importance to understand and control the physicochemical and biological interactions that occur at the interface between materials and cells. Cell adhesion is a key factor for the regulation of adherent cell growth, cell migration and differentiation [20,21]. Cell behavior in culture is generally influenced by the properties of the biomaterials surfaces such as the surface charge [22], chemistry [23], roughness and surface free energy [24]. On the other hand contact angle measurement depends on the surface hydrophilicity (or hydrophobicity), roughness, porosity, pore size and its distribution. In other words, this technique analyses the physical and chemical properties of the surface. This technique is useful due to the hydrophobic/hydrophilic balance plays a major role in the attachment cells to biomaterials [25].

There are many works dealing with the biocompatibility of PANI; however, there is few information about the modified PANI to improve biocompatibility. For this reason we present here an easy method that involves the modification of the polymer using cysteine amino acid. Some studies dealing with cysteine dissolved in the growth media, Walker et al. have demonstrated that L-cysteine improves growth of human peritoneal mesothelial cells (hPMC) in vitro [26]. Other researchers use the cysteine to functionalized surfaces in order to use it as a linker for molecules; such as Zhang et al. that they have modified

\* Corresponding authors.

E-mail address: [eyslas@exa.unrc.edu.ar](mailto:eyslas@exa.unrc.edu.ar) (E.I. Yslas).

surfaces with oligopeptides [27]. However, at the moment there is any report of the use of LM2 cells and HaCaT cells attached on cysteine surface modified. The result of this study demonstrates that it is not necessary to use the cysteine as a linker to improve the viability on this kind of cell. When the surface is modified with cysteine the viability increases up to 100%. Taking into account, the results demonstrate and ensure that with only modification of the surface polymer with cysteine it is possible to reach 100% of viability and no further modification with peptides or other molecules to improve viability is necessary. The hypothesis was that surface modification would have a positive impact on cell–substrate interactions. The present study shows the synthesis and characterization of a new biocompatible material composed of a PANI backbone modified with cysteine. Moreover, the biocompatibility of PANI-Cys films, using two cell lines LM2 and HaCaT is probed by assessing the adhesion to substrate. The cellular morphology of both cell lines is also studied in situ by fluorescence and AFM microscopies. All these tests show that this new material is suitable to attach and grow cells, indicating their potential use as biocompatible surfaces and tissue engineering.

## 2. Materials and methods

All the reagents were of analytical grade.

### 2.1. Synthesis and modification of polyaniline films

Polyaniline (PANI) films were obtained by in-situ polymerization of aniline onto polyethylene terephthalate (PET) and polyethylene (PE). Commercial films of PET and PE (Goodfellow) were submerged in an aqueous solution containing 50 mM aniline. To initiate the polymerization, ammonium persulfate (APS) as oxidant (50 mM) was added. Different pieces of film were left to react for 30 min to 4 h at room temperature. The optimal polymerization time to obtain uniform films was found to be 2 h. The films polymerized during 2 h were rinsed thoroughly with a solution 1 M of hydrochloric acid. Then PANI films were functionalized by nucleophilic addition [28,29]. The films were immersed into a stirred aqueous solution of L-cysteine 1 M for 24 h at room temperature. Then, they were washed with deionized water (DI), dried in air and stored at room temperature. Finally, these films were sterilized overnight with UV light in the laminar flow.

### 2.2. Characterization of chemical structure

The chemical structures of all samples were determined by Fourier-transform infrared spectroscopy (FTIR) and the spectra were collected on a Nicolet Impact 410 spectrometer in transmission mode in air of the polymer and modified polymer supported onto PE. A total of 200 scans were averaged at a resolution of  $4\text{ cm}^{-1}$ .

UV–visible spectra were recorded on a Shimadzu UV-2401PC spectrometer in the wavelength range from 250 nm to 1000 nm. Three films for each formulation were tested using air as a background, by transmission of the polymer deposited onto PET.

### 2.3. Contact angle measurement

The measurements were carried out at 25 °C, using 5  $\mu\text{l}$  of DI water deposited onto the surface. A microscope Intel Play QX3 with 60 $\times$  objective was used for photographing the drop image. The images (tiff format) were analyzed using “Drop Analysis”, an add-in of ImageJ® image processing software. At least five readings ( $n = 5$ ) were made on different parts of the films and the results informed were averaged of these 5 measurements [30].

### 2.4. Cell lines

HaCaT or LM2 cell line was cultured in Dulbecco's Modified Eagle's Medium (DMEM) supplemented with 10% Fetal Bovine Serum (FBS) and 1% of an antibiotic–antimycotic solution (Gibco) at 37 °C in a humidified 5%  $\text{CO}_2$  containing atmosphere. Cells were seeded onto unmodified TCP and PANI-Cys films. The modified films were sterilized on UV light overnight, and then placed in a dish culture.

### 2.5. Cell viability

Tetrazolium dye (MTT; 3[4,5-dimethylthiazol-2-yl]-2,5-diphenyltetrazolium bromide) assay was generally used for the determination of cytotoxic effects on the growth and cell viability [31]. The HaCaT or LM2 cell line was cultured on PANI and PANI-Cys in 96-well plates at a density of  $2.5 \times 10^5$  cells/well in DMEM. The TCP was used as the control. The MTT was added to each culture medium to obtain quantitative values of both the HaCaT cells and the LM2 cells on the 96 wells, PANI-Cys films after 24 and 36 h of culture and PANI films after 36 h of culture. To assay the attached cells, the cultured medium was discarded. After culturing the cells were rinsed three times with sterile phosphate-buffered saline (PBS). Then, a medium in MTT was added and the cells were continued to culture for 3 h. After removing the medium, dimethylsulfoxide was added, and the absorbance was read at 550 nm using a microplate reader (Thermo Lab systems, Finland). Ten parallel replicates were read for each sample.

### 2.6. Adhesion of HaCaT and LM2 cell lines to PANI-Cys surface

Cell count was based on incorporation of 5  $\mu\text{g}/\text{mL}$  Hoechst 33342 (Sigma-Aldrich Ltd.) that labels the DNA and serves for visualization of nuclei. The samples were fixed in cold methanol for 15 min then this fluorescent dye was added for 1 min to the cells that were finally washed. Fluorescence was recorded using a Nikon microscope, using an excitation filter BP340–380, with a color CCD camera. Cell counting was done using ImageJ® 1.34 s image analysis software. The cell number was counted on average in ten fields.

### 2.7. Atomic force microscopy, cell morphology studies

After the HaCaT and LM2 cells were grown in PANI-Cys films, 1 mL fixation solution (3.7% formaldehyde) was added to the sample for 15 min. The samples were then rinsed with PBS. Finally the fixed cells were studied by atomic force microscopy (AFM). The AFM measurements were made with an Agilent 5420 AFM/STM microscope in ambient conditions. The analysis of fixed cells was carried out at room temperature (20–25 °C) using a commercial Point Probe® Plus Non-Contact/Tapping Mode-Long Cantilever (PPP-NCL) with a force constant of  $6\text{ N m}^{-1}$  and resonance frequency of 156 Hz in the Acoustic AC (AAC) mode.

## 3. Result and discussion

### 3.1. Characterization PS-PANI-Cys films

The UV–visible absorption spectrum of PANI and PANI-Cys film is shown in Fig. 1A. This figure shows the typical electronic transitions of the PANI. A typical UV–vis spectrum of the PANI in the doped state (dot gray line), undoped state (solid black line) and PANI-Cys (dot black line) is shown. For the doped PANI, the shoulder at ca. 349 nm is attributed to the  $\pi \rightarrow \pi^*$  transition of the aniline ring and the band at ca. 413 nm is assigned to the  $n \rightarrow \pi^*$  transition of the localized cation radical. On the other side, the band at ca. 850 nm is assigned to the excitation from the highest occupied molecular orbital (HOMO) of the benzenoid rings (pb) to the lowest unoccupied molecular orbital (LUMO) of the quinoid rings (pq) in the quinoneimine units [32]. It is

Download English Version:

<https://daneshyari.com/en/article/7869495>

Download Persian Version:

<https://daneshyari.com/article/7869495>

[Daneshyari.com](https://daneshyari.com)