

Author's Accepted Manuscript

Non-inclusion induced crack initiation in multiphase high-strength steel during very high cycle fatigue

P. Zhao, Z. Liu, R.D.K. Misra, F. Du, C. Zhang, Z. Yang, E. Yan



PII: S0921-5093(17)31579-4
DOI: <https://doi.org/10.1016/j.msea.2017.11.119>
Reference: MSA35834

To appear in: *Materials Science & Engineering A*

Received date: 19 October 2017
Revised date: 27 November 2017
Accepted date: 28 November 2017

Cite this article as: P. Zhao, Z. Liu, R.D.K. Misra, F. Du, C. Zhang, Z. Yang and E. Yan, Non-inclusion induced crack initiation in multiphase high-strength steel during very high cycle fatigue, *Materials Science & Engineering A*, <https://doi.org/10.1016/j.msea.2017.11.119>

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting galley proof before it is published in its final citable form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Non-inclusion induced crack initiation in multiphase high-strength steel during very high cycle fatigue

P. Zhao^a, Z. Liu^{a*}, R.D.K. Misra^{b*}, F. Du^a, C. Zhang^c, Z. Yang^c, E. Yan^d

^aCollege of Materials Science and Engineering,

Qingdao University of Science & Technology, Qingdao 266044, China.

^bLaboratory for Excellence in Advanced Steel Research,

Department of Metallurgical, Materials and Biomedical Engineering, University of Texas, El Paso 500 W.

University Avenue, El Paso, TX 79968-0520, USA.

^cSchool of Materials Science and Engineering, Tsinghua University, Beijing 100084, China.

^dSchool of Materials Science and Engineering, Guilin University of Electronic Technology, Guilin 541004, China.

Abstract

During very high cycle fatigue (VHCF) crack can initiate at non-inclusion site in the interior of Mn-Si-Cr bainite/martensite (B/M) multiphase steels. The characteristics of non-inclusion induced crack initiation in B/M multiphase steels and the relationship between the size of granular bright facet (GBF) and VHCF limit were studied through ultrasonic fatigue testing, in terms of fracture surface analysis, crack initiation analysis, and failure mechanism. The current study reveals that GBF area became smaller with the increase of VHCF limit, i.e. the steel with higher fatigue-endurance strength exhibited smaller GBF area in the case of steel characterized by non-inclusion crack initiation in the VHCF regime. The relationship between GBF area, fatigue life, and applied stress was consistent with the following equation $\sqrt{area_{GBF}} = 29.41 \log N_f - 0.2916 \sigma_a + 47.51$. The study provides an understanding of non-inclusion induced crack initiation in VHCF and a guidance for steel fatigue design.

Keywords: Very high cycle fatigue, Bainite/martensite multiphase steel, Non-inclusion induced crack initiation.

* Corresponding authors.

E-mail addresses: liuzhonglimanor@163.com (Zhongli Liu), dmisra2@utep.edu (R.D.K. Misra).

Tel/ Fax: +86 0532 84022870.

Download English Version:

<https://daneshyari.com/en/article/7973986>

Download Persian Version:

<https://daneshyari.com/article/7973986>

[Daneshyari.com](https://daneshyari.com)