



Technical note

Entangled structures as high cycle compression springs



Folkers E. Rojas*, Alexander H. Slocum

Department of Mechanical Engineering, Massachusetts Institute of Technology, Cambridge, MA 02139, USA

ARTICLE INFO

Article history:

Received 2 February 2015

Accepted 20 April 2015

Available online 27 May 2015

Keywords:

Entangled structures

Foams

Fibrous metals

Springs

ABSTRACT

Entangled structures, such as steel wool, can be used as inexpensive, high cycle, low stiffness, thin profile compressive springs where uniform pressure on a surface is required particularly in elevated temperature and/or harsh environments. Mechanical compression tests were performed on a variety of steel wool samples to determine the stress–strain curve behavior over high cycles. After initial conditioning cycles, good repeatability can be obtained with hysteresis dependent on strain. The results show a nonlinear behavior over large strains (>10%) and reasonable linear behavior for strains less than 10%. The properties of an entangled structure spring can be selected to achieve the desired stiffness for a particular application.

© 2015 Elsevier Inc. All rights reserved.

1. Introduction

The mechanics of a random array of interwoven fibers, i.e. entangled wires such as found in steel wool, have been studied for applications such as damping, isolating, or filtering. In semiconductor test applications “Fuzz Buttons,” a compacted random array of wire, have been used as temporary electrical contacts for “low signal distortion, high frequency, and low insertion force, planarity, and shock/vibration resistance” [1]. Contact testers made from micro entangled structures have been used by the semi-conductor industry to test Through Silicon Via (TSV) and micro-bumps arrays [2,3]. The characterization of entangled wires is also very important for micro-electronics, micro fluidics, micro sensors and actuators that are based on entangled silica nano-wire structures [4]. The generation of the silica nanowire entangled arrays are grown, and not created via a mechanical means and they often appear as entangled [4,5]. Entangled structures are also used by the space industry to isolate instruments or to damp vibrations [6,7].

Entangled structures have also been evaluated as compatible replacements for porous aluminum as they have been shown to have good toughness and strength [8,9]. Entangled titanium wire materials (ETWM) and porous titanium foams have been considered for tissue reconstruction, orthopedic implants, and bone repairs [10–14]. The challenge for the medical industry has been to match the mechanical properties of entangled wire structures to similar mechanical properties of bone which has been attempted by altering the effective porosity of the structure

created by the entangled wires [11,14]. While compressive properties and pseudo-elastic hysteresis behaviors have been characterized for ETWMs, a high cycle analysis of the nonlinear elastic region of ETWMs is needed to make the design process more deterministic.

Prior work has shown that entangled structures have a three-stage stress–strain behavior under compressive loads: (1) nonlinear elastic deformation, (2) strain-hardening, and (3) densifying [10]. Here we build on this work by studying the higher cycle compliance of entangled structures under uniaxial compression for the use as an inexpensive and repeatable low-moderate stiffness thin profile large contact area spring. This type of spring has wide application in presses and rectilinear format batteries. This work also examines the effect of densification on the apparent Young's modulus for entangled structures for comparison with existing analytical models. Analogies are made with low density materials such as foams, composites, and elastomers in order to help develop modeling tools.

2. Experimental procedures

2.1. Sample characterization

One method for generating an entangled metal wire structure involves wrapping the wire around a rod to create a loose steel wire bundle. The unconsolidated deformed wire is placed into a set of molds where it is compressed and sintered to remove internal stresses [8,10,15]. Common steel wool, which is much more compliant and inexpensive, is made by shaving small strands from straight steel wire and consolidating the strands into an entangled structure using a needle punch machine to generate a mat of wool. The

* Corresponding author. Tel.: +1 603 513 8997; fax: +1 603 225 3102.
E-mail address: Folkers.Rojas@gmail.com (F.E. Rojas).

Table 1
Characterization of samples tested.

	For cyclic study	For densification and cyclic study
Initial size (mm ³)	52 × 52 × 8.5	61 × 63 × 36
Mass (g)	5.83	6.14

pads are held together by the entangling nature of the process that produces a semi-aligned structure with the fibers in the pad.¹ Prior work on characterizing steel wool pads was done in 2006 by Masse et al.; however, only 60 cycles were used to derive the stress–strain curve [16]. Their work showed that the stress–density curves had a power-law relation [16]. In the present work, we are interested in the cyclic performance of steel wool as a spring that acts over a wide area subject to thousands of cycles. Applications include providing a uniform pressure over the surface of an object as might be needed in a press or a rectilinear format battery.

To study high cycle behavior, two types of samples were initially evaluated: coarse (Grade #3) and fine (Grade #0) steel wool with wire diameters of 90 μm and 25 μm respectively were used. Test samples were cut from non-sintered steel wool pads.² The manufacturing method of the wool pad creates an inherent preferred orientation of a planar cross pattern.

Hydrostatic weighting is typically used for determining the porosity of a sample [10], in this case the mass of the sample was measured using an AG204 Delta Range Mettler Toledo scale with an accuracy of 0.1 mg/1 mg, at room temperature. The volume of a sample was measured with calipers accounting for an error of about 1 mm on each length measurement. The samples were cut from 7-in. diameter pads into squares as summarized in Table 1.

The objective of the densification experiment was to explore the repeatability over a range of compression states to determine effect of density on stiffness. The densification study is done with a highly porous steel wool sample (Grade 1 – purchased as a 1 pound bag from McMaster-Carr³) that is incrementally compressed while testing long term cyclic behavior at each stage. The sample used for the densification experiment does not contain the planar cross pattern of the wool pads. The sample is incrementally compressed until more than fifty percent strain has been achieved. At each state the sample is not strained more than ten percent at any given time.

2.2. Testing procedure

The stress–strain behavior of the samples was performed using an Admet testing machine (Model 5601QP2 – Serial 0611091 eXpert) with an Interference load cell, rated to 120 N (Serial # 708336). As shown in Fig. 1, the experimental setup consists of a base support with a pocket region for the samples that prevents horizontal shifting of the sample during the cycling process. A compressive plate provides an even load, measured by the load cell, across the sample. The testing machine is controlled by a programmed displacement cycle.

2.3. Cyclic testing

The preliminary tests, shown in Fig. 2, show the loading for a fine and course sample with ~97.7% porosity. The fine steel wool sample has a stiffer stress–strain response compared to the coarse sample, due to the limitation of the strain gauge only the course sample is tested extensively over a wider range of strains. The tests

show a settling/shifting effect in the stress–strain curve over first 100 cycles in the non-linear elastic region. Van Wyk alluded to this shifting effect in his 1964 paper: “the curve shifts with each successive cycle of compression and release, but finally attains a steady position” [17]. After the initial settling the data was repeatable. The discrepancy is attributed to the initial settling and distortion of the entangled structure in the process toward reaching stability. A 1000 cycle run was thus used to remove any long term settling of the samples. As a check, a low stiffness coil spring was substituted for the sample to ensure that testing machine was operating as expected, and the result confirmed the observation of the entangled structure behavior.

The coarse sample was cycled on the testing machine at a frequency of 0.5 Hz and at a constant strain rate of 24%, 2 mm/sec over a sample height of 8.5 mm. The fine sample was also cycled at a 0.5 Hz, but with a smaller strain rate as the stiffness was higher than the coarse sample. The densification sample was also tested at a constant strain rate with sample thickness starting from 36 mm and decreasing to 22 mm by 2 mm increments. For the initial data set the steel wool is cycled from 36 mm down to 34 mm. The first thousand cycles are discarded from the data, to establish the steady state behavior. An additional two thousand cycles are performed and used to analyze the steady state behavior in that region. With the completion of the initial data set, the following data set starts from a 34 mm thickness and is cycled down to 32 mm. The same process is carried out to all following data sets until reaching a final thickness of 22 mm.

3. Results

The data collected from the testing machine is shown in terms of vertical displacement and the compressive load measured by the load cell gauge. The data is combined with the geometry and sample properties to generate engineering stress–strain curves, as shown in Fig. 3.

3.1. Cyclic testing

The coarse sample was loaded for >11k cycles, with an initial 1k cycle break-in period for allowing the fibers to settle into a steady state region. Note that this type of break-in period is also required for steel cables [18]. As shown in Fig. 4, every two thousand samples, the loading curve is repeatable and below the initial curve of the break-in period. The first 1k sample (i.e. break in) was where it reaches steady state. Then the system was set to do a 2k run, when done the same preload was affirmed and then a run was done for the next 2k sample (i.e. sample 2001 is the first value). Notice that the break in curve is higher than all of the other curves. Each data set following the break in consists of 2000 cycles. At the conclusion of each data set the sample is reset to the starting preload in the event that drifting in the testing machine took place during cycling. Only the first data point of each data set is plotted to illustrate repeatability. After collecting 11k cycles, the average of all the first data sets was calculated and plotted. Future work will calculate the mean and error of all of the data points combined.

3.2. Young's modulus as densification

The sample used for the densification is a homogeneous unconsolidated coarse steel wire wool with a diameter of 90 μm. The goal was to demonstrate that a small change in the porosity of the structure can result in a change in the effective stiffness. The cycle stroke was set to 2 mm, which limited the strain from 5.5% (at 36 mm) to 9.1% (at 22 mm), to the authors surprise the stiffness was linear in these regions. Fig. 5 shows the response starting from a 36 mm thick sample undergoing a minimum of 3000 cycle test, for clarity

¹ See for example <http://www.youtube.com/watch?v=iaDzLP3TT.J>.

² Manufacturer of Wool pads: International Steel Wool Inc. (<http://steelwooldirect.com/>) for the 7 inch Tex-Wool floor pads grade 0 and 3.

³ Grade 1 Steel wool – 1 pound bag from McMaster-Carr Item Number 7363T24.

Download English Version:

<https://daneshyari.com/en/article/803893>

Download Persian Version:

<https://daneshyari.com/article/803893>

[Daneshyari.com](https://daneshyari.com)