




Contents lists available at ScienceDirect

Nuclear Instruments and Methods in Physics Research B

journal homepage: www.elsevier.com/locate/nimb

In situ high energy resolution off-resonant spectroscopy applied to a time-resolved study of single site Ta catalyst during oxidation

Wojciech Błachucki^{a,*}, Jakub Szlachetko^{b,c}, Yves Kayser^b, Jean-Claude Dousse^a, Joanna Hoszowska^a, Faisal Zeeshan^a, Jacinto Sá^{d,e}

^a Department of Physics, University of Fribourg, Chemin du Musée 3, CH-1700 Fribourg, Switzerland

^b Swiss Light Source, Paul Scherrer Institut, CH-5232 Villigen-PSI, Switzerland

^c Institute of Physics, Jan Kochanowski University, 25-406 Kielce, Poland

^d Department of Chemistry, Uppsala University, 752 37 Uppsala, Sweden

^e Institute of Physical Chemistry, Polish Academy of Sciences, 01-224 Warsaw, Poland

ARTICLE INFO

Article history:

Received 8 September 2016

Accepted 22 November 2016

Available online xxxx

Keywords:

Synchrotron radiation

Time-resolved high energy resolution off-

resonant X-ray spectroscopy

Catalysts

ABSTRACT

In the present work high energy resolution off-resonant X-ray spectroscopy (HEROS) was employed at a synchrotron to study a silica supported Ta(V) bisalkyl catalyst activated in hydrogen. The Ta $L\alpha_1$ HEROS spectra were measured during oxidation of the starting complex and the relative species' concentration was successfully retrieved as a function of time using the fingerprint HEROS spectra measured for the unoxidized and the oxidized catalyst. Based on the experimental data and theory-based calculations, it was shown that oxidation of the active Ta catalyst leads to the formation of mono- and di-meric species on the SiO_2 surface. The obtained results were compared to those of the previously reported time-resolved HEROS study on an inactive silica supported Ta(V) bisalkyl catalyst's concentration evolution during its oxidation Błachucki et al. (2015). The study allowed observation of an immediate transition of the active Ta catalyst from its unoxidized form to the oxidized one. This finding is dissimilar to the result of the study on the inactive Ta catalyst, where the oxidation led through an intermediate step.

© 2016 Elsevier B.V. All rights reserved.

1. Introduction

High energy resolution off-resonant X-ray spectroscopy (HEROS) is a method of determining the density of unoccupied electronic states [1–3]. HEROS is an alternative to the existing X-ray absorption spectroscopy (XAS) methods and opens the way for new studies not achievable before. HEROS makes use of high energy resolution X-ray emission spectroscopy (XES) to study spectra of inelastically scattered photons in off-resonant conditions, i.e., for incident photon energies below the atomic core level binding energy of interest. It has been shown that such spectra carry information on the occupancy of the discrete valence electronic states as well as the states above the ionization threshold (in the continuum) [4–7]. Provided that the incident photon beam energy bandwidth is smaller than the initial state lifetime broadening and a high resolution wavelength-dispersive detection system is used, HEROS allows to probe the density of unoccupied states with high energy resolution. This is possible because in the

off-resonant inelastic X-ray scattering process the scattered photons' spectra are not broadened by the lifetime of the core hole associated to the investigated absorption edge. Further, in HEROS the sample is irradiated with a monochromatic X-ray beam of energy fixed below the given ionization threshold and the crystal spectrometer (in the von Hamos or Johansson geometry), equipped with a position sensitive detector, allows recording emission spectra in one shot with covered energy ranges of typically tens of eV. This scanning-free arrangement thus allows to probe the density of unoccupied states with time resolution limited only by the experimental setup's efficiency. The swift way of probing the electronic structure of matter, provided by HEROS, is highly desirable in time-resolved spectroscopic studies on dynamically changing chemical systems. This also makes HEROS a method of choice in case of extremely bright pulsed X-ray sources such as X-ray free electron lasers (XFELs), where the target is damaged after every pulse and the beam intensity variations severely limit the usability of conventional XAS methods [8]. Moreover, the HEROS spectral profiles are not modified by the self-absorption effect [9].

The ability of the HEROS method to perform time-resolved studies on chemically dynamic systems has already been used to follow the time course of such chemical processes as oxidation,

* Corresponding author.

E-mail address: wojciech.blachucki@unifr.ch (W. Błachucki).

reduction and compound decomposition [1,10,11]. It has been shown that, despite the low fluorescence yield of off-resonant excitations, HEROS allows the observation of changes in the density of unoccupied states caused by the evolving chemical environment of the probed atoms with a high temporal resolution reaching 1 s or less. Moreover, the insensitivity of HEROS to the self-absorption effect [9] makes it a reliable tool to perform quantitative chemical speciations under reaction conditions.

2. Theory



As reported by Tulkki and Åberg [5], the photon scattering cross section for the off-resonant excitation well below the ionization threshold is correlated to the density of unoccupied states. Assuming that the fluorescence yield I_{XES} is proportional to the scattering cross section and the oscillator strength distribution for electron excitation I_{XAS} to the density of unoccupied states, one can reformulate the Tulkki and Åberg formula to retrieve the XAS data from the off-resonant XES data and *vice versa* [1,6]. In the present work, the density of unoccupied states of Ta atoms is measured through the detection of the photons emitted in the $L_3 \rightarrow M_5$ decay channel in off-resonant conditions. In this case, the Tulkki and Åberg formula has the following form:

$$I_{XES}(\hbar\omega_2) \propto \int_0^{\hbar\omega_2} \frac{\hbar\omega_2 (|E_{L_3}| - |E_{M_5}|)(E + |E_{L_3}|)}{\hbar\omega_1 (E + |E_{L_3}| - \hbar\omega_1)^2 + \Gamma_{L_3}^2/4} \times \frac{\Gamma_{M_5}}{(\hbar\omega_1 - \hbar\omega_2 - |E_{M_5}| - E)^2 + \Gamma_{M_5}^2/4} \times I_{XAS}(E) dE, \quad (1)$$

where E_{L_3} and E_{M_5} represent the electron binding energies in the initial and final states, respectively, and $\hbar\omega_1$ and $\hbar\omega_2$ stand for the energies of the incident and emitted photons. The initial and final state lifetime broadenings are denoted by Γ_{L_3} and Γ_{M_5} . The $I_{XAS}(E)$ function is proportional to the linear photoabsorption coefficient μ_{ph} as a function of the excitation energy $(E + |E_{L_3}|)$. The off-resonant XES data $I_{XES}(\hbar\omega_2)$ retrieved from the $I_{XAS}(E)$ function by means of Eq. (1) is proportional to the intensity of emitted photons as a function of their energy. It can be noted first that $I_{XES}(\hbar\omega_2) = I_{XES}(\hbar\omega_1 - |E_{M_5}| - E)$ according to the energy conservation law for the resonant inelastic X-ray scattering (RIXS) [5,6] and secondly that for incident energies tuned about 15 eV below the L_3 edge, like in the present experiment, the XES intensity given by Eq. (1) is nearly insensitive to the initial state width Γ_{L_3} .

3. Samples and experimental method

The measurements were carried out at the SuperXAS beamline of the Swiss Light Source of the Paul Scherrer Institut, Switzerland. The collimated synchrotron beam was monochromatized by means of a double Si(111) crystal monochromator and focused with a toroidally bent Rh mirror to a $100 \times 100 \mu\text{m}^2$ -spot size on the target. First, a Ta foil was used as the target to calibrate in energy the incident beam and the spectrometer. Then the investigated Ta complex was loaded into a quartz capillary reactor cell in a glove box and exposed to 20 ppm O_2 at room temperature. Two silica supported Ta complexes were studied, Ta(V) bisalkyl complex (Complex 1) and Ta hydride (Complex 2), i.e., more specifically:



The quartz capillary reactor cell was mounted on the sample holder and connected to a remotely switchable gas system which allowed applying a gas flow through the target on line. Two gases

were used: Ar to flush residual gases out of the reactor and 10% H_2/He mixture to activate the Ta complex. The temperature of the Ta complex was adjusted with an air blower and a thermometer placed on two sides of the reactor.

The induced fluorescence was detected in the energy range around the Ta $L\alpha_1$ emission line (8.146 keV) by means of a wavelength-dispersive von Hamos-type spectrometer consisting of two cylindrically curved segmented-type Si(444) crystals [12] and a two-dimensional PILATUS 100 K detector [13]. Two crystals were employed to increase the solid angle of the spectrometer. The latter was operated in the vertical dispersive geometry. The two crystals were oriented so that they cover exactly the same Bragg angular range. However, they were slightly tilted to each other about a vertical axis so that the photons diffracted by the two crystals were detected by two different regions of the PILATUS detector. An acquisition time of 40 s per image was used. For each time interval of 40 s, the HEROS spectrum was obtained by projecting the sum of the two 2D images onto the dispersion axis of the spectrometer. From the full width at half maximum (FWHM) of a Gaussian fit to the elastic scattering peak a total experimental resolution of 1.6 eV was found. A 30-cm-long, helium filled, ionization chamber was placed upstream the target to normalize the detected fluorescence yield as a function of the beam intensity.

4. Results and discussion

The Ta $L\alpha_1$ HEROS spectra measured at an incident beam energy of 9.863 keV during oxidation of Complex 1 are presented in Fig. 1 (a). The reaction took place at room temperature and it caused an increase in the fluorescence intensity as well as a shift of the detected spectral structure towards lower energies. In the case of Complex 2, the Ta $L\alpha_1$ HEROS spectra, which are shown in Fig. 1 (b), were collected at an incident beam energy of 9.867 keV. Complex 2 was obtained by activating Complex 1 in hydrogen. This was achieved by exposing Complex 1 to a 10% H_2/He gas mixture between 1300 s and 3200 s while rising the temperature from 20 °C to 150 °C. During activation, a slight gradual displacement of the detected spectral structure towards lower energies was observed. Further oxidation of Complex 2 led to a sudden spectral shift and increase in intensity of the emitted fluorescence.

As shown in Fig. 2(a), oxidation of Complex 1 caused a shift of the detected spectral structure towards lower energies by about 1 eV as well as an increase in the fluorescence intensity. It also gave rise to the evolution of another spectral structure on the low energy side of the main peak. Fig. 2(b) presents fingerprint Ta $L\alpha_1$ HEROS spectra measured for Complex 2 at three different stages: before the formation of Complex 2 from Complex 1 (through activation of Complex 1 in hydrogen), before reaction of the formed Complex 2 with oxygen and after Complex 2 turned into its oxidized form. During activation, a slight gradual displacement of the detected spectral structure towards lower energies (by about 0.5 eV) was observed. Further oxidation of Complex 2 led to a sudden spectral shift and an increase in intensity of the emitted fluorescence. The shape of the spectrum recorded for the oxidized Complex 2 reveals formation of another peak situated slightly closer in energy to the main peak as compared to the spectrum recorded for oxidized Complex 1.

The evolution during oxidation of the second peak in the HEROS spectra suggests the formation of Ta = oxo dimeric surface species with octahedral coordination [14], which is consistent with calculations of Ta L_3 edge XAS spectra and off-resonant Ta $L\alpha_1$ XES spectra for a monomeric and a dimeric Ta species (see Fig. 3). The absorption spectra were computed using the FEFF program [15] and the emission spectra were obtained using the Kramers-Heisenberg formula modified by Tulkki and Åberg [4,5] with the

Download English Version:

<https://daneshyari.com/en/article/8039543>

Download Persian Version:

<https://daneshyari.com/article/8039543>

[Daneshyari.com](https://daneshyari.com)