



ORIGINAL ARTICLE

Effect of different ratios of bioplastic to newspaper pulp fibres on the weight loss of bioplastic pot



Kang Chiang Liew *, Lian Kim Khor

School of International Tropical Forestry, Universiti Malaysia Sabah, Jalan UMS, 88400 Kota Kinabalu, Sabah, Malaysia

Received 2 April 2013; accepted 14 August 2013

Available online 29 August 2013

KEYWORDS

Bioplastic pot;
Newspaper pulp;
Weight loss

Abstract Nowadays, industry is searching for an alternative to reduce the usage of petroleum-based non-degradable conventional seedling plant pots. In this study, three different types of bioplastic pots incorporated with newspaper pulp fibres (the ratio of B75%:N25%, B50%:N50% and B25%:N75% denotes percentage of bioplastic to percentage of newspaper pulp fibres) were produced while B0%:N100% acted as the control. All cylinder square shape moulded bioplastic pots with 100 mm height and 2 mm thickness were planted with *Leucaena leucocephala* seedlings for 60 days in two ground levels (below ground and above ground). Weight loss for bioplastic pots was evaluated. Results showed that bioplastic pots tested below ground had a higher percentage of weight loss than those planted above ground. For percentage of weight loss of bioplastic pots, most bioplastic pots that were tested in both ground levels only showed a significant difference at $p \leq 0.05$ after 30 days. Bioplastic pots B75%:N25% that were tested below ground have the highest percentage of weight loss with 77.93%. As conclusion, B50%:N50% is the most suitable ratio for the production of bioplastic pot.

© 2013 Production and hosting by Elsevier B.V. on behalf of King Saud University.

1. Introduction

Population growth has increased the growth in agricultural activities thus increasing the generation of agricultural wastes indirectly. One of the most common wastes generated is the petroleum-based conventional seedling plant pots or polybags as these pots are the most common pots used in plantations.

Normally these non-biodegradable pots were disposed after use and end up in landfills which will cause pollution. In order to solve this issue, the plantation industries are searching for an alternative for the usage of non-biodegradable seedling plant pots.

Population growth had also increased solid waste generation such as organic waste, paper, plastic, rubber, metal, wood, glass, ceramics and textiles. Most of these solid wastes including newspaper end up in landfills as this is the most common method used for the disposal of solid waste in Malaysia. As the level of environment awareness increases, public starts to recycle used newspaper with the help of new technology. These recycled newspaper pulp fibres are used as the source of bio-fibre materials for construction, newsprint, paperboard packaging, insulation or building materials (Huda et al., 2005). In

* Corresponding author. Tel.: +60 88 320118; fax: +60 88 320876.
E-mail address: liewkc@ums.edu.my (K.C. Liew).

Peer review under responsibility of King Saud University.



Production and hosting by Elsevier

order to maximize the usage of recycled newspaper pulp fibres, industries are exploring more usage of these fibres into other products. One of these products would be the bioplastic pot which is a mixture of bioplastic and newspaper pulp fibres which may become an alternative for the non-degradable seedling plant pot. Moreover, the presence of bioplastic and newspaper pulp fibres can produce degradable pots with a higher durability. Besides, bioplastic contained in the pots can reduce swelling of pots caused by water absorption during production and planting process. In this study, production of bioplastic pot by incorporating newspaper pulp fibres into bioplastic was evaluated for its weight loss for pots made from different ratios of bioplastic and newspaper pulp fibres for planting above and below ground.

2. Materials and methods

2.1. Preparation of raw materials

Materials used for the production of bioplastic pot were newspaper, tapioca starch (or known as cassava starch), glycerol with 99.5% concentration and vinegar. Newspapers were collected from several sources normally in the recycling activity and soaked overnight in water. Soaked newspapers underwent fibrillation process by using a valley beater for five minutes.

2.2. Production of bioplastic

Materials for the production of bioplastics were tapioca starch, water, vinegar and glycerol. First, appropriate amounts of materials for bioplastic pot were weighed based on ratio of bioplastic and newspaper pulp fibres. Secondly, tapioca starch, water, vinegar and glycerol were mixed together in room temperature. After that, fibrillated newspaper pulp fibres were added into the mixture and stirred for two minutes until all materials were mixed well. Lastly, bioplastic and newspaper pulp fibre mixture was heated on hot plate at 80 °C temperature until obtain sticky gel texture based on [de Thomas \(2011\)](#).

2.3. Production of bioplastic pot

There were three different types of mixing ratios between bioplastic and newspaper pulp fibres which were B75%:N25%, B50%:N50% and B25%:N75%. Pot made from 100% of newspaper pulp fibres acted as control. Numbers of duplicates produced were 80 for each variable including control.

In order to get uniform size and shape of pot, stoppers of 2 mm were used in the formation of bioplastic pot. Mixture

of bioplastic with newspaper pulp fibres was spread evenly on an aluminium foil. Then, the spread of bioplastic and newspaper pulp fibre mixture was dried in an oven at 70 °C temperature. Drying time of the spread was varied according to different ratios of bioplastic and newspaper pulp fibre mixture as shown in [Table 1](#). The purpose of drying spread of bioplastic and newspaper pulp fibre mixture was to enable the process of spread removal from aluminium foil easier.

After that, the spread of bioplastic and newspaper pulp fibre mixture was removed from aluminium foil and formed by using cylinder square mould. Formed bioplastic pots were dried in an oven at 70 °C for 24 h in order to achieve equilibrium with temperature and humidity of the surrounding. Shape of bioplastic pot was cylinder square with 35 mm width, 100 mm height and 2 mm thick.

2.4. Testing of bioplastic pot

Firstly, initial weight of bioplastic pots was taken. Then, *Leucaena leucocephala* seedlings were planted in bioplastic pots and their initial heights were measured. A total of 40 bioplastic pots from each variable with planted seedlings were tested below soil in order to test the degradability of the pot with soil contact. Another 40 bioplastic pots from each variable with planted seedlings were tested above ground in order to test the degradability of bioplastic pot above ground. Then, cleaned bioplastic pots were dried at 50 °C for 24 h in oven based on [Singh and Sharma \(2008\)](#). Dried bioplastic pots were left for 24 h. Weight of dried bioplastic pots was measured. The process of drying continued until dried bioplastic pots obtained stable weight. Percentage weight loss of pot was calculated by using the formula below based on [Liu et al. \(2010\)](#):

$$\text{Weight loss(\%)} = \frac{W_i - W_f}{W_i} \times 100\%$$

W_i = Initial oven-dry weight (g)

W_f = Final oven-dry weight (g)

3. Results and discussion

Bioplastic pot B75%:N25% has an average initial weight of 10.76 g while bioplastic pot B50%:N50% is 11.5 g. The average initial weight of bioplastic pots B25%:N75% and B0%:N100% (Control) is 10.18 and 3.50 g, respectively.

Descriptive statistics (mean and standard deviation) and result for Post Hoc Test (Tukey HSD) at 95% of confidence interval for percentage of weight loss for bioplastic pots with different ratios of bioplastic and newspaper pulp fibres which were tested at different ground levels and harvested at different time intervals are shown in [Table 2](#).

Weight loss of all bioplastic pots that were tested below ground only showed significance difference where $p \leq 0.05$ after 30 days of planting except for bioplastic pots B75%:N25% ([Table 2](#)). On the other hand, all bioplastic pots that were tested above ground also only showed significance difference where $p \leq 0.05$ after 30 days of planting. This may be due to the fact that the microorganism that will only grow rapidly after 30 days. In the study of "Analysis of biodegradability of three biodegradable mulching films", [Liu et al. \(2010\)](#) only observed microbial growth on samples that had been inoculated with soil suspension after 28 days. Hence, duration of soil burial testing

Table 1 Drying time of spread of bioplastic and newspaper pulp fibre mixture.

Ratios of bioplastic and newspaper pulp fibres	Drying time (minutes)
B75%:N25%	15
B50%:N50%	10
B25%:N75%	5
B0%:N100% (control)	0

Download English Version:

<https://daneshyari.com/en/article/827220>

Download Persian Version:

<https://daneshyari.com/article/827220>

[Daneshyari.com](https://daneshyari.com)