



6th BSME International Conference on Thermal Engineering (ICTE 2014)

Effect of Biodiesel-Diesel Blending on Physico-Chemical Properties of Biodiesel produced from *Moringa oleifera*

M. Mofijur^{a*}, H.H. Masjuki^b, M.A. Kalam^b, M.G. Rasul^a, A.E. Atabani^c, M.A. Hazrat^a,
H.M. Mahmudul^d

^a School of Engineering & Technology, Central Queensland University, Queensland 4701, Australia

^b Department of Mechanical Engineering, University of Malaya, 50603 Kuala Lumpur, Malaysia

^c Department of Mechanical Engineering, Faculty of Engineering, Erciyes University, 38039 Kayseri, Turkey

^d Faculty of Mechanical Engineering, University Malaysia Pahang, 26600 Pekan, Pahang, Malaysia

Abstract

The aim of this paper is to study the physical and chemical properties of *Moringa oleifera* biodiesel and its blends of 10%-90% by volume with petro-diesel according to the American society for testing and materials (ASTM D6751) standards and European standards (EN 14214). It was found that when *Moringa* biodiesel is blended with diesel fuel, all its fuel properties such as kinematic viscosity (KV), density (D), calorific value (CV), flash point (FP), cloud point (CP), pour point (PP), and cold filter plugging point (CFPP). For example, B10 reduce the viscosity of B100 from 5.05 mm²/s to 3.54 mm²/s (1.4:1). Then developed empirical models of properties are show high regression value (R²) between properties and MOME-diesel blend. It is believed that the results obtained and empirical model proposed in this study will help the researchers to predict the properties of biodiesel-diesel blend which are important parameters to design the fuel system of biodiesel engine.

© 2015 The Authors. Published by Elsevier Ltd. This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/by-nc-nd/4.0/>).

Peer-review under responsibility of organizing committee of the 6th BSME International Conference on Thermal Engineering (ICTE 2014)

Keywords: Fossil fuel; *Moringa oleifera*; Biodiesel production; Characterization; Blending.

* Corresponding author. Tel.: +61749309634
E-mail address: m.rahman@cqu.edu.au

1. Introduction

As the reserves of fossil energy resources are limited and decreasing day by day, discovering alternative energy sources has become one of the global agenda now a day. Biodiesel has gained popularity among the researchers as one of the alternative energy sources due to potential possession of reducing dependency on fossil diesel fuel, environmental pollutants, etc. [1-4]. Biodiesel can be obtained by employing the transesterification process of vegetable oils, animal fats, waste cooking oil and waste restaurant greases. The most common biodiesel sources from edible oils are palm oil, rapeseed oil, sunflower oil, coconut oil, peanut oil, *Jatropha curcas*, neem, cotton, jojoba, rubber, *Moringa oleifera*, Mahua, castor and animal tallow [5-7].

Recently, investigations have been carried out by numerous researchers [3, 8, 9] regarding the potential of biodiesel production from edible oil and non-edible oil sources and their utilization in a diesel engine. A few authors [9-13] have reported on the potential of biodiesel production from *Moringa oleifera*, a non-edible oil source but there is no extensive report on the characterization of *Moringa oleifera* biodiesel blend. *Moringa oleifera* is a member of the *Moringaceae* family, mainly grows in tropical countries. It is drought-tolerant pioneer species. The *Moringa oleifera* are most available in northwest India, Malaysia, Bangladesh, Africa, South America and Arabia, etc. [14]. It can grow up to 5 to 10 m. The plant starts bearing Pods 6-8 months after planting and reaches an average of 3 t of seed per hectare per year [15, 16]. The seeds of *Moringa oleifera* are triangular in shape which contains about 40% of oil by weight. The oil produced from the seed kernel of *Moringa oleifera* is golden yellow in color. It has been reported that *Moringa oleifera* oil contains higher amount of oleic acid and it is almost 74.41% of the entire fatty acid profile. Among all feedstocks, *Moringa oleifera* oil has a good potential to be converted into biodiesel and being non-edible oil source, it will not create the food versus fuel conflict. Thus the aim of this paper is to study the physical and chemical properties of *Moringa oleifera* biodiesel and its blends of 10%-90% by volume with petrodiesel according to the American society for testing and materials (ASTM D6751) standards and European standards (EN 14214).

Table 1: List of equipment used for properties test

Property	Equipment	Manufacturer	Test method
Kinematic viscosity	SVM 3000	(Anton Paar, UK)	ASTM D445
Density	SVM 3000	(Anton Paar, UK)	ASTM D1298
Oxidation stability	873 Rancimat	(Metrohm, Switzerland)	EN ISO 14112
Flash Point	Pensky-martens flash point - automatic NPM 440	(Norma lab, France)	ASTM D93
Cloud and Pour point	Cloud and Pour point tester - automatic NTE 450	(Norma lab, France)	ASTMD2500, ASTM D97
Cold filter plugging point	Cold filter plugging point tester - automatic NTL 450	(Norma lab, France)	ASTM D6371
Caloric value	C2000 basic calorimeter	(IKA, UK)	ASTM D240

2. Materials and methods

2.1 Materials

Crude *Moringa oleifera* oil (CMOO) was collected through a personal communication. All other chemicals, reagents and accessories were purchased from LGC Scientific Sdn Bhd. Table 1 shows the list of equipment that used for properties test.

Table 2 Physico-chemical properties of CMOO

Properties	Unit	CMOO	MOME	Diesel
Kinematic viscosity at 40 °C	mm ² /s	43.33	5.05	3.23
Flash point	°C	268.5	150.5	68
CFPP	°C	18	18	5
Pour Point	°C	11	19	0

Download English Version:

<https://daneshyari.com/en/article/856512>

Download Persian Version:

<https://daneshyari.com/article/856512>

[Daneshyari.com](https://daneshyari.com)