

International Symposium on Dynamic Response and Failure of Composite Materials, DRaF2014

## Low Velocity Impact Response Of Carbon Fibre Laminates Made By Pulsed Infusion

V. Antonucci<sup>a\*</sup>, M. R. Ricciardi<sup>a</sup>, F. Caputo<sup>b</sup>, A. Langella<sup>c</sup>, V. Lopresto<sup>c</sup>, A. Riccio<sup>b</sup> and M. Zarrelli<sup>a</sup>

<sup>a</sup> CNR Research National Council, IMCB, Inst. of Comp. and Biom. Mat., P.E. Fermi, Portici (NA), Italy

<sup>b</sup> Dpt. of Aerospace and Mechanical Engineering, Second University of Naples, via Roma, 29, Aversa (CE), Italy

<sup>c</sup> Dpt. of Chemical, Materials and Production Engineering, University of Naples "Federico II", P.le Tecchio, 80, Naples, Italy

---

### Abstract

Carbon fibre composites were subjected to low velocity impact tests. The scope was to investigate the response of laminates fabricated by a new vacuum assisted technology, labelled as "pulse infusion", under dynamic loads. At this aim, experimental tests up to complete penetration and at a different energy levels, were carried out. Some of the specimens were destined to CAI tests and the residual strength was evaluated. All the parameters involved in the phenomenon, like penetration energy and indentation depths, were studied to validate existing semi empirical models. By the comparison with results from literature, good agreements were found denoting the efficiency of the new fabrication method.

© 2014 The Authors. Published by Elsevier Ltd. This is an open access article under the CC BY-NC-ND license

(<http://creativecommons.org/licenses/by-nc-nd/3.0/>).

Peer-review under responsibility of the Organizing Committee of DRaF2014

*Keywords:* low velocity impacts; composite materials; indentation; pulsed infusion.

---

### 1. Introduction

Composites materials under dynamic loads can fail in a wide variety of modes. The integrity of the structural components can severely be reduced even if the visual damage is not evident.

The different impact damages can be collected in: a) external damages like indentation and b) internal damages (delamination), fibres cracks and matrix cracks. Moreover, the interaction between failure modes is very complex

---

\* Corresponding author. Tel.: +39 081 7758836; fax: +39 0817758850

E-mail address: [vinanton@unina.it](mailto:vinanton@unina.it)

and important in the understanding of damage initiation and propagation [1, 2, 3]. A lot of efforts were already done [1, 2, 3, 4] at the aim to investigate about the influence of the large number of parameters involved in the dynamic phenomena on the different modes of failure and the very complex impact response of composites. A large number of experimental tests were carried out but a lot of questions remain unanswered yet. Moreover, since the influence of a variety of parameters on the complex interaction between the failure modes, the damage can be hardly predicted by analytical and numerical tools [5, 6, 7].

Another very critical aspect in this field is represented by the fabrication methods that are always too expensive or enable to obtain good quality laminates. Moreover, since the impact damage is not always a visible damage, the techniques, in particular the non destructive ones, to observe, measure and analyse the failures, are continuously under attention.

Semi empirical models could be an essential tool to reduce testing time and costs in the development phase, especially for impact tests on large structures too expensive to be carried out in the development stage.

In this work, low velocity impact tests have been carried out on composites with the aim to supply useful information to develop an impact oriented design methodology. The laminates made by carbon fibres in polymeric matrix RTM6 were manufactured by a new vacuum-assisted technology named Pulsed Infusion. Impact tests at complete penetration were carried out to record the complete load displacement curve to obtain the penetration energy. On this curve, different energy values in correspondence of load drops or changing in slope, were obtained for the indentation tests. The indentation measured by a confocal microscope and the penetration energy were used to validate existing semi empirical models for the prediction of the impact energy and the residual strength. The agreement was quite good denoting the goodness (o efficiency) of the new adopted techniques.

## 2. Materials and experimental set up

The laminates made by carbon fibres in polymeric matrix RTM6 have been manufactured by a new vacuum assisted technology called pulsed infusion based on the use of a proper designed pressure distributor to control the pressure of the vacuum bag on the dry fiber and induces a pulsed transverse action to promote the through the thickness resin flow.

Unidirectional layers of dry fibre were overlapped following the stacking sequence [(0)/(90)/(+45)/(-45)]<sub>s</sub>, resulting in a nominal thickness of 2.5 mm.

The experimental tests have been carried out on a Ceast Fractovis drop weight machine, allowing to vary the impact energy by changing the impactor mass and the drop height. Impact tests were, first, carried out up to the complete penetration of the coupons. The instrumented impactor was cylindrical shaped hemispherical nose, 19.8 mm in diameter. The rectangular specimens, 100x150 mm, were clamped using a clamping device suggested by the EN6038 standard. The force-time and force-displacement curves obtained by the complete penetration tests were recorded by the DAS16000 acquisition program and successively studied to evaluate the penetration energy and the variable energy values for the indentation tests. The latter allowed the study of the damage initiation and propagation. The variable energies were measured in correspondence of characteristic points of the load curves like load drops or changing in slope clearly evidencing a change in material behaviour like it is possible to find in correspondence of a damage.

The load curves recorded in all the test conditions were used to evaluate the main impact parameters involved in the phenomenon like penetration energies and maximum forces, so as the correspondent displacements. Penetration and absorbed energy, first failure and maximum force have been measured.

The indentation depth was measured by confocal microscope LEICA DCM3D. This equipment gives the possibility to extract and record the three-dimensional shape of the surface from that it is possible to extract the section in correspondence of which derive the information about the profile and the measurement of the indentation depth left by the indenter.

## 3. Results: indentation and penetration

In [8], plotting the indentation depth against the non dimensional energy,  $U/U_p$ , for different thicknesses and material systems, an exponential law was found to describe the master curve collecting all the experimental

Download English Version:

<https://daneshyari.com/en/article/857605>

Download Persian Version:

<https://daneshyari.com/article/857605>

[Daneshyari.com](https://daneshyari.com)