

Short communication

A novel amperometric biosensor based on ZnO:Co nanoclusters for biosensing glucose

Z.W. Zhao^{a,e,*}, X.J. Chen^b, B.K. Tay^a, J.S. Chen^{c,d,**}, Z.J. Han^a, K.A. Khor^b

^a School of Electrical and Electronic Engineering, Nanyang Technological University, Singapore 639798, Singapore

^b School of Mechanical & Aerospace Engineering, Nanyang Technological University, Singapore 639798, Singapore

^c Department of Materials Science and Engineering, National University of Singapore, Singapore 119260, Singapore

^d Data Storage Institute, DSI Building, 5 Engineering Drive 1, Singapore 117608, Singapore

^e School of Electronic Science and Engineering, Southeast University, Nanjing, 210096, China

Received 4 December 2006; received in revised form 26 February 2007; accepted 19 March 2007

Available online 30 March 2007

Abstract

ZnO:Co nanoclusters were synthesized by nanocluster-beam deposition with averaged particle size of 5 nm and porous structure, which were for the first time adopted to construct a novel amperometric glucose biosensor. Glucose oxidase was immobilized into the ZnO:Co nanocluster-assembled thin film through Nafion-assisted cross-linking technique. Due to the high specific active sites and high electrocatalytic activity of the ZnO:Co nanoclusters, the constructed glucose biosensor showed a high sensitivity of $13.3 \mu\text{A}/\text{mA cm}^2$. The low detection limit was estimated to be $20 \mu\text{M}$ ($S/N = 3$) and the apparent Michaelis–Menten constant was found to be 21 mM, indicating the high affinity of the enzyme on ZnO:Co nanoclusters to glucose. The results show that the ZnO:Co nanocluster-assembled thin films with nanoporous structure and nanocrystallites have potential applications as platforms to immobilize enzyme in biosensors.

© 2007 Elsevier B.V. All rights reserved.

Keywords: ZnO; Nanoclusters; Glucose biosensor; Cross-linking

1. Introduction

Glucose biosensor, as one of the most popular biosensors, has been intensively investigated due to its importance in clinics, environment and food industry. Glucose oxidase (GOX) is often used as the enzyme in glucose amperometric biosensors to catalyze the oxidation of glucose and the reaction could be detected in a form of current at the electrode. Since the first glucose biosensor in 1962 (Clark and Lyons, 1962), extensive efforts have been made on the improvement of the performance and stability of enzyme electrodes, where modified electrodes with various configurations and the performance of the constructed biosensors have attracted great interests. Recent biosensor development is based on combing the properties of biologically active

substances with those of inorganic nanocrystalline materials. These inorganic materials with nanostructure could provide large surface to volume ratio and the increased surface activity, making their unique advantages over other conventional materials for enzymatic immobilization and signal transduction. They could keep activity of enzyme due to the desirable microenvironment, and enhance the direct electron transfer between the enzyme's active sites and the electrode (Zhang et al., 2004).

Up to now, many inorganic nanomaterials, such as gold nanoparticles and nanoclusters (Zhang et al., 2005; S. Zhao et al., 2006; Bharathi et al., 2001), Au/polyaniline nanocomposite (Xian et al., 2006), carbon nanotube (Liu et al., 2005), nanocrystalline diamond (Zhao et al., 2006), calcium carbonate nanoparticles (Shan et al., 2007) and Ag dendritic nanostructures (Wen et al., 2006), have been studied as signal transducers and platforms for the enzyme immobilization in biosensors. ZnO as a wide band gap (3.37 eV) semiconductor plays an important role in optics, optoelectronics, sensors, and actuators due to its semiconducting, piezoelectric, and pyroelectric properties (Norton et al., 2004; Sun and Kwok, 1999). Nanostructured ZnO not only possesses high surface area, nontoxicity, good bio-

* Corresponding author. Tel.: +86 25 83792250; fax: +86 25 83794756.

** Corresponding author at: Department of Materials Science and Engineering, National University of Singapore, Singapore 119260, Singapore. Tel.: +65 65167574; fax: +65 67763604.

E-mail addresses: zwszg@hotmail.com (Z.W. Zhao), msecj@nus.edu.sg (J.S. Chen).

compatibility and chemical stability, but also shows biomimetic and high electron communication features (Tian et al., 2002; Sberveglieri et al., 1995; Rodriguez et al., 2000), making it great potential applications in biosensors. Zhang et al. (2004) have reported a reagentless uric acid biosensor based on ZnO nanorodes. Recently, GOx was immobilized on ZnO nanocombs and nanorods to construct an amperometric biosensor for glucose biosensing (Wang et al., 2006; Wei et al., 2006), showing a sensitivity of 15–23 $\mu\text{A}/\text{mA cm}^2$.

Nanoclusters, as a bridge between molecules and bulk materials, are aggregates of a small and finite number of atoms or molecules, which could be ranged from several atoms up to large nanoclusters made up of several tens of thousands of atoms. The nanocluster-assembled thin films/materials have attracted increasing interests due to novel properties and technological applications. In addition to their small nanocrystallites in several nanometers, ZnO-based nanoclusters possess nanoporous network structure, making them different from previous ZnO nanorods, nanocombs, nanowires and other low dimensional nanostructures. In our group, the unique optical and magnetic properties of the ZnO-based nanoclusters (Zhao et al., 2007) have been demonstrated. Cobalt shows high electrocatalytic activity for the oxygen reduction and low detecting potential for hydrogen peroxide, posing it great potential application in fuel cell and biosensor development (Cataldi et al., 1995). In this work, ZnO:Co nanoclusters (doping 2% Co in ZnO) with small average size of 5 nm and density as low as one-third of ZnO bulk materials were developed and employed for the first time to construct a novel amperometric glucose biosensor by taking the advantages of the high electrocatalytic activity of ZnO and cobalt and the high specific surface area of the nanocluster structure.

2. Experiments

2.1. Reagents and material

The glucose oxidase (EC1.1.3.4, from *Aspergillus niger*, 200 units/mg), β -D-(+)-glucose, 25% glutaraldehyde and bovine serum albumin (BSA) were obtained from Sigma–Aldrich and used without further purification. The buffer solutions were prepared from 0.08 M K_2HPO_4 and 0.02 M KH_2PO_4 (99.9%, Sigma–Aldrich). All the solutions were prepared with a Millipore Q water (resistance: $\sim 18.0 \text{ M}\Omega \text{ cm}^{-1}$). Glucose stock solutions were prepared and kept overnight at room temperature before use to allow mutarotation. The poly(ethylene terephthalate) (PET) plate used as a substrate for electrode was purchased from Goodfellow with a thickness of 200 μm .

2.2. Synthesis of nanocluster-assembled ZnO:Co thin films

ZnO:Co nanoclusters, produced by a magnetron sputtering gas aggregation source, were obtained by a nanocluster-beam deposition system as described in the literature (Chen et al., 2005; Zhao et al., 2005). The growth region was cooled with liquid nitrogen and kept the temperature at 170 K. A 2 in. metal target consisting of 98% Zn and 2% Co was used and DC sputter-

ing power was 130 W. Ar, He and O_2 gases with a corresponding total pressure of 0.75 Torr were introduced into the system, and ZnO:Co nanoclusters were thus formed and further deposited onto the substrates.

2.3. Fabrication of PET/Ti/Au/ZnO:Co electrode

Metal Ti thin layer on PET plate was implanted by plasma immersion ion implantation technology at 12 keV with a dose of 10^9 ions/ cm^3 , where the Ti ions were obtained from the plasma generated by a filtered cathodic vacuum arc source with an arc current of 90 A. The Ti layer thickness including the penetration depth in PET was about 20 nm. After that, Au layer with thickness of 30 nm was deposited on Ti-implanted PET substrate by DC magnetron sputtering with power of 20 W at room temperature. This process makes the Au layer well adhesive to Ti/PET substrate with excellent conductivity ($20 \Omega/\text{sq}$). The obtained PET/Ti/Au electrode was then loaded to the chamber of nanocluster-beam system for the deposition of ZnO:Co nanoclusters. The thickness of nanocluster-assembled thin film was around 300 nm.

2.4. Immobilization of glucose oxidase on PET/Ti/Au/ZnO:Co electrode

GOx solution was prepared by dissolving 30.0 mg GOx and 20 mg BSA in 1.0 mL phosphate buffer solution (PB, 0.1 M, pH 7.4). Cross-linking method was employed to immobilize glucose oxidase on PET/Ti/Au/ZnO:Co electrode. In brief, 100 μL above GOx solution, 50 μL 2.5% glutaraldehyde and 50 μL 0.5% Nafion solution were mixed thoroughly. Subsequently, 4 μL above mixture solution was applied onto the PET/Ti/Au/ZnO:Co electrode surface and allowed to dry in air at room temperature. Finally, 4 μL 0.5% Nafion was further coated on the enzyme electrode to eliminate the possible fouling and prevent the leaching of the enzyme. The enzyme electrodes were kept dry in refrigerator at 4 °C when not in use.

2.5. Characterization and amperometric measurement

Surface morphology of ZnO:Co nanoclusters was characterized using atomic force microscopy (AFM) in tapping mode (Dimension 3000 scanning probe microscope from Digital Instrument). Transmission electron microscopy (TEM, JEOL 2010) operated at 200 keV was used for the examination of microstructure of the obtained ZnO:Co nanoclusters on carbon coated copper grid. X-ray photoelectronic spectroscopy (XPS) was used to study the chemical states of the film. All the amperometric measurements of the enzyme electrodes were carried out in an Autolab electrochemical analyzer (Autolab/PGSTAT30, ECO CHEMIE, Netherlands). A conventional three-electrode configuration was employed consisting of a fabricated PET/Ti/Au/ZnO:Co electrode as the working electrode, a platinum foil as the counter electrode, and a Ag/AgCl, KCl (3 M) electrode as the reference electrode. The amperometric response measurements were carried out in phosphate buffer solution (PB, pH 7.4) at applied potential of 0.8 V versus Ag/AgCl reference

Download English Version:

<https://daneshyari.com/en/article/870183>

Download Persian Version:

<https://daneshyari.com/article/870183>

[Daneshyari.com](https://daneshyari.com)